

MasterRoc[®] MP 307 CE

Low viscosity, fast reacting acrylic resin for permanent water sealing and layer curtaining of concrete and masonry

DESCRIPTION

MasterRoc MP 307 CE is a highly reactive two-component acrylic sealing resin with a low viscosity for good penetration. The product cures quickly, forming a rubber-like resin with the ability to withstand certain ground and crack movement. **MasterRoc MP 307 CE** is especially designed for concrete repair and is CE certified according to EN 1504-5.

TYPICAL APPLICATIONS

- Concrete repair - swelling fitted filling of cracks and fissures (EN 1504-5: category S)
- Curtain injection
- Permanent water sealing of tunnel and shaft concrete linings and masonry
- Stopping of minor water inrush through cracks
- Injection hose applications
- Ground stabilization

ADVANTAGES

- Upon curing forms a highly flexible compact resin with good adhesion properties even on damp and wet surfaces
- Due to the special latex emulsion of Part B the cured system is rubber-like and strong but still extremely flexible
- Very low viscosity (close to water) allows deep penetration at low pressure into very fine cracks or fissures and long flow paths
- Withstands a permanent water pressure of more than 12 bar
- Superior flexibility (elongation at break >300%) enabling balance of ground movements or settlements
- Not sensitive to water and always stays close to its original shape (maximum change of mass -15% to +20%)
- Neither the liquid nor the cured resin is corrosive and is therefore suitable for reinforced concrete structures
- Good chemical resistance against acids, bases, solvents, fuels, etc

- Environmentally friendly: harmless in contact with groundwater and does not emit any dangerous substances

PACKAGING

MasterRoc MP 307 CE Resin: 20kg can
MasterRoc MP 307 CE Accelerator: 1kg can
MasterRoc MP 307 CE Part B: 20kg can
MasterRoc MP 307 CE Hardener: 0.3kg can

TYPICAL PROPERTIES*

MasterRoc MP 307 CE Resin

| | |
|------------------|--------------|
| Appearance | Clear liquid |
| Viscosity (20°C) | 5 mPa·s |
| Density (20°C) | 1.05kg/l |
| VOC content (%) | 0 (zero) |

MasterRoc MP 307 CE Accelerator

| | |
|------------------|--------------|
| Appearance | Clear liquid |
| Viscosity (20°C) | 2 mPa·s |
| Density (20°C) | 0.93kg/l |
| VOC content (%) | 0 (zero) |

MasterRoc MP 307 CE Part B

| | |
|------------------|--------------|
| Appearance | White liquid |
| Viscosity (20°C) | 12 mPa·s |
| Density (20°C) | 1.01kg/l |
| VOC content (%) | 0 (zero) |

MasterRoc MP 307 CE Hardener

| | |
|-----------------|-----------------|
| Appearance | White solid |
| Density (20°C) | Approx. 2.6kg/l |
| VOC content (%) | 0 (zero) |

Mixed material (mixing ratio Resin : Part B of 1:1)

| | |
|---------------------|------------------|
| Appearance | White liquid |
| Viscosity (20°C) | 7 mPa·s |
| Density (20°C) | 1.03kg/l |
| Gel time (20°C) | 3 to 22 minutes |
| Final curing (20°C) | 10 to 25 minutes |

MasterRoc[®] MP 307 CE

APPLICATION GUIDELINES

Premix the Resin (20kg) with 5% of accelerator (1kg) to activate it prior to use.

To prepare Part B, dissolve 0.20% (40g) to 5% (1kg) of hardener powder into 20 l of Part B and (the same volume of Part B as of activated resin). The amount of hardener is adjusted to the needed pot life (see Table 1).

The activated resin and Part B have a pot life of approx. 5 hours at 20°C. The activated components are injected in the ratio of 1:1 by volume, using a two-component injection pump, equipped with a static in-line mixer or by premixing the two components thoroughly and using a one-component pump (long open time needed).

For steel reinforcement injection, the amount of hardener powder should be limited to 1.5% (e.g. 300g).

Table 1: Hardener dosage to adjust gel time

| Amount of MasterRoc MP 307 CE Hardener | | | |
|--|---------------------|------------------------|------------------------|
| (%) | (g) per 20kg Part B | Gel time at 10°C (min) | Gel time at 20°C (min) |
| 0.2 | 40 | 24:18 | 22:00 |
| 0.25 | 50 | 21:42 | 20:17 |
| 0.5 | 100 | 17:15 | 15:17 |
| 1 | 200 | 13:10 | 09:40 |
| 1.5 | 300 | 09:40 | 07:10 |
| 3 | 600 | 05:46 | 04:30 |
| 5 | 1000 | 03:40 | 03:30 |

CE certification tests have been carried out with 0.25% of Hardener powder.

Please Note: The reaction time is dependent on the temperature of the components and the ground.

The components can be prepared accordingly using water instead of **MasterRoc MP 307 CE** Part B. Please note that for this composition, the CE testing has not been done.

CLEANING OF INJECTION EQUIPMENT

Equipment can easily be cleaned of uncured material using water (if possible with a detergent).

STORAGE AND SHELF LIFE

In unopened, tightly closed containers, the components of **MasterRoc MP 307 CE** can be stored for up to 12 months, if kept dry and within a temperature range of +10°C to +30°C, protected from sunlight.

HEALTH AND SAFETY

Please refer to the Material Safety Data Sheet for further safety measures.


Avoid contact with skin and eyes by using the required personal protective equipment, such as overalls, gloves and safety glasses.

If contact with skin occurs, wash thoroughly using soap and water. If contact with eyes occurs, rinse thoroughly with water and seek medical advice.

The cured **MasterRoc MP 307 CE** is harmless.

Uncured products should be prevented from entering local drainage systems and water courses. Spillage must be collected using absorbent materials such as sawdust and sand, and disposed of in accordance with local regulations.

MasterRoc® MP 307 CE

| | |
|--|---|
|  | |
| MasterRoc® P 307 CE | |
| BASF SE Underground Construction Salzachstrasse 2-12 68199 Mannheim Germany | |
| 12 | |
| EN 1504-5 | |
| Injection product for swelling fitted filling of cracks, fissures and voids | |
| U (S2) W (1) (1/2/3) (5/40) | |
| Water tightness | 7·10 ⁵ Pa |
| Viscosity | ≤ 60 mPa.s |
| Corrosion behavior | no corrosion |
| Change in volume / mass by air drying and water immersion | Air drying: approx. -15% Water immersion: approx. +20% |
| Sensitivity to water | passed |
| Sensitivity to wet-drying cycles | passed |
| Compatibility with concrete | passed |
| Application temperature | +5°C to +40°C |
| Dangerous substances | Comply with 5.4 |

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

MBS_CC-UAE/Roc_MP307CE/v1/03_17/v2/04_19

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
Construction Chemicals LLC
 P.O. Box 37127, Dubai, UAE
 Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae

Disclaimer: the TUV mark relates to certified management system and not to the product mentioned on this datasheet



A brand of
MBCC GROUP