

MasterRoc[®] MP 355 1K

One component polyurethane injection foam to stop small to mid-volume water ingress

DESCRIPTION

MasterRoc MP 355 1K is a solvent free, one component polyurethane foam which reacts only in contact with humidity or water.

TYPICAL APPLICATIONS

- Stopping of small to mid-volume water ingress in underground structures
- Also suitable for filling of water bearing voids

ADVANTAGES

- Reacts in moist surroundings
- Good bonding to wet surfaces

PACKAGING

MasterRoc MP 355 1K: 25 kg cans
 Accelerator for **MasterRoc MP 355 1K:** 2.5 kg cans

TYPICAL PROPERTIES*

MasterRoc MP 355 1K

Density, 20°C	1.16 g/cm ³
Viscosity, 23°C	320 mPa.s
Color	Brown
Application temperature	+ 5°C to 40°C
Maximum foam expansion rate at 10% accelerator dosage	25-30

Accelerator for MasterRoc MP 355 1K

Density, 20°C	1.10 g/cm ³	
Viscosity, 23°C	70 mPa.s	
Color	Clear	to yellowish

APPLICATION GUIDELINES

Add the accelerator to **MasterRoc MP 355 1K** (up to 10%, depending on the required reaction time), mix quickly and thoroughly. Inject the mixture through a single component injection pump. The moisture / water in the ground will generate a foaming reaction. In the case of dry ground, flush the borehole with water before injecting.

To achieve the best mixing of the components during injection, the inclusion of a static in-line mixer in connection with the mixing head is strongly advised. The length of the static mixer should be approximately 32 cm.

Note: **MasterRoc MP 355 1K** is not suitable for large volume void filling.

REACTION TIME

The reaction time depends on the ground and product temperature, as well as the accelerator dosage (see Table 1). Site trials should be performed in advance to establish the required reaction time.

Table 1:

Reaction Times with 10% water and 10% accelerator				
Initial Temperature (°C)	5	10	15	20
Start of reaction (sec)	120	60	25	10
End of reaction (sec)	300	200	110	50
Foam expansion rate (approximately)	25	25	25	30

MasterRoc[®] MP 355 1K

CLEANING OF INJECTION EQUIPMENT

During short breaks in the injection procedure, the pump and hoses should be filled with non-accelerated resin to avoid blockages. After finishing the injection, pump an appropriate agent or oil which does not contain water through the pump and injection lines.

STORAGE AND SHELF LIFE

MasterRoc MP 355 1K must be stored in airtight containers in a cool, dry place. If stored in original containers under the above mentioned conditions, it has a shelf life of 12 months. The product must be prevented from freezing.

HEALTH AND SAFETY

MasterRoc MP 355 1K is not hazardous. However, follow standard safety procedures when handling the product and wear gloves and safety glasses.

Avoid eye and skin contact. If skin contact occurs, wash with plenty of water and soap. In case of eye contact rinse with plenty of water and seek medical advice. For further information refer to Material Safety Data Sheet.

Uncured products should be prevented from entering local drainage systems and water courses. Spillage must be collected using absorbent materials such as sawdust and sand, and disposed of in accordance with local regulations.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

MBS_CC-UAE/Roc_MP3551K/v2/07_14

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
Construction Chemicals LLC
P.O. Box 37127, Dubai, UAE
Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae

Disclaimer: the TUV mark relates to certified management system and not to the product mentioned on this datasheet



A brand of
MBCC GROUP