

MasterTop[®] 500

Mortar bonding agent for bonded screeds and cementitious mortars

DESCRIPTION

MasterTop 500 is a mortar bonding agent for bonding screeds and cementitious mortars. For indoor and outdoor use.

TYPICAL APPLICATIONS

MasterTop 500 is recommended for:

- indoor and outdoor use
- for walls and floors
- bonding agent for repair mortar, ready-to-mix mortar for fast-track screeds, drain and screed-mortar and sand-cement mortar
- Bonding agent for the installation of fast setting screeds based on binder as well as for conventional cement screeds.
- Bonding agent for the production of bonded coverings in industrial and commercial areas an also for sloping screeds on balconies and terraces.
- Bonding agent for natural stone insensitive to staining and non-translucent.

ADVANTAGES

- Highly secure bonding. Following the appropriate preparation of the substrate, a powerful bond is formed between the cement-based substrate and the conventional cement screeds
- Waterproof and frost resistant, suitable for universal internal and external use

PACKAGING

MasterTop 500 is packaged in 25 kg PE lined heavy duty paper bags.

TYPICAL PROPERTIES*

Physical form	Powder
Components	1 part
Granulometric grading	0 – 2.2 mm
Material base	Special cement, polymers and aggregates
Labelling for - Regulation for hazardous goods on roads - Regulation for hazardous substances	- Non hazardous - Irritant, contains cement
Layer thickness	Approx. 1.5 mm
Working temperature	+5°C to +30°C (temperature of substrate and circulating air)
Quantity of gauging water	
- for 25 kg bag	- approx. 6 L
- for 1 kg powder	- approx. 240 ml
Mixing time	Approx. 3 min
Working time*	Approx. 1 h

* At 23°C and 50% relative humidity. Higher temperatures reduce, lower temperatures increase the times given.

APPLICATION GUIDELINES

1. Pour 2/3 of the gauging water in a clean mixing container, add **MasterTop 500** and mix for at least 3 minutes to form a lump-free bonding slurry. Add the rest of gauging water and mix again. Quantities up to 25 kg can be mixed with a suitable paddle attached to a high-speed mixer. Larger quantities should be mixed in a blade-type concrete mixer.
2. Apply the mixed **MasterTop 500** immediately to the prepared surface and work in thoroughly using a hard broom for floors or a brush for walls. Fully cover the whole surface area with the bonding agent. Do not allow the bonding agent to dry.

MasterTop® 500

- Immediately after applying **MasterTop 500**, apply the screed mortar or cement mortar to be installed wet on wet.

PREPARATION OF THE SUBSTRATE

The substrate must be clean, sound, open-pored, absorbent and sufficiently rough. In the case of bonded coverings exposed by heavy use, the concrete substrate must comply with grade B 25 as a minimum.

Extremely impermeable and smooth substrates, any layers which are not able to bear weight and also damaged concrete surfaces must be roughened and/or removed by appropriate methods, e.g. jet blasting with solid blasting agents or high-pressure water jets.

Wet the pre-treated cementitious substrate at least 2 hours, and if possible 24 hours, before applying **MasterTop 500**. Keep it sufficiently damp. Before applying the slurry, the surface should be mat and damp but must not be wet! Avoid puddles forming.

CLEANING

Clean tools, mixing and work equipment with water immediately after use. When product is dry, cleaning is only possible by mechanical means.

COVERAGE / YIELD

Approx. 2 to 2.5 kg of dry mortar / m².

Remarks

- Do not work with **MasterTop 500** when substrate temperatures are below +5°C and above +30°C, or in conditions where heat or wind may have a strong effect.
- Substrates treated with water-repellent waterproofing agents or evaporation protection must be pretreated.
- Only mix a quantity of **MasterTop 500** that can be used within an hour.
- On large areas apply the slurry in sections. Any further work must be carried out wet on wet.

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
 Construction Chemicals LLC
 P.O. Box 37127, Dubai, UAE
 Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae



A brand of
MBCC GROUP

Disclaimer: the TUV mark relates to certified management system and not to the product mentioned on this datasheet

- The bonding agent must be applied to cover the whole area completely, minimal thickness is 1.5 to 2 mm.
- Never add water or wet **MasterTop 500** to a **MasterTop 500** slurry which has already started to set.

STORAGE AND SHELF LIFE

Shelf life is 12 months when stored in dry conditions, no permanent storage over +30°C.

HEALTH AND SAFETY

MasterTop 500 contains cement. Contact with moisture or gauging water sets off an alkaline reaction which may cause skin irritation and/ or caustic burns to mucous membranes (e.g. eyes). Risk of serious damage to eyes, therefore avoid contact with eyes and prolonged contact with skin. In case of contact with eyes immediately rinse with plenty of water and consult a doctor. In case of contact with skin change contaminated clothing immediately and wash skin with plenty of soap and water. Wear appropriate protective gloves (e.g. cotton gloves soaked in nitrile). Keep out of reach of children. If ingested seek prompt medical attention and show packaging or this product data sheet.

QUALITY AND CARE

All products originating from Master Builders Solutions Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001 and ISO 14001.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

MBS_CC-UAE/Top_500_03_10/v1/11_13/v2/12_19