

MasterEmaco® S 423 (Formerly known as Eski Adı Emaco® S23 NB)

Cement-Based Grout

DESCRIPTION OF PRODUCT

MasterEmaco® S 423, is cement based one part, high strength, polymer modified, and self compacting non-shrink grout.

FIELDS OF APPLICATION

MasterEmaco® S 423 is used in;

- Large volume repairs,
- High rise buildings such as beams, columns and walls
- Columns, piers and cross beams on highway structures
- Marine and other civil structures
- Tunnels, pipes and other below ground construction
- Fixing of pre-cast concrete elements
- Fixing of the turbines on the foundations
- Fixing of the generators, compressors and pumps on the foundations
- Fixing of the industrial machines on the foundations
- Fixing of the steel columns on the RC foundations
- Filling of the voids in the jacketing applications

FEATURES AND BENEFITS

- Mixed with only water and can be applied easily
- High compressive strength
- High fluid consistency
- Free of bleeding
- Resistant to water and weather conditions
- Perfect bonding to the concrete and steel
- Water proof
- Non-Shrink

APPLICATION PROCEDURE


Preparation of Machine and Foundation

The concrete should be free of frost, curing membranes, waterproofing treatments, oil stains, laitance, friable material and dust. The concrete surfaces should be chipped and if there is a water leakage it must be drained or properly plugged. Base plate, rods and bolts should be free of oil stains, grease and dust. Enough number of holes should be opened on the base plate for air drain. Machine should be assembled and balanced before grouting. The concrete surfaces should be saturated with water at least 6 hours before the grouting.

Formwork Preparation

The form material should be waterproof and resistant to hydrostatic forces of the grout. Formwork installation should be done against the possible leakage of the cement paste. An opening should be designed in the formwork with a width of 5 cm at minimum for pouring the grout. For providing a constant pressure for easy compacting of the grout the forms should be as high as possible in the pouring side. In grouting of huge base plates, special pipe and pump systems can be used or grout can be prepared with 5% extra water. For preventing the pressure releases, the forms should be placed without any tolerances and gaps between the concrete and form material.

TECHNICAL DATA

Product Chemistry	Mineral fillers, and polymer modified cement	
Colour	Grey	
Compressive Strength (TS EN 12190)		
1 day	>30 N/mm ²	
7 day	>50 N/mm ²	
28 day	>60 N/mm ²	
Flexural Strength (28 day) (TS EN 196)	>8 N/mm ²	MK
Bonding Strength (28 day)		
To concrete	>2 N/mm ²	
To steel	>2 N/mm ²	
Elasticity Modulus (28 day) (TS EN 13412)	>20,000 N/mm ²	
Application Modulus	Min. 20 mm Max. 100 mm	
Application Temperature	+5°C + 30°C	
Service Temperature	-20°C + 400°C	
Pot Life	45 minutes	
Fully Cured at 23°C	28 day	

*Depending up on the area thicker applications can be done. Please apply **Master Builders Solutions**

**Typical values are obtained from the test results of 4x4x16 mortar prism in 23°C and 50% relative humidity conditions. High temperatures shortens the curing and working time, lower temperatures extends the durations

MasterEmaco® S 423 (Formerly known as Eski Adı Emaco® S23 NB)

Cement-Based Grout

Mixing

Add enough water into a clean mixing bucket by using a proper water gauge. Add the powder into the bucket slowly and continuously. Mix the fresh mortar with a proper electrical mixer (300-600 rpm) for 4 minutes until having a homogenous consistency. Let the mortar have rest for 4 minutes and re-mix for 30 seconds.

Mixing Ratio

MasterEmaco® S 423	Part A	Part B
Quantity	<0,12 liter	<3,00 liter
Mixed Density	-2,42 kg/liter	

APPLICATION METHOD

In the case of operating neighbour machines, a glass of water should be put on the groutin base and the vibrations caused by the environment can be observed. If needed, surrounding machines should be swith off until (10-10 hours in 20°C) the grout sets. **MasterEmaco® S 423** should be poured directly into the formwork or it should be pumped under pressure. Application thickness should be 2-10 cm. For pre-venting the possible air gaps in the formwork, pour the grout from single opening and let the air draining. For thicker applications second layer of the mortar should be applied in same way or consult to the **Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.** technical. Open areas should be protected from the rain, wind, etc. Aggressive whether conditions during the first 24-48 hours after finishing repair by using wet clothes, curing membranes etc.

COVERAGE

22 kg/m² for obtaining 1 cm thick layer

WATCH POINTS

- During the application the substrate and environment temperature should be between 5-30°C.
- Open areas should be protected from the rain, wind, etc. Aggressive whether conditions during the first 24-48 hours after finishing repair.
- Cement based materials' pot life and curing times vary depending on the relative humidity, substrate and environment temperature. Reaction gets slow in low temperatures and it causes to extension on pot life and working time. On the other hand high temperatures speed up the reaction, which results to short pot life and working time. For full curing of material, both the substrate and environment temperature shouldn't be under allowed application temperature.
- Do not use **MasterEmaco® S 423** in case of contacting to liquids with a PH under 5.5.
- Do not use vibrator for placing the mortar.
- In low temperatures (5°C-10°C) the following precautions should be taken;
 - o The product should be stored in warm conditions,

- o Hot water (30°C-50°C) should be used for mixing,
- o Grouting area should be heated and protected from cold.
- In high temperatures (25°C-30°C) the following precautions should be taken;
 - o The product should be stored in cool conditions,
 - o Cold water (0°C-10°C) and ice should be used for mixing.

CLEANING OF TOOLS

After the application all tools should be cleaned with water. **MasterEmaco® S 423** can be cleaned with only mechanical abrasion after hardening.

PACKAGING

25 kg bag

STORAGE

Store in original container in cool (+5°C - +25°C) and dry indoor conditions.

SHELF LIFE

12 months under proper storage conditions after production date.

HEALTH AND SAFETY PRECAUTIONS

It is dangerous to approach the application sites. During the application, a protective apparel, protective gloves, goggles and masks which comply with the Occupational Health and Safety Rules should be used. Due to the irritation effect of the uncured materials, the mixtures should not come into contact with skin and eyes; in case of contact, the affected area should be washed with plenty of water and soap; in case of swallowing, a physician should be consulted immediately. No food or beverages should be brought to the application area. The product should be stored and kept out of reach of children. For detailed information please consult the Material Safety Data Sheet.

DISCLAIMER

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. **Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.** is only responsible for the quality of the product **Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.** is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding the place and the method of use. This technical form is valid only till a new version is implemented and nullifies the old ones.

MasterEmaco® S 423 (Formerly known as Eski Adı Emaco® S23 NB)

Cement-Based Grout

CONTACT INFORMATION

**Master Builders Solutions Yapı Kimyasalları
Sanayi ve Ticaret Ltd. Şti.**

Adres: Barbaros Mah. Begonya Sok.

Nidakule Kuzey Ataşehir, C Kapısı

No:3 E/5, 34746 Ataşehir İstanbul / Türkiye


Tel: 0216 217 88 00

Mail: mbs.tr@mbcc-group.com

Web: www.master-builders-solutions.com/tr-tr

® Registered trademark of a MBCC Group member in many countries of the world

MasterEmaco® S 423 Technical Data Sheet -Revision
Date: 12/2020

	
1020 Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti. Adres: Barbaros Mah. Begonya Sok. Nidakule Kuzey Ataşehir, C Kapısı No:3 E/5, 34746 Ataşehir İstanbul 20 1020 – CPR – 040 065838 DOP NO: 02.1504.3.007	
EN 1504-3:2005 MasterEmaco S 423 Yapısal olan ve yapısal olmayan tamir (Structural and Non-Structural Repair Mortar) Sınıf R4 (Class R4)	
3.1 Elle harç uygulaması (Concrete restoration by applying mortar by hand)	
3.2 Yeniden beton dökülmesi (Concrete restoration by recasting with concrete)	
4.4 Harç veya beton ilavesi (structural strengthening by adding mortar or concrete)	
7.2 Bozunmuş betonun yenilenmesi (Replacing contaminated or carbonated concrete)	
Basınç Dayanımı (Compressive Strength)	≥ 45 N/mm ²
Klorür İçeriği (Chloride ion Content)	≤ % 0,05
Adezyon Dayanımı (Adhesive bond)	≥ 2,0 N/mm ²
Isıl uyumluluk Bölüm 1: Donmaçözülme (Thermal compatibility, freeze-thaw)	≥ 2,0 N/mm ²
Isıl uyumluluk Bölüm 2: Yüksek sıcaklık farkıyla birlikte yağmur etkisi (ısıl şok) (Thermal compatibility, thunder shower)	≥ 2,0 N/mm ²
Isıl uyumluluk Bölüm 4: Kuru-çevrim (Thermal compatibility, dry cycling)	≥ 2,0 N/mm ²
Elastisite Modülü (Elastic Modulus)	≥ 20 Gpa
Yangına tepki (Reaction to fire)	A1
Tehlikeli maddeler (Dangerous substances)	Madde 5.4'e uygun (Comply with clause 5.4)