

MasterRoc® SA 160 (Formerly known as Meyco® SA 160)

Alkali-Free, Liquid High Performance Set Accelerator for Sprayed Concrete

DESCRIPTION OF PRODUCT

MasterRoc® SA 160 is a high performance alkalifree set accelerator for sprayed concrete, whose dosage can be varied to the desired setting and hardening times.

FIELDS OF APPLICATION

- Temporary and permanent ground support in tunneling and mining
- Slope stabilisation
- Also suitable for acceleration of cementitious grouts, such as for annulus grout in TBM tunnels, cemented ground injection and foam concrete.

FEATURES AND BENEFITS

MasterRoc® SA 160 is ideally suited for wet mix sprayed concrete for ground support:

- The quick setting property allows rapid work progress and the ability to construct thick sprayed concrete linings via layered application during one construction sequence.
- The unique product formulation provides fast setting, continuous early-age strength development high durability and good long term strength.
- Very low dust generation during application and therefore a good working environment.
- Possibility of low rebound applications when using the correct nozzle angle and distance.
- Non-aggressive properties provide improved working safety, reduced environmental impact and lower handling costs.

APPLICATION PROCEDURE

The substrate should be clean and free from loose particles and preferably damp. It is recommended to use only fresh cement as the age of the cement can have a negative influence on the setting characteristics of the mix. **MasterRoc® SA 160** can be sensitive to the type of cement. With some cements the setting characteristics can be too slow. We recommend the use of Portland

cements (PC/HPC), which normally give faster setting than blended or sulphate resistant cement types. However, **MasterRoc® SA 160** also works well with composite cements types (blended cements, fly-ash/slag). In all cases, it is strongly recommended to carry out preliminary tests to check setting and the 24 h strength of the cements planned for use in a project.

Evaluation of setting and 24 h strength should be carried out on a test mortar in accordance with EFNARC European Specification for Sprayed Concrete (1996), Appendix 1, Clause 6.3.

The following results should be taken as a performance guide only:

Initial set	Final set	24 h strength	Rating
2 min.	6-8 min.	18-20 MPa	good
5 min.	8-12 min.	12-15 MPa	OK
>10min.	>15 min.	<10MPa	poor

Concrete Mix

When **MasterRoc® SA 160** is used for wet mix spraying, the w/c+b ratio should be below 0.5 and preferably <0.45. When targeting extremely high early strength, 0.40 or lower. The lower w/ c+b ratios provide faster setting, higher early strength, better durability, lower accelerator dosage and thicker layers can be applied overhead.

PACKAGING

MasterRoc® SA 160 is supplied in 300 kg drums, 1400 kg containers or in bulk.

DOSING SYSTEM

MasterRoc® SA 160 is added at the nozzle. It is essential to have a constant and accurate dosage of accelerator into the concrete stream.

To ensure quality sprayed concrete, follow the pump selection guidelines given below:

Works very well with:

- Mono pumps (stator & rotor pumps)
- Peristaltic pumps (Bredel)

TECHNICAL DATA

Form	Suspension
Color	Beige
Density (+20°C)	1.44 ± 0.03 g/ml
Ph value (1:1 water solution)	2.5 ± 0.5
Viscosity ¹⁾	675 ± 325 mPa.s
Thermal stability	+5°C to +35°C
[Na ₂ O] EQV. (%bw) Chloride Free	<1%

¹⁾Brookfield, +20°C. Viscosity is dependent on degree of product agitation and temperature.

MasterRoc[®] SA 160 (Formerly known as Meyco[®] SA 160)

Alkali-Free, Liquid High Performance Set Accelerator for Sprayed Concrete

Should not to be used with:

- Piston pumps
- All pumps with ball and seat valves
- Pressure tanks
- Gear pumps

Do not use a filter on the suction hose as this causes obstructions. Preferably draw the material off the bottom of the drum/container.

Compatibility with Other Accelerators

MasterRoc[®] SA 160 can be interchanged with most of **Master Builders Solutions**'s alkali-free accelerators. For advice please contact your local **Master Builders Solutions** representative.

Do not mix or interchange **MasterRoc[®] SA 160** with any type of accelerator produced by another manufacturer, as this can cause immediate clogging of dosing pumps and hoses.

CONSUMPTION

The consumption of **MasterRoc[®] SA 160** also depends on the w/c+b ratio, temperature conditions (concrete and ambient), cement reactivity and on required layer thickness, setting time and early strength development. The consumption is normally in the range of 3 to 10% of binder weight.

Overdosing (>10%) may result in decreased final strength.

CLEANING OF DOSING PUMP

After the use of **MasterRoc[®] SA 160**, the dosing pump and other parts of the system must be thoroughly cleaned with plenty of water. Failure to do so provokes blockages in the dosing system when next used. Make sure that all operators involved in testing and application are fully informed.

STORAGE

- Must be stored at minimum +5°C and maximum +35°C (optimum temperature for storage and performance +20°C).
- Has to be kept in closed containers made of plastic, glass fiber or stainless steel.
- Must not be stored in normal steel containers.
- Storage in bulk tanks requires the use of agitation and/or circulation systems.
- After prolonged storage or transport we recommend to fully agitate it prior to use by mechanical stirring or re-circulation pumping.
- If stored in tightly closed original containers under the above conditions, it has a shelf life of 6 months. Periodical remixing can extend the shelf life further.

- Please contact your local **Master Builders Solutions** representative prior to the use of any product that has been frozen.
- After prolonged storage, performance testing should always be carried out before use.

SAFETY PRECAUTIONS

The same precautions as with handling and use of cementitious products should be observed.

Avoid eye and skin contact and wear rubber gloves and safety glasses. If contact occurs, rinse with plenty of water. In case of eye contact seek medical advice. For further information, refer to the Material Safety Data Sheet or contact your local **Master Builders Solutions** representative.

DISCLAIMER

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. **Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.** is only responsible for the quality of the product **Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.** is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding the place and the method of use. This technical form is valid only till a new version is implemented and nullifies the old ones.

CONTACT INFORMATION

Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.

Adres: Barbaros Mah. Begonya Sok.

Nidakule Kuzey Ataşehir, C Kapısı

No:3 E/5, 34746 Ataşehir İstanbul / Türkiye

Tel: 0216 217 88 00

Mail: mbs.tr@mbcc-group.com

Web: www.master-builders-solutions.com/tr-tr

® Registered trademark of a MBCC Group member in many countries of the world

MasterRoc[®] SA 160 Technical Data Sheet -Revision
Date: 12/2020

MasterRoc® SA 160 (Formerly known as Meyco® SA 160)

Alkali-Free, Liquid High Performance Set Accelerator for Sprayed Concrete

	
1020	
Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti. Adres: Barbaros Mah. Begonya Sok. Nidakule Kuzey Ataşehir, C Kapısı No:3 E/5, 34746 Ataşehir İstanbul 20 DoP No: TR14/02/01 1020 – CPR – 040 065836 EN 934-5:2007	
MasterRoc SA 160 Alkali İçermeyen Priz Hızlandırıcı Katkı; EN 934 - 5 : T2 (Non-alkaline Set Accelerating Admixture ; EN 934 - 5 : T2)	
Klorür İçeriği (Chlorine Content)	<% 0,1 Kütlece (in mass)
Alkali İçeriği (Alkaline Content)	<% 1 Kütlece (in mass)
Korozyona Etkisi (Corrosion Behavior)	Yok (None)
Tehlikeli maddeler (Dangerous Substances)	Yok (None) (1999/45/CE,2001/60/CE)