

MasterTop® 1327 C

High sound deadening, bacteriostatic, elastic, satin matt, low emission (compliant with AgBB) polyurethane system

DESCRIPTION

MasterTop® 1327 C, is a polyurethane based, cigarette burn resistant, flexible, easily cleaned, hygienic, self-leveling, matt surface comfort coating system which can absorb sound and impact and also which has a capacity of crack bridging.

FIELDS OF APPLICATION

- Hospitals and Rest Homes,
- Schools,
- Offices,
- Hotels,
- Doctor Offices.

FEATURES AND BENEFITS

- Easy to apply.
- Has perfect adherence.
- Resistant against cigarette burns.
- Surface structure that does not allow the formation of microbes.
- Easily cleaned to create hygienic environments.
- Has structure that can absorb sound.
- Has crack bridging capacity.
- Flexible.

WATCH POINTS

- Avoid application under excessive heat or wind and/or when the ambient and/or substrate temperature is below +10 or above +30°C.
- The materials to be used at the appropriate temperatures should be brought and stored in the application area 1-2 days prior to the application and enabled to adjust the ambient conditions.
- In extremely cold conditions, heaters should be used to increase the ambient and the workability of the product, the packages should be preconditioned to +20 - +25°C to become ready to use.
- Epoxy and polyurethane based floor coatings should be applied by specialists.
- The reaction and workability times of resin based systems depend on the ambient and substrate temperatures as well as the relative humidity. Under lower temperatures, the chemical reaction times are prolonged and this increases the pot life, coating interval and the working time. In addition to this, the consumption is increased as the viscosity increases. High temperatures ignite stronger chemical reactions and the above mentioned times decrease accordingly. For the material to be cured properly, the ambient and the substrate temperatures should not fall below the specified limits. After the application, the Material should be protected from direct contact with water for 24 hours minimum. Within this period, a contact with water may cause a surface carbonation and/or

tackiness; both of which will cause the coating to lose its characteristics. In such cases, the overall coating should be removed from the floor and renewed.

- The empty packs should be consolidated and disposed properly in order to prevent reusing of the packages.
- For detailed information about how to use the products, the Technical Product Information Brochures should be referred.

DISCLAIMER

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. **Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.** is only responsible for the quality of the product **Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.** is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding the place and the method of use. This technical form is valid only till a new version is implemented and nullifies the old ones.

CONTACT INFORMATION

Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.

Adres: Barbaros Mah. Begonya Sok.

Nidakule Kuzey Ataşehir, C Kapısı

No:3 E/5, 34746 Ataşehir İstanbul / Türkiye


Tel: 0216 217 88 00

Mail: mbs.tr@mbcc-group.com

Web: www.master-builders-solutions.com/tr-tr

® Registered trademark of a MBCC Group member in many countries of the world

MasterTop® 1327 C Technical Data Sheet -Revision
Date: 12/2020



MasterTop® 1327 C

High sound deadening, bacteriostatic, elastic, satin matt, low emission (compliant with AgBB) polyurethane system

TECHNICAL CHARACTERISTICS

		Consumption:	
	Primer	MasterTop P 615 EP, 2-component, non-solvented (total solid)	0.3 – 0.5 kg/m ²
	Optional/ Scratch primer Up to 1 mm	MasterTop P 615 EP, 2-component, non-solvented (total solid) 1:0,5 filled with oven dried silica sand, size Ø 0,1-0,3 mm	0.6 – 1.0 kg/m ² *
	Massive elastic underlayment	MasterTop BC 327 FLR Massive, high elastic, pigmented, PU, 2 component, non-solvented	3.2 – 3.7 kg/m ²
	Body coat	MasterTop BC 325 N Pigmented, PU, 2-component, non-solvented,	2.5 – 3.0 kg/m ²
	Top coat By light colours at Least two applications are necessary	MasterTop TC 417 W (pigmentli) Pigmented, PU, 2-component, water borne, non- solvented, UV-stable, bacteriostatic	0.10 – 0.12 kg/m ² Each application
Total thickness Of the system		Ca. 6.0 – 7.0 mm	

Remark: Consumptions are indicative and may be higher, depending on substrate roughness, temperature and porosity, as well as waste produced during application.

* Consumption incl. Filler