

# MasterRoc<sup>®</sup> SA 160

Alkali-free, liquid high performance set accelerator for sprayed concrete

## DESCRIPTION

**MasterRoc SA 160** is a high performance alkali-free set accelerator for sprayed concrete, whose dosage can be varied to the desired setting and hardening times.

## FLIEDS OF APPLICATION

- Temporary and permanent ground support in tunneling and mining
- Slope stabilisation
- Also suitable for acceleration of cementitious grouts, such as for annulus grout in TBM tunnels, cemented ground injection and foam concrete.

## FEATURES AND BENEFITS

- **MasterRoc SA 160** is ideally suited for wet mix sprayed concrete for ground support:
- The quick setting property allows rapid work progress and the ability to construct thick sprayed concrete linings via layered application during one construction sequence.
- The unique product formulation provides fast setting, continuous early-age strength development high durability and good long term strength.
- Very low dust generation during application and therefore a good working environment.
- Possibility of low rebound applications when using the correct nozzle angle and distance.
- Non-aggressive properties provide improved working safety, reduced environmental impact and lower handling costs.

## TECHNHICAL DATA

|   |                  |
|---|------------------|
| Form  | Suspension       |
| Color   | Beige            |
| Density (+20°C)                                 | 1.43 ± 0.03 g/ml |
| pH value (1:1 water solution)                   | 2.6 ± 0.5        |
| Viscosity <sup>1)</sup>                         | >400m Pa.s       |
| Thermal stability                               | +5°C to+35°C     |
| [Na <sub>2</sub> O] EQV. (%bw)<br>Chloride free | <1%              |

- 1) Brookfield, + 20°C. Viscosity is dependent on degree of product agitation and temperature.

## APPLICATION

The substrate should be clean and free from loose particles and preferably damp.

It is recommended to use only fresh cement as the age of the cement can have a negative influence on the setting characteristics of the mix.

**MasterRoc SA 160** can be sensitive to the type of cement. With some cements the setting characteristics can be too slow. We recommend the use of Portland cements (PC/HPC), which normally give faster setting than blended or sulphate resistant cement types. However, **MasterRoc SA 160** also works well with composite cements types (blended cements, fly-ash/slag). In all cases, it is strongly recommended to carry out preliminary tests to check setting and the 24 h strength of the cements planned for use in a project.

Evaluation of setting and 24 h strength should be carried out on a test mortar in accordance with EFNARC European Specification for Sprayed Concrete (1996), Appendix 1, Clause 6.3.

The following results should be taken as a performance guide only:

| Initial set | Final set | 24h strength | Rating |
|-------------|-----------|--------------|--------|
| 2 min.      | 6-8 min.  | 18-20 MPa    | Good   |
| 5 min.      | 8-12 min  | 12-15 MPa    | OK     |
| >10 min     | >15 min   | <10 MPa      | Poor   |

### Concrete mix

When **MasterRoc SA 160** is used for wet mix spraying, the w/c+b ratio should be below 0.5 and preferably <0.45. When targeting extremely high early strength, 0.40 or lower. The lower w/c+b ratios provide faster setting, higher early strength, better durability, lower accelerator dosage and thicker layers can be applied overhead.

### Dosing system

**MasterRoc SA 160** is added at the nozzle. It is essential to have a constant and accurate dosage of accelerator into the concrete stream. To ensure quality sprayed concrete, follow the pump selection guidelines given below:

# MasterRoc<sup>®</sup> SA 160

Works very well with:

- Mono pumps (stator & rotor pumps)
- Peristaltic pumps (Bredel)

Should not use with:

- Piston pumps
- All pumps with ball and seat valves
- Pressure tanks
- Gear pumps

Do not use a filter on the suction hose as this causes obstructions. Preferably draw the material off the bottom of the drum/container.

## Compatibility with other accelerators

**MasterRoc SA 160** can be interchanged with most of Master Builders Solutions alkali-free accelerators. For advice please contact your local representative.

Do not mix or interchange **MasterRoc SA 160** with any type of accelerator produced by another manufacturer, as this can cause immediate clogging of dosing pumps and hoses.

## Consumption

The consumption of **MasterRoc SA 160** also depends on the w/c+b ratio, temperature conditions (concrete and ambient), cement reactivity and on required layer thickness, setting time and early strength development. The consumption is normally in the range of 3 to 10% of binder weight.

Overdosing (>10%) may result in decreased final strength.

## Cleaning of dosing pump

After the use of **MasterRoc SA 160**, the dosing pump and other parts of the system must be thoroughly cleaned with plenty of water. Failure to do so provokes blockages in the dosing system when next used. Make sure that all operators involved in testing and application are fully informed.

## PACKAGING

**MasterRoc SA 160** is supplied in 210 litre drums, 1000 litre containers or in bulk.

## SHELF LIFE

- Must be stored at minimum +5°C and maximum +35°C (optimum temperature for storage and performance +20°C).
- Has to be kept in closed containers made of plastic, glass fiber or stainless steel.
- **Must not** be stored in normal steel containers.
- Storage in bulk tanks **requires** the use of agitation and / or circulation systems.
- After prolonged storage or transport we recommend to fully agitate it prior to use by mechanical stirring or re-circulation pumping.
- If stored in tightly closed original containers under the above conditions, it has a shelf life of 6 months. Periodical remixing can extend the shelf life further.
- Please contact your local Master Builders Solutions representative prior to the use of any product that has been frozen.
- After prolonged storage, performance testing should always be carried out before use.

## PRECAUTIONS

The same precautions as with handling and use of cementitious products should be observed.

Avoid eye and skin contact and wear rubber gloves and safety glasses. If contact occurs, rinse with plenty of water. In case of eye contact seek medical advice. For further information, refer to the Material Safety Data Sheet or contact your local Master Builders Solutions representative.

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.