

MasterSeal[®] P 770

2-component primer based on Xolutec - Technology for MasterSeal Systems

DESCRIPTION

MasterSeal P 770 is a two-component primer based on Xolutec - Technology, providing high substrate penetration and acting as bond promoter for the subsequent MasterSeal systems, e.g. MasterSeal 7000 CR.

Xolutec™ – a new dimension in durability

Xolutec is an innovative and smart way of combining complementary chemistries. When the material is mixed on site a cross linked interpenetrating network (XPN) is formed enhancing the overall material properties. By controlling the cross-linking density, the properties of Xolutec can be adjusted depending on the product performance required, e.g. this allows the formulation of materials with varying degrees of toughness and flexibility. Xolutec is very low in volatile organic components (VOC), is quick and easy to apply with both spray and hand application depending on requirements. It cures rapidly even at low temperature, reducing application time thus enabling fast return to service and minimizing downtime. This technology is not sensitive to moisture and tolerates a wide variety of different site conditions, greatly expanding the application window and reducing the potential for delays and failures. Long maintenance cycles and lower life cycle costs significantly reduce total cost of ownership

FIELD OF APPLICATION

MasterSeal P 770 is used as primer on mineral substrates for MasterSeal systems. The primer coat will improve the adhesion and prevent the appearance of pinholes or bubbles in the subsequent hardened coating.

FEATURES AND BENEFITS

- Low viscosity
- Easy to apply
- Excellent penetration
- Seals pores and capillaries
- Moisture tolerant: can be applied on substrates with high residual humidity.
- Excellent bond to substrate
- Does not contain solvents.

APPROVALS AND CERTIFICATES

CE Certification as Primer for **MasterSeal P 790** in the system MasterSeal 7000 CR per EN 1504-2.

PERFORMANCE DATA

Touch Dry at +20°C (Hours)	approx. 5
Ready for pedestrian traffic / Re-coating interval (Hours)	
at +10 °C	min. 11
at +20 °C	min. 5
at +30 °C	min. 2
Fully cured (Days)	
at +10 °C	7
at +20 °C	5
at +30 °C	2
Glass transition temperature (°C) (EN 12614)	
at 28 Days	55
Adhesion to concrete (N/mm ²) (EN 1542)	
at 28 Days	> 2.0
Adhesion (N/mm ²) (EN 1542) in combination with subsequent layers of :	
MasterSeal M 790	> 2.5
MasterSeal M 689	> 2.5
MasterSeal M 811	> 3.0

PROPERTIES

Density (g/cm ³) (EN ISO 2811-1)	
Part A	approx. 1.3
Part B	approx. 1.2
Mixed	approx. 1.2
Viscosity (mPas) (EN ISO 3219)	
Part A	approx. 1140
Part B	approx. 125
Mixed	approx. 650
Application temperature (°C)	
Substrate	from +5 to +35
Material	from +5 to +35

MasterSeal[®] P 770

Application Condition	
Substrate moisture	No Restriction, Visibly Dry surface
Relative humidity (%)	
at +10 °C	≤ 75
at +20 °C	≤ 85
Pot-life (minutes)	
at +5 °C	approx. 30
at +10 °C	approx. 25
at +20 °C	approx. 20
at +30 °C	approx. 10

Note: Data are measured at 21°C ± 2°C and 60% ± 10% relative humidity if not stated differently. Higher temperatures and/or higher relative humidity can shorten hardening/curing times, and vice versa. Technical data shown are statistical results and do not correspond to guaranteed minima. Tolerances are those described in appropriate performance.

APPLICATION METHOD

(a) Surface Preparation

All substrates (new and old) must be structurally sound, dry, free of laitance and loose particles and clean of oil, grease, rubber skid marks, paint stains and other adhesion impairing contaminants.

Concrete: The surface should be prepared by shot blasting, high-pressure water jetting or other suitable mechanical method. After preparation, concrete and other cementitious substrates must have a minimum pull off strength of 1 N/mm².

Very rough/irregular substrates on walls should be levelled before application with a suitable fairing coat, eg. **MasterEmaco N 5100**. On floors a suitable repair or levelling solution should be used. The substrate should be visibly dry-there is no limit to residual humidity. Substrate temperature must be minimum + 5°C and maximum +35°C

(b) Mixing

MasterSeal P 770 is supplied in working kits which are pre-packaged in the exact mixing ratio.

Pour the entire content of Part B into the container of Part A and mix with a mechanical drill and paddle at low speed (max. 400 rpm) for at least 3 minutes. Scrape the sides and the bottom of the container several times to ensure complete mixing. Keep the mixer blades submerged in the coating to avoid introducing air bubbles.

Do not mix part packs and do not mix by hand!

(c) Application

After mixing, **MasterSeal P 770** is applied to the prepared substrate by brush or roller. The curing time of the material is influenced by the ambient, material and substrate temperatures.

At low temperatures, the chemical reactions are slowed down; this lengthens the pot life, open time and curing times. High temperatures speed up the chemical reactions thus the pot life, open time and curing times are shortened accordingly. To fully cure, the material, substrate and application temperature should not fall below the minimum.

MasterSeal P 770 dries as an intense transparent film (within 5 hours @ 20°C). In case there are holes not covered by primer, please apply a second coat of primer.

Wait for at least 5 hours (@ 20°C) before applying MasterSeal systems.

FINISHING AND CLEANING

Tools can be cleaned with solvent-based cleaner while still wet. Once cured, the material can only be removed mechanically.

COVERAGE

The consumption of **MasterSeal P 770** is approximately 0.25 – 0.4 kg/m².

This consumption is theoretical and can vary according to the absorption and roughness of the substrate. It is essential to carry out representative trials on site to evaluate the exact consumption.

WORKING TIME

Approximately 20 minutes at 20°C ambient and substrate temperature.

PACKAGING

MasterSeal P 770 is available in 5kg kits consisting of 2.2kg Part A and 2.8 kg Part B.

COLOURS

Milky-ivory

STORAGE

MasterSeal P 770 should be stored in original containers under dry conditions at temperatures between 10 - 25° C preferably. Protect from frost and no permanent storage over +35 °C.

SHELF LIFE

Shelf life under these conditions is 12 months for both parts.

MasterSeal[®] P 770

WATCH POINTS

- Do not apply at temperatures below + 5°C nor above + 35 °C
- Eventual separation of Part A can occur – this is no product failure, and the material can be easily re-homogenized by mixing.
- Do not add any solvents or other components to **MasterSeal P 770** mixes.

HANDLING AND TRANSPORT

Usual preventive measures for the handling of chemical products should be observed when using this product, for example do not eat, smoke or drink while working and wash hands when taking a break or when the job is completed.

Specific safety information referring the handling and transport of this product can be found in the Material Safety Data Sheet.

Disposal of product and its container should be carried out according to the local legislation in force. Responsibility for this lies with the final owner of the product.

® = registered trademark of a MBCC Group member in many countries of the world

MAP#MasterSeal P 770 v2. 12. 2020

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability, or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified, or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Singapore Pte Ltd
1 Harbourfront Avenue #07-07/08
Keppel Bay Tower, Singapore 098632
Tel : +65 6232 4888