

MasterGlenium® 118

Polycarboxylic ether-based superplasticizer for the production of high-quality ready-mix concrete

DESCRIPTION

MasterGlenium 118 is an innovative latest generation superplasticizer based on polycarboxylic ether (PCE) polymers and is specially engineered for ready-mix concrete.

MasterGlenium 118 is differentiated from conventional superplasticisers, such as those based on sulphonated naphthalene formaldehyde condensate in that it is based on a unique carboxylic ether polymer with long lateral chains. This greatly improves cement dispersion. At the start of the mixing process the same electrostatic dispersion occurs but the presence of the lateral chains, linked to the polymer backbone, generate a steric hindrance which stabilises the cement particles capacity to separate and disperse. This mechanism provides flowable concrete with greatly reduced water demand.

TYPICAL APPLICATIONS

MasterGlenium 118 is used for the production of high-quality ready-mix concrete.

ADVANTAGES

The ready-mix producer:

- Capability of delivering high performance concrete at any time to the job site in place
- Production of a concrete with low water cement ratios with excellent workability retention properties
- Single product for many application needs

The contractor / applicator:

- Easier placing and faster strength development
- Improved concrete surfaces

The engineer:

- Insurance that concrete meets original specification
- High quality durable concrete

PACKAGING

MasterGlenium 118 is supplied in 210 L drums, 1,000 L containers or in bulk.

STANDARDS

ASTM C-494 Type F&G
BS EN 934-2

TYPICAL PROPERTIES*

Appearance	Brown coloured liquid
Specific gravity @ 25°C	1.056
pH value	4.5 – 6.5
Chloride content	"chloride-free" to EN 934

APPLICATION GUIDELINES

The normally recommended dosage rate of **MasterGlenium 118** is 0.8 to 2.5 L/100kg of total cementitious material.

Other dosages may be recommended in special cases according to the specific site conditions. In this case please consult our Technical Services Department for advice.

MIXING

MasterGlenium 118 is a ready-to-use admixture to be added to the concrete as a separate component. Optimal result is obtained if **MasterGlenium 118** is poured into the concrete mix right after the addition of the first 80% of the mixing water, i.e. when all solids are wetted. Avoid adding the admixture to the dry aggregates.

MasterGlenium 118 is suitable for mixes containing:

- Microsilica (Silica Fume)
- Fly Ash (PFA)
- GGBS (ground granulated blast furnace slag)

Note: **MasterGlenium 118** is not compatible with **MasterRheobuild** superplasticizers.

MasterGlenium[®] 118

STORAGE AND SHELF LIFE

MasterGlenium 118 should be stored out of direct sunlight and protected from extremes of temperature. The shelf life is 12 months when stored as above.

The occurrence of a surface layer with **MasterGlenium 118** is normal and will have no effect on the performance of the product.

HEALTH AND SAFETY

No special requirements must be observed during use. Protection gloves and glasses are however recommended. **MasterGlenium 118** is non-flammable, non-toxic or irritant and is not subject to special transport requirements.

MasterGlenium 118 contains no hazardous substances requiring labelling. For further information refer to the Material Safety Data Sheet.

QUALITY AND CARE

All products manufactured by Master Builders Solutions Egypt, or imported from Master Builders Solutions affiliate companies world-wide, are manufactured to procedures certified to conform to the quality, environment, health & safety management systems described in the ISO 9001:2015, ISO 14001:2015 & OHSAS 18001:2007 standards.

* Properties listed are based on laboratory controlled tests.

® Registered trademark of a MBCC Group member
In many countries of the world

