

# MasterRheobuild® 3030

High range, water-reducing superplasticiser for rheoplastic concretes

## DESCRIPTION OF PRODUCT

**MasterRheobuild 3030** is formulated from synthetic polymers specially designed to impart rheoplastic qualities to concrete.

A rheoplastic concrete is a fluid concrete, easily flowing, but at the same time free from segregation and bleeding having the same w/c ratio as that of a low slump concrete without admixture with a slight set retarding effect. Also, it provides a substantial water reduction effect for promoting high, early and ultimate strengths.

**MasterRheobuild 3030** is chloride-free.

## ADVANTAGES

**MasterRheobuild 3030** considerably improves the properties of fresh and hardened concrete.

## PRIMARY USES

- Microsilica concrete
- Mass concrete pours
- Ready-mixed concrete
- Long distance transport
- Pumped concrete
- Casting in hot climates

## TO OBTAIN:

- Reduced thermal peaks
- High workability for longer periods
- Lower pumping pressure
- Delayed setting with longer workability
- Higher ultimate strengths
- Reduced permeability
- Improved durability

## COMPATIBILITY

**MasterRheobuild 3030** is compatible with all cements and most air-entraining agents meeting ASTM standards. The addition of **MasterRheobuild 3030** and **MasterAir 111** (air-entraining agent) to concrete is recommended where it is required to withstand freezing and thawing cycles.

## PACKAGING

**MasterRheobuild 3030** is available in 1000ltr bulk.

## TTYPICAL PROPERTIES

Colour: Dark brown liquid
Specific gravity: 1.130-1.160
Chloride content: Nil to BS 5075
Nitrate content: Nil
pH: 5-7
Flashpoint: 0°C
Freezing point: N/A

## STANDARDS

ASTM C-494: Types D and G

BS 5075: Part 3

## DOSAGE

Optimum dosage of **MasterRheobuild 3030** should be determined in trial mixes. As a guide, the following dosages are recommended as a starting point for any trial: in normal concrete, a dosage of between 0.6 - 2.0 ltr/100kg of cement.

Please consult Master Builders Solutions's Technical Services Department for further information.

## DISPENSING

**MasterRheobuild 3030** is a ready-to-use liquid, which is dispensed into the concrete together with the mixing water. The plasticising effect and water reduction are higher if the admixture is added to the concrete after 50 to 70% of the mixing water has been added. The addition of MasterRheobuild 865 to dry aggregate or cement is not recommended. Automatic dispensers are available.

## WORKABILITY

**MasterRheobuild 3030** ensures that rheoplastic concrete remains workable in excess of 2 hours at +20°C.

Workability loss is dependent on temperature, the type of cement, nature of aggregates, method of transport and initial workability. It is strongly recommended that concrete should be properly cured, particularly in hot and dry climates.

# MasterRheobuild® 3030

## STORAGE

**MasterRheobuild 3030** must be stored where temperatures do not drop below +5 °C. If product has frozen, thaw and agitate until completely reconstituted. Store under cover, out of direct sunlight and protect from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice, consult Master Builders Solutions's Technical Services Department.

## SHELF LIFE

Up to 24 months if stored according to manufacturer's instructions in unopened containers.

## NOTE

Field service, where provided, does not constitute Supervisory responsibility. For additional information, contact your local Master Builders Solutions representative.

Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

## QUALITY STATEMENT

All products manufactured by Master Builders Solutions Egypt, or imported from Master Builders Solutions affiliate companies world-wide, are manufactured to procedures certified to conform to the quality, environment, health & safety management systems described in the ISO 9001:2015, ISO 14001:2015 & OHSAS 18001:2007 standards.

\* Properties listed are based on laboratory controlled tests.

® Registered trademark of a MBCC Group member in many countries of the world

Master\_Builders\_Solutions\_CC-EG//Rheobuild\_3030\_08\_17/v1/08\_17

MBS Construction Chemicals Egypt (S.A.E), Business Park A, Building A1, Cairo Festival City, Ring Road, New Cairo, Egypt

Hotline: 15560, Phone: +202 2128 7800, Fax: +202 2128 7801

Website: <https://www.master-builders-solutions.com/en-eg>



**15560**