

MasterRheobuild® 3375

High range, water-reducing superplasticiser for rheoplastic concrete

DESCRIPTION OF PRODUCT

MasterRheobuild 3375 is formulated from synthetic polymers specially designed to impart rheoplastic qualities to concrete.

A rheoplastic concrete is a fluid concrete, easily flowing, but at the same time free from segregation and bleeding having the same w/c ratio as that of a low slump concrete without admixture with a slight set retarding effect. Also, it provides a substantial water reduction effect for promoting high, early and ultimate strengths.

MasterRheobuild 3375 is chloride-free.

ADVANTAGES

MasterRheobuild 3375 considerably improves the properties of fresh and hardened concrete.

PRIMARY USES

- Microsilica concrete
- Mass concrete pours
- Ready-mixed concrete
- Long distance transport
- Pumped concrete
- Casting in hot climates

TO OBTAIN:

- Reduced thermal peaks
- High workability for longer periods
- Lower pumping pressure
- Delayed setting with longer workability
- Higher ultimate strengths
- Reduced permeability
- Improved durability

COMPATIBILITY

MasterRheobuild 3375 is compatible with all cements and most air-entraining agents meeting ASTM standards. The addition of **MasterRheobuild 3375** and **MasterAir 111** (air-entraining agent) to concrete is recommended where it is required to withstand freezing and thawing cycles.

PACKAGING

MasterRheobuild 3375 is available in 1000ltr bulk.

TYPICAL PROPERTIES

Colour:	Dark brown liquid
Specific gravity:	1.10-1.160
Chloride content:	Nil to BS 5075
Nitrate content:	Nil
Freezing point:	0°C
Flashpoint:	N/A
pH:	5-7

STANDARDS

ASTM C-494: Types D and G
BS 5075: Part 3

DOSAGE

Optimum dosage of **MasterRheobuild 3375** should be determined in trial mixes. As a guide, the following dosages are recommended as a starting point for any trial: in normal concrete, a dosage of between 0.6 - 2.0 ltr/100kg of cement.

Please consult Master Builders Solutions 's Technical Services Department for further information.

DISPENSING

MasterRheobuild 3375 is a ready-to-use liquid, which is dispensed into the concrete together with the mixing water. The plasticising effect and water reduction are higher if the admixture is added to the concrete after 50 to 70% of the mixing water has been added. The addition of MasterRheobuild 865 to dry aggregate or cement is not recommended. Automatic dispensers are available.

WORKABILITY

MasterRheobuild 3375 ensures that rheoplastic concrete remains workable in excess of 2 hours at +20°C. Workability loss is dependent on temperature, the type of cement, nature of aggregates, method of transport and initial workability. It is strongly recommended that concrete should be properly cured, particularly in hot and dry climates.

MasterRheobuild® 3375

STORAGE

MasterRheobuild 3375 must be stored where temperatures do not drop below +5 °C. If product has frozen, thaw and agitate until completely reconstituted. Store under cover, out of direct sunlight and protect from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice, consult Master Builders Solutions 's Technical Services Department.

SHELF LIFE

Up to 24 months if stored according to manufacturer's instructions in unopened containers.

NOTE

Field service, where provided, does not constitute Supervisory responsibility. For additional information, contact your local MASTER BUILDERS SOLUTIONS representative.

Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY STATEMENT

All products manufactured by Master Builders Solutions Egypt, or imported from Master Builders Solutions affiliate companies world-wide, are manufactured to procedures certified to conform to the quality, environment, health & safety management systems described in the ISO 9001:2015, ISO 14001:2015 & OHSAS 18001:2007 standards.

* Properties listed are based on laboratory controlled tests.

® Registered trademark of a MBCC Group member in many countries of the world

Master_Builders_Solutions_CC-EG//MRheobuild_3375_11_15

MBS Construction Chemicals Egypt (S.A.E), Business Park A, Building A1, Cairo Festival City, Ring Road, New Cairo, Egypt
Hotline: 15560, Phone: +202 2128 7800, Fax: +202 2128 7801
Website: <https://www.master-builders-solutions.com/en-eg>



15560