

MasterRoc® AGA 155

Plasticising admixture with set retarding properties for use in annular grout mixes for TBM tunneling.

DESCRIPTION

MasterRoc® AGA 155 is a liquid plasticiser which disperses and deflocculates cement particles whilst delaying the hydration process, thereby retarding the initial and final set. It can be used to improve workability without the addition of extra water, or to allow reductions in the free water content. Due to improved dispersion of the cement particles the process of hydration proceeds under the optimum conditions, leading to improved strength characteristics with or without reduction in free water.

PRIMARY

- High flow, low cement content, high W/C ratio annular grout mixes.
- Hot weather applications of grout where control of initial and final set is important.
- Retarded mortars (also in combination with Rheomix 910)

TYPICAL APPLICATIONS

Setting control of annular grout mixes for injection behind segmental tunnel linings.

MasterRoc® AGA 155 is designed for use in one or two component grouting systems and is compatible with accelerators such as MasterRoc® AGA 370.

BENEFITS

- Increases compressive, tensile and flexural strength of concrete.
- Increases density of grout mixes reducing permeability and thus increasing durability.
- Allows a reduction in free water in the region of 8-12%.
- Highly effective in low cement content high water cement ratio mixes where its use enables grout to be made more workable without loss in strength, density and durability.
- Enables controlled extension of initial set.
- The retarding action allows storage of the annular grout in the pumping lines and grout agitator tanks on the TBM for up to 72 hours depending on dosage.
- The strength gain of annular grouts containing MasterRoc AGA 155 is enhanced. After retardation of initial and final set, a more rapid hardening of the grout occurs, and the effect on stripping time is negligible.

PACKAGING

MasterRoc® AGA 155 is available in bulk, 1000 litre IBCs or 210 litre drums.

COMPATIBILITY

MasterRoc® AGA 155 can be used with all types of Portland cement including sulphate resisting (Type V). For use with other special cements, contact Master Builders Solutions UGC Technical Dept.

MasterRoc® AGA 155 should not be premixed with other admixtures. If other admixtures are to be used in annular grouts containing MasterRoc® AGA 155, they must be dispensed separately. If in doubt, consult Master Builders Solutions UGC Technical Dept.

PROPERTIES

Colour:	Dark brown liquid
Specific gravity:	1.22 – 1.23 at 25°C.
Chloride content:	“chloride free” to EN 934-2
Freezing point:	0°C

STANDARDS

EN 934-2 Tables 6 and 10
ASTM C494: Type B & D
BS 5075: Part 1 (superseded by EN 934-2)

DIRECTIONS FOR USE

MasterRoc® AGA 155 should be added to the annular grout mix during the mixing cycle, at the same time as the water, or the bentonite. Never add MasterRoc® AGA 155 to the dry cement. No extension to normal mixing time is necessary.

DOSAGE

Field trials should be conducted to determine the optimum addition rates of MasterRoc® AGA 155. As a guide to these trials, a dosage range of 500ml to 750ml per 100kg of cementitious material for normal use and 750 to 1500ml where higher retardation is required. Dosages outside this range can be used where improved workability, increased water reduction and / or further set retardation are required.

EFFECTS OF OVER DOSAGE

A severe over dosage of MasterRoc® AGA 155 will result in:

- Increased retardation of initial and final set.
- Increase in workability.

MasterRoc® AGA 155

Providing annular grout is properly cured the ultimate strength of the grout will not be adversely affected and will generally be higher than for normal concrete. Care should be taken to allow for the effect on injection pressures and advance rates.

DISPENSER

MasterRoc® AGA 155 should be dispensed through a proprietary dispenser, such as is available from Master Builders Solutions.

STORAGE

Up to 2 years in unopened original packing.

Store under cover, out of direct sunlight and protect from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult Master Builders Solutions's Technical Services Department.

SAFETY PRECAUTIONS

MasterRoc® AGA 155 is not a fire or health hazard. Spillages should be washed down immediately with cold water. For further information refer to the Material Safety Data Sheet.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information, contact your local Master Builders Solutions representative.

Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY STATEMENT

All products manufactured by Master Builders Solutions Egypt, or imported from Master Builders Solutions affiliate companies world-wide, are manufactured to procedures certified to conform to the quality, environment, health & safety management systems described in the ISO 9001:2015, ISO 14001:2015 & OHSAS 18001:2007 standards.

* Properties listed are based on laboratory controlled tests.

® Registered trademark of a MBCC Group member in many countries of the world

Master_Builders_Solutions_CC-EG/Roc - AGA155_09_10/v1/03_21

