

MasterRoc® SA 545

Alkali-free, non-caustic and non-toxic high performance powder accelerator for dry-mix sprayed concrete

DESCRIPTION

MasterRoc SA 545 is a high performance alkali-free, non caustic and non toxic accelerator for use in the dry-mix sprayed concrete process. It is a powder additive whose dosage can be varied to the desired setting and hardening times.

FIELDS OF APPLICATION

MasterRoc SA 545 is suitable for all applications where high early strength, high final strength and very thick sprayed concrete layers are required.

- For temporary and permanent ground support in tunnelling and mining
- Slope stabilization
- For repair works

FEATURES AND BENEFITS

- Overhead layer thickness of 10-15 cm in a single application
- Rapid work process
- Good early strength development
- Limits the decrease of final strength
- Improves durability as compared to mixes with traditional accelerators
- Provides an improved working environment
- Reduces salt content in leaching water

PACKAGING

MasterRoc SA 545 is supplied in 20 kg bags.

TECHNICAL DATA*

Form	powder
Colour	white
Bulk density	1030 -1100 kg/m ³
pH value (EN ISO 787-9)	4 ± 1
Chloride content	<0.1%

APPLICATION PROCEDURE

The substrate must be clean and free from loose particles and preferably damp.

It is recommended to only use fresh cement as the age of the cement can have a negative influence on the setting characteristics of the mix.

MasterRoc SA 545 is sensitive to the type of cement. With some cements the obtained setting characteristics can be too slow. This sensitivity can be compensated by reducing the water content. We recommend the use of Portland cements (PC/HPC), which normally give faster setting than blended or sulphate resistant cement types.

In any case, it is strongly recommended to carry out preliminary tests to check the setting and the 24 hour strength characteristics of the cements planned for use in a project.

Evaluation of setting and 24 hour strength characteristics:

Initial set	Final set	24 h strength	Rating
2 min.	6-8 min.	18-20 MPa	good
5 min.	8-12 min.	12-15 MPa	OK
>10 min	>15 min.	<10 MPa	poor

CONCRETE MIX

The minimum cement content with the use of **MasterRoc SA 545** is 350 kg per m³. It is normally added to the mix immediately prior to use.

A combination of **MasterRoc SA 545** and MasterRoc HCA 10 hydration control admixture prolongs the open time of the mix.

- Dosage: 0.4% by weight of binder of MasterRoc HCA 10 at ambient temperatures of >+20° C.
- At ambient temperatures between +15° C and +20° C only 0.2% by weight of binder should be used.

MasterRoc[®] SA 545

- Below +15° C **MasterRoc HCA 10** should not be used at all.

CONSUMPTION

The consumption of **MasterRoc SA 545** also depends on the water added, temperature conditions (dry mix and ambient), cement reactivity and on required layer thickness, setting time and early strength development. The consumption is normally in the range of 4 to 8% of binder weight.

Overdosing (>10%) may result in decreased final strength.

STORAGE

If stored dry and in tightly closed original bags, **MasterRoc SA 545** has a shelf life of 12 months. If subjected to humidity, the product loses its effectiveness. Any lumps can simply be crushed by hand. Material which is too hard must be discarded.

SAFETY PRECAUTIONS

The same precautions as with handling and use of cementitious products should be observed.

Avoid eye and skin contact and wear rubber gloves and safety glasses. If contact occurs, rinse with plenty of water. In case of eye contact seek medical advice.

For further information, refer to the Material Safety Data Sheet or contact your local Master Builders Solutions representative.

* Properties listed are based on laboratory controlled tests.

® Registered trademark of a MBCC Group member in many countries of the world

**Master Builders Solutions CC-
UAE/Roc_SA545/v2/11_13**

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions Construction Chemicals UAE LLC

P.O. Box 37127, Dubai, UAE

Tel: +971 4 8090800

Fax: +971 4 8851002

www.master-builders-solutions.ae

