

MasterTop[®] 548

Fast setting screed mortar – ready blended for fast track cementitious screeds

DESCRIPTION

A ready-mixed pre-bagged fast setting screed suitable for indoor and outdoor use.

FIELDS OF APPLICATION

For indoor and outdoor use, also suitable for direct use.
 For areas which are exposed to permanent wetness.
 For fast track bonded screeds and screeds installed on an isolating or insulating layer.
 Suitable for heated screeds.
 As repair mortar for concrete floors and cementitious screeds.
 For layer thicknesses from 10 to 80 mm for continual layer of application.

FEATURES AND BENEFITS

Can be tiled after approx. 3 days, already walkable after approx. 1 day.
 Ready-to-mix mortar, no on-site mixing with sand required.
 Long working time, can be worked with and smoothed for almost 1 hour despite of short curing time.
 Suitable for application by pump, even at higher temperatures.
 Temperature resistant from -30°C to +80°C, therefore suitable for balconies, terraces, garages, industrial floor coverings cleaned with superheated steam.
 Insensitive to moisture, therefore suitable for areas exposed to permanent wetness.
 Pipes & conduits must be covered by a layer thickness of 30mm.

PACKAGING

25kg PE lined heavy duty paper bag

SHELF LIFE

Minimum 6 months when stored in dry conditions, no permanent storage over +30°C.

TECHNICAL DATA*

Material:

| | |
|--|---|
| Material base | special cement with admixtures and aggregates |
| Maximum grade | 4mm |
| Components | 1 part |
| Fresh wet density | Approx. 2.210kg/litre |
| Consistency | powder |
| Colour | grey |
| Screed classification in accordance to BS EN 13813 can be produced * | CT-C35-F6 |
| - Compressive strength after 28 days | >35N/mm ² |
| Flexural strength BS EN 13813 | 6.0N/mm ² |
| BRE test (impact resistance) | Category A |
| Moisture content test @ 3 days BS EN 1097-5 2008 | 1.9% |

MasterTop® 548

APPLICATION

| | |
|--|---|
| Consumption | approx. 22.1kg/m ² per cm layer thickness |
| Quantity of gauging water | approx. 2 litres of water for 25kg of MasterTop 548 |
| Layer thickness - minimum - maximum - for pipes & conduits | approx. 10mm for bonded screeds; approx. 40mm for screeds on isolating or insulating layer approx. 80mm min. 30mm to cover |
| Working temperature ** | +5°C to +30°C |
| Mixing technique | Force action concrete mixer |
| Conveyor technique | pneumatic |
| Consistency of mortar | stiff-plastic |
| Working time * | approx. 60 minutes |
| Curing time * - foot traffic after - can be tiled after - Residual moisture content | approx. 1 day approx. 3 days (with ceramic and/or natural stone) ≤2% after approx. 3 days |
| Temperature resistance | -30°C to +80°C |
| Frost resistance | yes |
| Resistance to permanent wetness | yes |

* Times are achieved when the temperatures of mortar, ambient air and substrate are approx. +23°C over the entire period and the relative humidity does not exceed 50%. See also "General information on the application of rapid setting cement screeds".

** For hot weather condition please follow best practices of hot weather application methods or contact MASTER BUILDERS SOLUTIONS technical Services.

PREPARATION OF SUBSTRATE FOR BONDED SCREEDS ACCORDING TO BS 8204-1

The substrate must be clean, sound, free from grease, old paint and other residues. Remove heavy contamination mechanically, residues of oil and wax. Smoothed surfaces with a cement slurry on top should be removed by e.g. shot blasting. Pre-wet the prepared substrate at an early stage, keep damp, apply the bonding agent **MasterTop 500** and the screed mortar **MasterTop 548** wet on wet.

APPLICATION PROCEDURE

The recommendations BS 8204-1 should be followed during the application of **MasterTop 548**.

MIXING

- 1 Add **MasterTop 548** in a forced action concrete mixer and mix with water for approx. 1 minute while mixer is running until a stiff-

plastic consistency is achieved. The amount of water required per 25kg bag of **MasterTop 548** is about 2 litres.

- 2 Single bags of **MasterTop 548** can also be mixed in a suitable vessel (e.g. hob back) with a basket stirrer attached to an electric drill. Put adequate amount of gauging water in the vessel, add **MasterTop 548** and mix until a stiff-plastic consistency is achieved.

APPLICATION

Spread the mortar with a shovel, trowel or screeding bar, compact, scrape off with a levelling board, rub down with a wooden board and smooth if necessary.

Protect newly applied screed from too rapid dehydration (like wind, direct sunlight eg). The applied screed should be covered with polythene sheet immediately following finishing (with all leading edges lapped and secured), and left covered for a minimum 2 days.

MasterTop® 548

GENERAL INFORMATION ON THE PRODUCTION OF RAPID SETTING CEMENT SCREEDS

The mix must be of a stiff-plastic consistency! If the consistency is too soft and/or contains too much water, the screed does not achieve the appropriate strength resulting in shrinkage cracks and bulges. The equilibrium moisture will not be reached until later. The strength and low residual moisture level important for laying subsequent coverings are dependent on the following factors:

COMPACTION OF THE FRESH MORTAR

Insufficient compaction of pre-mixed mortars for screeds results in low strength of screed.

TEMPERATURE AND HUMIDITY

Curing and drying times may considerably increase at low application and substrate temperatures or high humidity (compared with the times at +23°C). The relative humidity should not exceed 70% during the curing process. In principle, the residual moisture should be checked prior to the application.

PLEASE NOTE

The general guidelines for cement screeds must be observed.
 The rapid curing properties of **MasterTop 548** must be taken into consideration.
 Use only whole bags of **MasterTop 548**.
MasterTop 548 must not be mixed with cement, rapid bonding agents, ready-to-mix screeds, dry mortars, as well as fibres, admixtures or additives and/or blended with aggregate mixes.

Apply **MasterTop 548** within approx. 60 minutes (at approx. +23°C) after mixing. Higher temperatures reduce, lower temperatures increase the time given.

Never add water or fresh **MasterTop 548** to reconstitute a mortar mix which has already begun to set.

In outdoor areas where early exposure to rain is expected or under extremely windy conditions it is recommended to cover the installation with construction foil until walkable.

Clean tools and mixing vessels with water immediately after use, once the product has cured cleaning with water is not possible any more.

HEALTH AND SAFETY

MasterTop 548 contains cement. Contact with moisture or gauging water sets off an alkaline reaction which may cause skin irritation and/or caustic burns to mucous membranes (e.g. the eyes). Risk of serious damage to eyes, therefore avoid contact with eyes and prolonged contact with skin. In case of contact with eyes immediately rinse with plenty of water and seek prompt medical attention. In case of contact with skin change contaminated clothing at once and immediately wash skin with plenty of soap and water. Wear suitable protective gloves (e.g. cotton gloves soaked in nitrile) and safety goggles/face protection. If ingested seek prompt medical attention and show packaging or this product data sheet. Keep out of reach of children.

For further information refer to the MASTER BUILDERS SOLUTIONS Material Safety Data Sheet.

® Registered trademark of a MBCC Group member in many countries of the world

**Master_Builders_Solutions_CC-
 UAE/Top_548_02_13/v4/04_16**

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

**Master Builders Solutions Construction
 Chemicals UAE LLC** P.O. Box 37127,
 Dubai, UAE
 Tel: +971 4 8090800, Fax: +971 4 8851002
www.master-builders-solutions.ae

Disclaimer: the LRQA mark relates to certified management system and not to the product mentioned on this datasheet

