

MasterEmaco T1100 TIX

Fast setting and hardening, extra high-strength, shrinkage compensated, fibre reinforced, thixotropic traffic repair mortar

DESCRIPTION

MasterEmaco T1100 TIX is a single component, fast setting and hardening thixotropic repair and bedding mortar that meets the requirements of the new European Norm EN 1504 part 3 class R4.

MasterEmaco T1100 TIX is a ready-to-use material that contains sulphate resistant Portland cement (HSR LA), hydraulic binders, well graded sands, specially selected polymer fibres (PAN – polyacrylonitril) and special additives provide rapid strength build-up even at sub-zero temperatures, improved durability and un-matched, low drying shrinkage.

When mixed with water, MasterEmaco T1100 TIX forms a plastic / thixotropic mortar which can be easily applied by hand.

MasterEmaco T1100 TIX can be used in thicknesses from 10 mm up to 150 mm.

FIELD OF APPLICATION


MasterEmaco T1100 TIX is used for:

- Bedding small to medium size manhole frames.
- Bedding curb stones and pavement stones
- Horizontal patch repair areas
- Inclined patching areas
- Optimizing traffic management.
- Both internal and external use.
- Use in cold conditions or cold store rooms.
- Applications under the most difficult jobsite conditions.
- Where very short traffic disruption periods are required.

FEATURES AND BENEFITS

- Ultra rapid strength build-up.
- MasterEmaco T1100 TIX can be opened to all traffic in just 2 hours.
- Excellent application properties
- Higher thickness possible with the addition of gravel
- Can be used at sub-zero temperatures as low as -10°C.
- Very high early and final strengths.

- Excellent adhesion and excellent durability.
- Extra low shrinkage for durability.
- Minimized cracking tendency due to constrained shrinkage by PAN fibres.
- Excellent freeze-thaw resistance.
- Very good reinforcement protection due to very low water absorption and good carbonation resistance.
- Very good skid resistance, even in wet conditions.
- Very high resistance to hydrocarbons.

 0749	
BASF Belgium Coordination Center Comm. V. Business Belux - Construction Chemicals Nijverheidsweg 89, B-3945 Ham 09 BE0027/01	
EN 1504-3 Fast setting, thixotropic traffic repair mortar EN 1504-3 Principles 3.1 / 3.2 / 4.4 / 7.1 / 7.2	
Compressive strength	Class R4
Chloride ion content	≤ 0,05 %
Adhesion	≥ 2,0 MPa
Durability - Freeze/Thaw	≥ 2,0 MPa
Carbonation resistance	Pass
Skid resistance	Class III
Capillary absorption	≤ 0,5 kg/m ² ·x·h ^{-0,5}
Fire resistance	A1
Dangerous substances	Complies with 5.4

MasterEmaco T1100 TIX

Fast setting and hardening, extra high-strength, shrinkage compensated, fibre reinforced, thixotropic traffic repair mortar

APPLICATION METHOD

(a) Surface Preparation

Concrete must be fully cured, clean and sound to ensure good adhesion. All loose traces of concrete or mortar, dust, grease oil, etc. must be removed.

Damaged or contaminated concrete should be removed to obtain a keyed surface. Non-impact/vibrating cleaning methods, e.g. shot blasting, sandblasting or high water pressure blasting are recommended. Aggregate should be clearly visible on the surface of the concrete structure after surface preparation.

Cut the edges of the repair vertically to a minimum depth of 10 mm.

If reinforcing steel is visible, clean to a minimum grade of Sa 2 according to ISO 8501-1 / ISO 12944-4. Ensure back of rebar is also clean.

Heavily damaged reinforcement, or when rebar sections have decreased below the safety level, need to be replaced for structural reasons. Ensure a 2 cm rebar cover when installing additional reinforcement.

Although MasterEmaco T1100 TIX can be applied at ambient temperatures as low as -10°C, the temperature of the substrate should be minimum > 0°C and maximum + 30°C. Frozen substrates need to be defrosted just prior to the application of MasterEmaco T1100 TIX. Make sure that any metal parts, e.g. reinforcement and manhole frames are defrosted with a temperature above the freezing point. Try to keep the temperature uniform during application and hardening.

(b) Mixing

It is strongly recommended that only full bags are mixed. Damaged or opened bags should not be used.

First pour the clean tap water in the mixing container and afterwards, while mixing, add approx. 2/3 of the MasterEmaco T1100 TIX powder slowly and steadily into the water. Continue mixing for at least 1 minute. After 1 minute, add the rest of the powder and mix continuously until a homogeneous mortar is obtained.

Mix MasterEmaco T1100 TIX with a suitable paddle attached to a powerful, slow speed electric drill (max 400 rpm). The total mixing time is 3 to 4 minutes until a homogenous, plastic consistency is obtained. Only use clean uncontaminated water.

Mixing water needed: 3.1 to 3.6 litres per 25 kg bag are

required for plastic consistency.

Note: It is strongly recommended to comply the mixing times before adjusting or not the consistency by adding extra water! Do not mix more material as can be applied within the pot life of approximately 20 to 30 minutes at 20°C. MasterEmaco T1100 TIX with any other material. Only the addition of maximum 30% of clean, well sized gravel is permitted for applications with a thickness over 100 mm.

(c) Application

Concrete substrates and any metal parts coming in contact MasterEmaco T1100 TIX need to be defrosted.

The prepared substrate should be pre-soaked, preferably for 24 hours, but at least 2 hours before applying MasterEmaco T1100 TIX. The surface must be mat-damp, but without standing water.

For optimum curing of the product the temperatures during application of MasterEmaco T1100 TIX are between -10°C and +30°C.

Place MasterEmaco T1100 TIX onto the pre-dampened substrate and overfill to allow for compaction. Gently lower the manhole frame, curb or pavement stone into the fresh mortar and set to the required level. Make sure to apply enough material onto the individual bedding area before lowering the manhole frame or curb stone. Punctual applications of MasterEmaco T1100 TIX, and under-filling after previous levelling of manhole frames is not allowed.

In order to ensure optimum adhesion, a slurry coat of MasterEmaco T1100 TIX is brush applied onto the pre-dampened substrate prior to repair applications. Place MasterEmaco T1100 TIX onto the substrate, which is already primed by bonding slurry. Scratch the mortar into the roughness of the substrate.

MasterEmaco T1100 TIX is basically self-curing. Wet curing is not advised.

When working at sub-zero temperatures, cover MasterEmaco T1100 TIX with insulation materials or dry cloths until sufficiently hardened, preferably 24 hours or until MasterEmaco T1100 TIX is to be opened for traffic.

Do not apply MasterEmaco T1100 TIX if the temperature is expected to drop below -10°C during application or within 24 hours.

COVERAGE

Approximately 78 bags are required to produce 1 m³ of

MasterEmaco T1100 TIX

Fast setting and hardening, extra high-strength, shrinkage compensated, fibre reinforced, thixotropic traffic repair mortar

fresh mortar. 25 kg bag will yield approximately 12.9 litres of mortar.

FINISHING AND CLEANING

Tools and mixer must be cleaned immediately after use with water. Cured material can only be removed mechanically.

CURING

Full cure is reached in 28 days after the application at a constant temperature of 23 °C.

WORKING TIME

20 minutes in 20 °C ambient and substrate temperature.

PACKAGING

MasterEmaco T1100 TIX is available in 25 kg paper bags.

STORAGE

Store at ambient temperatures, out of direct sunlight, in cool, dry warehouse conditions and clear of the ground on pallets protected from rainfall prior to application.

SHELF LIFE

12 months if stored at above mentioned storage conditions.

WATCH POINTS

- Do not apply MasterEmaco T1100 TIX at temperatures below -10°C nor above +30°C.
- Do not add cement, sand or other substances that could affect the properties of MasterEmaco T1100 TIX.
- Never add water or fresh mortar to a mortar mix which has already begun to set.
- Keep the mixing water ratio between the recommended limits.
- When applying MasterEmaco T1100 TIX at cold or sub-zero temperatures, we advise to use warm mixing water

in order not to delay the hardening of the mortar too much.

- For applications over 100 mm, 7.5 kg of clean gravel (4-8 mm or 8-16 mm depending on the thickness) may be added to 25 kg of MasterEmaco T1100 TIX powder.
- Do not wet cure the material. Prevent from rain.

HANDLING AND TRANSPORT

Usual preventive measures for the handling of chemical products should be observed when using this product, for example do not eat, smoke or drink while working and wash hands when taking a break or when the job is completed.

Specific safety information referring the handling and transport of this product can be found in the Material Safety Data Sheet. For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

Disposal of product and its container should be carried out according to the local legislation in force. Responsibility for this lies with the final owner of the product.

CONTACT DETAILS

Master Builders Solutions UK Ltd

19 Broad Ground Road

Lakeside

Redditch

Worcestershire

B98 8YP

Tel: +44 (0) 1527 512255

Fax +44 (0) 1527 503576

www.master-builders-solutions.basf.co.uk

© Master Builders Solutions UK Ltd

MasterEmaco T1100 TIX

Fast setting and hardening, extra high-strength, shrinkage compensated, fibre reinforced, thixotropic traffic repair mortar

Product Data				
Property	Standard	Data	Unit	
Chemical Base	-	Cement	-	
Colour	-	Grey	-	
Grain Size	maximum	3.15	mm	
Chloride Ion Content	EN 1015-17	≤ 0.05	%	
Layer Thickness	minimum maximum	10 ¹ - 25 ² 100 ¹ - 150 ²	mm	
Fresh Mortar Density	-	Approx. 2.20	g/cm ³	
Mixing Water for 25 kg Bag	-	ca. 3.1 – 3.6	l	
Working Time ³	-	20	Minute	
Open to Traffic (at 20°C)	light traffic heavy traffic	60 120	Minute	
Application Temperature (ambient and substrate)	-	-10 - +30	Celcius	
Modulus of Elasticity	EN 13412	35,000	N/mm ²	
Compressive Strength		+20°C⁴ +5°C⁵ -5°C⁶		
	2 hours	31 3 8	N/mm ²	
	4 hours	48 15 18		
	1 day	62 63 55		
	7 days	80 83 80		
	28 days	93 86 86		
Flexural Strength	1 day 7 days 28 days	EN 196-1	≥ 7 ≥ 8 ≥ 10	N/mm ²
Adhesion to Concrete	28 days	EN 1542	≥ 3.0	N/mm ²
Adhesion to Concrete after Freeze-Thaw (50 cycles with salt)	28 days	EN 13687-1	≥ 3.0	N/mm ²
Carbonation resistance	28 days	EN 13295	d _k ≤ Ref. Concrete	mm
Skid Resistance	28 days	EN 13036-4	Class III – tested wet	
Capillary Absorption	28 days	EN 13057	≤ 0.1	kg.m ⁻² .h ^{-0.5}
Cracking Tendency (I)		Coutinho Ring	No Cracking	Up to 180 days

MasterEmaco T1100 TIX

Fast setting and hardening, extra high-strength, shrinkage compensated, fibre reinforced, thixotropic traffic repair mortar

Product Data				
Property		Standard	Data	Unit
Drying Shrinkage	28 days	EN 12617-4	≤ 0.300	mm/m
Pull out strength of steel rebar	28 days	Rilem-CEB-FIP RC6-78)	≥ 20	N/mm ²

Note: ¹ Used as repair mortar

² Used as bedding mortar

³ Hardening times are measured at 21°C ± 2°C and 60% ± 10% relative humidity. Higher temperatures will reduce these times and lower temperatures will extend them. Technical data shown are statistical results and do not correspond to guaranteed minima. Tolerances are those described in appropriate performance standards.

⁴ Curing, water and powder temperature: 20°C

⁵ Curing; water and powder temperature +5°C

⁶ Curing -5°C; water and powder temperature +20°C

MasterEmaco T1100 TIX - Master Builders Solutions UK Ltd, Version 1

Health and Safety

*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

Solvent Based Products

Use in well ventilated areas; avoid inhaling. Suitable respiratory equipment may be needed, eg when spraying. Can cause skin, eye irritation. Wear protective eye shields and gloves during use. Do not smoke or allow sparks or naked lights when stored or in use.

Resin Products

Can cause irritation, dermatitis or allergic reaction. Use protective equipment particularly for skin and eyes. Use only in well ventilated areas.

Spillage

Chemical products can cause damage; clean spillage immediately.

DISCLAIMER

"Master Builders Solutions UK Ltd" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct. However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use.

Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application.

Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.