

MasterSeal M869

A highly elastic, non-solvented, two component, hand applied membrane for use in Car Park waterproofing applications

DESCRIPTION

MasterSeal M869 is a hand applied, non-solvented, 2-component, self levelling polyurethane based, elastomeric coating.

FIELD OF APPLICATION

MasterSeal M869 is the waterproofing membrane for hand applied MasterSeal car park deck waterproofing system amongst other applications.

FEATURES AND BENEFITS

- monolithic – no laps, welds or seams
- fully bonded
- high water vapour permeability – low risk of blistering
- excellent mechanical properties
- excellent crack bridging capability
- resistant to puncture
- thermoset – does not soften at elevated temperatures
- remains elastic at low temperatures Tg approx. - 45°C
- non-solvented
- approved by the United Kingdom Water Regulations Advisory Scheme, Listing No: 080559

SUBSTRATE PRETREATMENT

The preparation of the substrate and the use of the appropriate primer are of paramount importance. All surfaces to which MasterSeal M869 is applied must be clean and dry and free from oil, grease and loose material and any other contamination which might impair adhesion.

Primer selection will depend on substrate type. Application should take place within the re-coat interval of the primer, to which it is to be applied.

Refer to primer technical data sheet.

APPLICATION CONDITIONS

For best results, materials, substrate and air temperature should be in the range 15 - 25°C

Low temperatures will reduce flow and can impair the visual appearance of the membrane.

High temperatures will shorten the open time and can impair the appearance of the membrane.

The temperatures should not fall below the minimum stated until the material is fully cured. The temperature of the substrate must be at least 3°C above the dew point both during the application and for at least a further 6 hours (at 15°C).

APPLICATION

MasterSeal M869 is supplied in working units. Before mixing, both A and B components should be preconditioned to a temperature of 15 to 20°C.

Pour the entire contents of part A into the container of part B. mix with a low speed (ca. 300 rpm) electric drill and paddle for at least 3 minutes until homogeneous. Scrape the sides and bottom of the container several times during mixing to ensure complete mixing. Keep the mixing head submerged to avoid entrapping air.

Do not work out of the original container. Decant the mixed material into a fresh container and remix for another minute.

MasterSeal M869 is poured onto the prepared substrate and spread with a notched trowel or spreader (rubber or steel). Bubbles should be removed by rolling with a spiked roller.

COVERAGE

Typically 1.2kg/m² per mm thickness. Minimum membrane thickness: 1.5mm.

FINISHING AND CLEANING

Tools must be cleaned immediately after use with xylene or other suitable solvent.

CURING

Full cure is reached in 7 days after the application at a constant temperature of 20°C.

PACKAGING

MasterSeal M869 is supplied in 30kg working packs.

STORAGE

Store in original containers under normal warehouse conditions. Off the ground, dry and at a temperature between 5 - 30°C. Do not expose to direct sunlight.

MasterSeal M869

A highly elastic, non-solvented, two component, hand applied membrane for use in Car Park waterproofing applications

SHELF LIFE

For maximum shelf life under these conditions, see "Best before....." label.

EU Regulation 2004/42 (Decopaint Guideline)

This product conforms to the EU directive 2004/42/EG (Deco-Paint directive) and contains less than the maximum allowable VOC limit (Stage 2, 2010).

According to the EU directive 2004/42, the maximum allowable VOC content for the Product Category IIA / j is 500 g/l (Limit: Stage 2, 2010). The VOC content for MasterSeal M869 is < 500 g/l (for the ready to use product).

HANDLING AND TRANSPORT

Usual preventive measures for the handling of chemical products should be observed when using this product, for example do not eat, smoke or drink while working and wash hands when taking a break or when the job is completed.

Specific safety information referring the handling and transport of this product can be found in the Material Safety Data Sheet. For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

Disposal of product and its container should be carried out according to the local legislation in force. Responsibility for this lies with the final owner of the product.

CONTACT DETAILS

Master Builders Solutions UK Ltd
19 Broad Ground Road
Lakeside
Redditch
Worcestershire
B98 8YP
Tel: +44 (0) 1527 512255
Fax +44 (0) 1527 503576

www.master-builders-solutions.com/en-gb

© Master Builders Solutions UK Ltd

MasterSeal M869

A highly elastic, non-solvented, two component, hand applied membrane for use in Car Park waterproofing applications

Product Data	
Mixing ratio, By weight	100:50
Density g/cm ³ at 20°C	1.2
Re-coat intervals at 20°C	
minimum / hours	9
maximum / days	2
Fully cured at 20°C / days	7
Ambient and substrate temperature	
Minimum / °C	5
Maximum / °C	30
Relative humidity, maximum / % RH	80
Physical properties after 28 days	
Shore A hardness	72
Elongation, DIN 53504	800

The above figures are intended as a guide only and should not be used as a basis for specifications.



When MasterSeal Membrane 869 is used as a membrane with other MasterTop and MasterSeal products the system conforms to the relevant CE marks.

Please refer to the relevant Declaration of Performance and the product and system data sheets.

MasterSeal M869

A highly elastic, non-solvented, two component, hand applied membrane for use in Car Park waterproofing applications

MasterSeal M869 - Master Builders Solutions UK Ltd, Version 1

Health and Safety

*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

Solvent Based Products

Use in well ventilated areas; avoid inhaling. Suitable respiratory equipment may be needed, eg when spraying. Can cause skin, eye irritation. Wear protective eye shields and gloves during use. Do not smoke or allow sparks or naked lights when stored or in use.

Resin Products

Can cause irritation, dermatitis or allergic reaction. Use protective equipment particularly for skin and eyes. Use only in well ventilated areas.

Spillage

Chemical products can cause damage; clean spillage immediately.

DISCLAIMER

"Master Builders Solutions UK Ltd" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct. However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use.

Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application.

Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.