

# MasterSeal Traffic 2260


## A skid resistant car park deck coating system

For use on intermediate decks and ramps where a hard wearing, limited crack bridging system is required

		<b>Consumption</b>
<div style="display: flex; align-items: center;"> <div style="width: 15px; height: 15px; background-color: #FFC000; margin-right: 5px;"></div> <div> <p><b>Primer</b></p> </div> </div>	<p><b>MasterTop P622</b>                  2 component, moisture tolerant epoxy                  or  <b>MasterTop P604</b>                  2 component pre-filled epoxy</p>	<p>0.3 – 0.5 kg/m<sup>2</sup></p>
<div style="display: flex; align-items: center;"> <div style="width: 15px; height: 15px; border: 1px solid black; margin-right: 5px;"></div> <div> <p><b>Sand broadcast</b></p> </div> </div>	<p><b>MasterTop F5 filler</b>                  (0.3 – 0.8mm), uniformly applied</p>	<p>1.0 – 1.2 kg/m<sup>2</sup></p>
<div style="display: flex; align-items: center;"> <div style="width: 15px; height: 15px; background-color: #FFC000; margin-right: 5px;"></div> <div> <p><b>Optional Scratchcoat</b>                      Up to 1mm profile</p> </div> </div>	<p><b>MasterTop P622 or MasterTop P604</b>                  1:1 filled with MasterTop F1 filler (0.1 – 0.3mm), uniformly applied</p>	<p>*0.6 1.0 kg/m<sup>2</sup></p>
<div style="display: flex; align-items: center;"> <div style="width: 15px; height: 15px; border: 1px solid black; margin-right: 5px;"></div> <div> <p><b>Sand broadcast</b></p> </div> </div>	<p><b>MasterTop F5 filler</b>                  0.3 – 0.8mm or 0.7 – 1.2mm oven dried silica sand, applied to rejection</p>	<p>2.0 – 3.0 kg/m<sup>2</sup></p>
<div style="display: flex; align-items: center;"> <div style="width: 15px; height: 15px; background-color: #000000; margin-right: 5px;"></div> <div> <p><b>Topcoat</b></p> </div> </div>	<p><b>MasterSeal TC374</b>                  Pigmented, epoxy, 2 component, solvent free, gloss finish</p>	<p>0.4 – 0.89 kg/m<sup>2</sup></p>
<p><b>Total thickness of system</b></p>	<p>Approx. 1.2 – 1.5mm</p>	

**Note:** Consumptions are indicative, and may be higher depending on substrate roughness, temperature and porosity as well as waste produced during application

\* Consumption including filler



# MasterSeal Traffic 2260

## A skid resistant car park deck coating system

For use on intermediate decks and ramps where a hard wearing, limited crack bridging system is required

### CONTACT DETAILS

Master Builders Solutions UK Ltd  
 19 Broad Ground Road  
 Lakeside  
 Redditch  
 Worcestershire  
 B98 8YP  
 Tel: +44 (0) 1527 512255  
 Fax +44 (0) 1527 503576  
[www.master-builders-solutions.com/en-gb](http://www.master-builders-solutions.com/en-gb)

© Master Builders Solutions UK Ltd

#### DISCLAIMER

"Master Builders Solutions UK Ltd" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct. However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use.

Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application.

Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.

<b>CE</b>	
1119	
Master Builders Solutions UK Ltd 19 Broad Ground Road Lakeside, Redditch Great Britain B98 8YP	
08	
226001	
EN 1504-2:2004	
Surface protection material - coatings	
Linear shrinkage	NPD
Compressive strength	NPD
Abrasion resistance	≤ 3000 mg
Permeability to CO <sub>2</sub>	Sd > 50
Permeability to water vapour	Class II
Capillary absorption and permeability to water	< 0.1 kg/(m <sup>2</sup> xh <sup>0.5</sup> )
Thermal compatibility after freeze-thaw cycling	≥ 2.0 N/mm <sup>2</sup>
Resistance to severe chemical attack	Reduction of hardness < 50 %
Impact resistance	Class I
Adhesion strength by pull-off test	≥ 2.0 N/mm <sup>2</sup>
Reaction to fire	B <sub>f</sub> -s1
Skid resistance	Class III