

Ucrete DPAS

Antistatic defined profile heavy duty screed

DESCRIPTION

Ucrete DPAS is a unique heavy duty resin floor with exceptional resistance to aggressive chemicals, heavy impact and temperatures up to 80°C providing antistatic properties for use in explosion hazarded areas.

Ucrete DP is a family of products with defined surface profiles suitable for applications in wet and dry process environments.

The system offers a uniformity of surface texture with enhanced aesthetics, with a gloss or matt finish, so providing a safe and attractive working environment.

Two antistatic versions are available with fine and medium textured surfaces to meet a range of slip resistance, aesthetics and ease of cleaning requirements.

Ucrete Industrial Flooring has been widely used throughout industry for more than 50 years, many of the older floors are still in service. A detailed project reference list is available upon request.

FEATURES AND BENEFITS

- Expert installation by fully trained licensed applicators
- Suitable for application on to 7 day old concrete and 3 day old polymer screed
- Formulated aggregates for specifiable levels of slip resistance
- Non-tainting from the end of mixing, as tested by Campden BRI
- Gloss and matt versions available
- Does not support bacterial or mould growth

PERFORMANCE DATA

ANTISTATIC PROPERTIES

Ucrete DP10AS and Ucrete DP20AS comply with the requirements of BS5958, EN1081 and DIN51953.

For details on earthing antistatic floors refer to the separate data sheet, 'Guidelines to Earthing of Ucrete Antistatic Floors.'

AIR QUALITY

Ucrete has been awarded the Indoor Air Comfort Gold Label following extensive VOC emission chamber testing and auditing of quality management and production control procedures.

This demonstrates that Ucrete is an extremely clean product without any volatile compounds that might taint foodstuff or affect the well-being of personnel.

All Ucrete grades give very low emissions and conform to all the emissions requirements for indoor flooring systems in Europe including AgBB in Germany, Afsset in France, where they are rated A+ for VOC emissions (the cleanest rating), and M1 in Finland.

NON TAINTING

Ucrete DP systems are non-solvented and non-tainting from the end of mixing, as tested by Campden BRI.

SLIP RESISTANCE

The Ucrete DP surface profiles have coefficient of friction as determined to EN13038 Part 4 using the 4S rubber on the wet floor as follows:

Ucrete DP10AS	45 - 50
Ucrete DP20AS	45 - 55

The Ucrete DP surface profiles conform to DIN51130 as follows:

Ucrete DP10AS	R11	-
Ucrete DP20AS	R13	V4

The extremely robust aggregates used to provide the texture of Ucrete DP20AS are designed to maintain optimum slip resistance for many years.

Optimum slip resistance can only be maintained with regular cleaning.

TEMPERATURE RESISTANCE

The Ucrete DP resins do not start to soften until temperatures above 130°C are exceeded.

The 6mm Ucrete DPAS floor is fully resistant to liquid spillage and discharge up to 80°C and can be lightly steam cleaned.

Suitable for freezer temperatures down to -25°C

CHEMICAL RESISTANCE

Ucrete DPAS offers exceptional resistance to a wide range of chemical aggressors. For example, Ucrete DPAS is resistant to the following commonly encountered chemicals:

Most dilute and concentrated organic acids such as, Acetic Acid, Lactic Acid, Oleic Acid and Citric Acid as commonly found in the food industry,

Ucrete DPAS

Antistatic defined profile heavy duty screed

Mineral acids: hydrochloric, nitric, phosphoric and sulphuric.

Dilute and concentrated alkalis, including sodium hydroxide to 50% concentration

Animal fats and vegetable oils, sugars flavourings and essences.

Mineral oils, kerosene, gasoline and brake fluids
A wide range of organic solvents including Methanol, Xylene Ethers and Chlorinated solvents

Extensive chemical resistance tables are available upon request

Note: some staining or discolouration may occur with some chemicals, depending upon the nature of the spillage and the standards of housekeeping employed.

IMPACT RESISTANCE

With high mechanical strengths and a low elastic modulus, Ucrete DPAS floors are very resilient and able to withstand severe impact loads. While no material is indestructible and surface chipping may occur, brittle modes of failure resulting in cracking and disbondment are unknown with Ucrete floors.

SUBSTRATE MOISTURE TOLERANCE

Ucrete Industrial Flooring is extremely tolerant to residual substrate moisture and can be installed directly onto 7 day old concrete, or onto old good quality concretes with high moisture contents without the use of special primers, provided there is a functioning DPM within the structure. This enables rapid construction programmes to be maintained and facilitates refurbishment work in wet process areas.

Epoxy surface DPMs should not be used as they soften under high temperature conditions and will lead to floor failure.

PERMEABILITY

Ucrete DPAS exhibits zero absorption when tested to CP.BM2/67/2.

CLEANING & HYGIENE

Ucrete flooring systems are accredited for use in facilities operating HACCP based food safety systems.

Regular cleaning and maintenance will enhance the life and appearance of any floor.

Ucrete DPAS is cleaned using industry standard cleaning chemicals and equipment. The use of a food industry standard scrubber drier machine is recommended.

Detailed cleaning guidelines are available from your local Master Builders Solutions office.

COLOURS

Ucrete DPAS is available in nine standard colours:

Red	Orange	Yellow	Bright Yellow
Grey	Cream	Blue	Green/Brown
Green			

Ucrete floor systems have been formulated to provide the very highest chemical and heat resistance. As a direct result some yellowing of the installed floor will occur in areas of direct UV exposure. This is most apparent in lighter colours.

SPECIFICATION

The floor finish shall be Ucrete DP10AS/DP20AS*, from Master Builders Solutions UK Ltd, of 19 Broad Ground Road, Redditch, Worcestershire, B98 8YP, installed at 6mm with a matt/gloss* finish in accordance with the manufacturer's instructions.

*(select as required)

SUBSTRATE QUALITY

Concrete substrates should be visibly dry and have a minimum tensile strength of 1.5 MPa.

Refer to the guide 'The Design & Preparation of Substrates for Ucrete Industrial Flooring'

All joints in the substrate concrete subject to movement should be reflected through the Ucrete floor and sealed with a suitable sealant.

EARTHING

The floor must be properly earthed with at least 2 earth linkages per room to ensure that all areas of floor are reliably connected to earth.

For more detailed information on earthing antistatic floors refer to the separate data sheet 'Guidelines to Earthing of Ucrete antistatic floors'

APPLICATION CONDITIONS

For best results materials, substrate and air temperature should be in the range 15–25°C. Whilst Ucrete DPAS will cure out effectively over a wide range of temperatures the optimum appearance and profiles are most readily achieved under good site conditions

Ucrete DPAS

Antistatic defined profile heavy duty screed

Low temperatures will retard the setting and can impair the visual appearance of the floor.

High temperatures will shorten the open time and can impair the appearance of the floor.

CURING

Normally Ucrete DPAS floors can be put into service within 24 hours even at 8°C.

UCRETE LICENSED APPLICATORS

To achieve the best floor possible with a professional installation, you must use one of our fully trained Ucrete Licensed Applicators.

BIM OBJECTS

All Ucrete products have a dedicated BIM object available to download from the [NBS National BIM](#) Library or [Bimobject](#).

STORAGE

In covered warehouse conditions, above 5°C and below 30°C and out of direct sunlight. Materials must be raised off the floor and kept dry. Liquid components must be protected from frost.

WARNINGS AND PRECAUTIONS

In its cured state Ucrete is physiologically non-hazardous.

For normal flooring applications Ucrete does not require the use of respiratory protective equipment during installation.

Operatives should consult the CoSHH risk assessment and their work instructions.

HANDLING AND TRANSPORT

Usual preventive measures for the handling of chemical products should be observed when using this product, for example do not eat, smoke or drink while working and wash hands when taking a break or when the job is completed.

Specific safety information referring the handling and transport of this product can be found in the Material Safety Data Sheet. For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

Disposal of product and its container should be carried out according to the local legislation in force. Responsibility for this lies with the final owner of the product.

CONTACT DETAILS

Master Builders Solutions UK Ltd

19 Broad Ground Road

Lakeside

Redditch

Worcestershire

B98 8YP

Tel: +44 (0) 1527 512255

Fax +44 (0) 1527 503576

www.master-builders-solutions.com/en-gb

© Master Builders Solutions UK Ltd

Ucrete DPAS

Antistatic defined profile heavy duty screed

Product Data	
Density	2000 - 2090 kg/m ³
Compressive strength (EN13892-2)	48 - 54 MPa
Tensile strength (BS6319 Part 7)	5 - 7 MPa
Flexural strength (EN13892-2)	12 - 14 MPa
Compressive modulus (BS 6319:Part 6)	3250 - 5000 MPa
Adhesive strength to concrete (EN13892-8)	concrete failure
Coefficient of thermal expansion (ASTM C531:Part 4.05)	$4 \times 10^{-5} \text{ }^{\circ}\text{C}^{-1}$
Fire Testing (EN13501: Part 1)	B _{FL} – S ₁
Resistance to earth (EN1081)	<10 ⁶ Ohm

Note:- Samples cured for 28 days at 20 °C

	
Master Builders Solutions UK Ltd 19 Broad Ground Road Lakeside, Redditch, B98 8YP	
04	
0111374, 01060355	
EN 13813:2002	
Synthetic resin screed material	
Reaction to fire:	B _{FL} – S ₁
Release of corrosive substances:	NPD
Water permeability:	NPD
Mechanical resistance:	NPD
Wear resistance:	AR0,5
Bond strength:	B>2,0
Impact resistance:	IR>4
Sound insulation:	NPD
Sound absorption:	NPD
Thermal resistance:	NPD
Chemical resistance:	NPD
Electrical resistance:	ER ² <10 ⁶ - ER ³ <10 ⁶



Ucrete DPAS

Antistatic defined profile heavy duty screed

Ucrete DPAS - Master Builders Solutions UK Ltd, Version 2

Health and Safety

*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

Solvent Based Products

Use in well ventilated areas; avoid inhaling. Suitable respiratory equipment may be needed, eg when spraying. Can cause skin, eye irritation. Wear protective eye shields and gloves during use. Do not smoke or allow sparks or naked lights when stored or in use.

Resin Products

Can cause irritation, dermatitis or allergic reaction. Use protective equipment particularly for skin and eyes. Use only in well ventilated areas.

Spillage

Chemical products can cause damage; clean spillage immediately.

DISCLAIMER

"Master Builders Solutions UK Ltd" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct. However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use.

Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application.

Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.