

Ucrete TZAS

Heavy duty antistatic terrazzo floor finish

DESCRIPTION

Ucrete TZAS is a unique heavy duty antistatic resin floor with exceptional resistance to aggressive chemicals, heavy abrasion and thermal shock.

Ucrete TZAS provides a smooth protective floor finish suitable for applications in predominantly dry environments.

It is dense and impervious providing the ideal floor finish for applications in pharmaceutical production facilities including process areas, clean room, laboratory, packing hall and warehouse applications and wherever a highly attractive, robust, long lived floor is required.

Ucrete Industrial Flooring has been widely used throughout industry for more than 50 years, many of the older floors are still in service. A detailed project reference list is available upon request

FEATURES AND BENEFITS

- Expert installation by fully trained licensed applicators
- Suitable for application on to 7 day old concrete and 3 day old polymer screed
- Hygienic and easy to clean
- Non-solvented and non-tainting
- Highly attractive terrazzo appearance
- Very long life
- Antistatic properties for explosion protection.

PERFORMANCE DATA

AIR QUALITY

Ucrete has been awarded the Indoor Air Comfort Gold Label following extensive VOC emission chamber testing and auditing of quality management and production control procedures.

This demonstrates that Ucrete is an extremely clean product without any volatile compounds that might taint foodstuff or affect the well-being of personnel.

All Ucrete grades give very low emissions and conform to all the emissions requirements for indoor flooring systems in Europe including AgBB in Germany, Afsset in France, where they are rated A+ for VOC emissions (the cleanest rating), and M1 in Finland.

For further information please contact your local Master Builders Solutions representative.

NON TAINING

Ucrete TZAS is non-solvented and non tainting from the end of mixing, as tested by the Campden BRI.

ANTISTATIC PROPERTIES

Ucrete TZAS, complies with the requirements of BS5958, DIN51953 and EN 61340-5-1.

For more detailed information on earthing anti-static floors, refer to the separate datasheet 'Guidelines to Earthing of Ucrete antistatic floors'.

SLIP RESISTANCE

Ucrete TZAS floors have a coefficient of friction as determined to EN 13036 Part 4 with 4S rubber on the wet floor as follows:

Ucrete TZAS 35 - 40

Optimum slip resistance can only be maintained with regular cleaning.

TEMPERATURE RESISTANCE

The Ucrete TZAS resins do not start to soften until temperatures above 130°C, are exceeded. Specifications are available that are fully serviceable up to 130°C and resistant to occasional spillage up to 150°C.

Correctly installed, Ucrete TZAS can withstand regular and routine discharges of boiling water.

Suitable for freezer temperatures down to -40°C

CHEMICAL RESISTANCE

Ucrete TZAS offers exceptional resistance to a wide range of chemical aggressors. For example, Ucrete is resistant to spillages of the following commonly encountered classes of chemicals:

Most dilute and concentrated organic acids such as Acetic acid, Lactic Acid, Oleic Acid and Citric Acid, as commonly found in the food industry,

Dilute and concentrated acids: hydrochloric, nitric, phosphoric and sulphuric.

Dilute and concentrated alkalis, including sodium hydroxide to 50% concentration

Animal fats and vegetable oils, sugars flavourings and essences.

Mineral oils, kerosene, gasoline and brake fluids

A wide range of organic solvents including Methanol, Xylene Ethers and Chlorinated solvents

Note: some staining or discolouration may occur with some chemicals, depending upon the nature of the spillage and the standards of house keeping employed.

Ucrete TZAS

Heavy duty antistatic terrazzo floor finish

Extensive chemical resistance tables are available in the separate data sheet 'A guide to the chemical resistance of Ucrete Flooring'. For detailed information, please contact your local Master Builders Solutions office for guidance.

IMPACT RESISTANCE

With high mechanical strengths and a low elastic modulus, Ucrete TZAS is very resilient and able to withstand severe impact loads. While no material is indestructible and surface chipping may occur, brittle modes of failure resulting in cracking and disbondment are unknown with Ucrete floors

Regular cleaning and maintenance will enhance the life and appearance of any floor. Ucrete TZAS is readily cleaned with industry standard cleaning chemicals and equipment. Please consult your local cleaning chemical or equipment supplier.

Detailed cleaning guidelines are available from your local Master Builders Solutions office.

PERMEABILITY

Ucrete TZAS exhibits zero absorption when tested to CP.BM2/67/2.

CLEANING & HYGIENE

Regular cleaning and maintenance will enhance the life and appearance of any floor. Ucrete TZ is readily cleaned with industry standard cleaning chemicals and equipment. Please consult your local cleaning chemical or equipment supplier.

Detailed cleaning guidelines are available from your local Master Builders Solutions office.

COLOURS

Ucrete TZAS is available in nine standard colours:

Red	Orange	Yellow	Bright Yellow
Grey	Cream	Blue	Green/Brown
Green			

Ucrete floor systems have been formulated to provide the very highest chemical and heat resistance. As a direct result some yellowing of the installed floor will occur in areas of direct UV exposure. This is most apparent in lighter colours.

SPECIFICATION

The floor finish shall be Ucrete TZAS from Master Builders Solutions UK Ltd of 19 Broad Ground Road, Redditch, Worcestershire, B98 8YP installed 9/12* mm in thickness in accordance with the manufacturers' instructions

*(select as required)

*A 9mm Ucrete TZAS floor is fully resistant to high temperature spillage and discharge up to 120°C and is fully steam cleanable. Suitable for freezer temperatures down to -40°C.

*A 12mm Ucrete TZAS floor is fully resistant to high temperature spillage and discharge up to 130°C and occasional spillage up to 150°C and is fully steam cleanable. Suitable for freezer temperatures down to -40°C.

In extreme thermal shock environments a well designed substrate of good quality concrete is essential.

SUBSTRATE QUALITY

Concrete substrates should be visibly dry and have a minimum tensile strength of 1.5 MPa.

Refer to the guide 'The Design & Preparation of Substrates for Ucrete Industrial Flooring'

All joints in the substrate concrete subject to movement should be reflected through the Ucrete floor and sealed with a suitable sealant.

SUBSTRATE MOISTURE TOLERANCE

Ucrete Industrial Flooring is extremely tolerant to residual substrate moisture and can be installed directly onto 7 day old concrete, or onto old good quality concretes with high moisture contents without the use of special primers, provided there is a functioning DPM within the structure.

This enables rapid construction programmes to be maintained and facilitates refurbishment work in wet process areas.

Epoxy surface DPMs should not be used as they soften under high temperature conditions and will lead to floor failure.

APPLICATION CONDITIONS

For best results materials, substrate and air temperature should be in the range 5 - 20°C. Whilst Ucrete TZAS will cure out effectively over a wide range of temperatures, the optimum appearance is most readily achieved under good site conditions.

COVERAGE

9mm: 20 - 22 kg/m²

12mm: 26 - 27 kg/m²

CURING

Normally Ucrete TZAS floors can be put into service within 24 hours.

Ucrete TZAS

Heavy duty antistatic terrazzo floor finish

UCRETE LICENSED APPLICATORS

To achieve the best floor possible with a professional installation, you must use one of our fully trained Ucrete Licensed Applicators.

BIM OBJECTS

All Ucrete products have a dedicated BIM object available to download from the [NBS National BIM](#) Library or [Bimobject](#).

STORAGE

In covered warehouse conditions, above 5°C and below 30°C and out of direct sunlight. Materials must be raised off the floor and kept dry. Liquid components must be protected from frost.

WARNINGS AND PRECAUTIONS

In its cured state Ucrete is physiologically non-hazardous.

For normal flooring applications Ucrete does not require the use of respiratory protective equipment during installation.

Operatives should consult the CoSHH risk assessment and their work instructions.

HANDLING AND TRANSPORT

Usual preventive measures for the handling of chemical products should be observed when using this product, for example do not eat, smoke or drink while working and wash hands when taking a break or when the job is completed.

Specific safety information referring the handling and transport of this product can be found in the Material Safety Data Sheet. For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

Disposal of product and its container should be carried out according to the local legislation in force. Responsibility for this lies with the final owner of the product.

CONTACT DETAILS

Master Builders Solutions UK Ltd,
19 Broad Ground Road
Lakeside
Redditch
Worcestershire
B98 8YP

Tel: +44 (0) 1527 512255

Fax +44 (0) 1527 503576

www.master-builders-solutions.com/en-gb


© Master Builders Solutions UK Ltd

Ucrete TZAS

Heavy duty antistatic terrazzo floor finish

Product Data	
Density	2090 kg/m ³
Compressive strength (EN13892-2)	52 - 57 MPa
Tensile strength (BS6319 Part 7)	6 MPa
Flexural strength (EN13892-2)	14 MPa
Compressive modulus (BS 6319:Part 6)	3250 MPa
Adhesive strength to concrete (EN13892-8)	concrete failure
Coefficient of thermal expansion (ASTM C531:Part 4.05)	2.4 x 10 ⁻⁵ °C ⁻¹
Fire Testing (EN13501: Part 1)	B _{FL} – S ₁
Resistance to earth (EN1081) (EN61240-4-1)	< 10 ⁶ Ohm < 10 ⁹ Ohm

Note:- Samples cured for 28 days at 20 °C

	
Master Builders Solutions UK Ltd 19 Broad Ground Road Lakeside, Redditch Great Britain B98 8YP	
04	
01040365	
EN 13813:2002	
Synthetic resin screed material	
Reaction to fire:	B _{FL} – S ₁
Release of corrosive substances:	NPD
Water permeability:	NPD
Mechanical resistance:	NPD
Wear resistance:	AR0,5
Bond strength:	B>2,0
Impact resistance:	IR>4
Sound insulation:	NPD
Sound absorption:	NPD
Thermal resistance:	NPD
Chemical resistance:	NPD
Electrical resistance:	ER ² <10 ⁶ -ER ³ <10 ⁶



Ucrete TZAS

Heavy duty antistatic terrazzo floor finish

Ucrete TZAS – Master Builders Solutions UK Ltd, Version 2

Health and Safety

*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

Solvent Based Products

Use in well ventilated areas; avoid inhaling. Suitable respiratory equipment may be needed, eg when spraying. Can cause skin, eye irritation. Wear protective eye shields and gloves during use. Do not smoke or allow sparks or naked lights when stored or in use.

Resin Products

Can cause irritation, dermatitis or allergic reaction. Use protective equipment particularly for skin and eyes. Use only in well ventilated areas.

Spillage

Chemical products can cause damage; clean spillage immediately.

DISCLAIMER

"Master Builders Solutions UK Ltd" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct. However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use.

Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application.

Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.