

MasterTop 333

Dust arresting and hardening treatment

DESCRIPTION

MasterTop 333 is a deep penetrating silicate solution for sealing and dust-proofing powdery or friable concrete and concrete block surfaces

RECOMMENDED USES

Old concrete floors that are dusting. Powdery or friable concrete that is dusting due to inadequate curing and/or low cement content and concrete block work with friable surfaces. New concrete surfaces to seal against oil, grease and many chemical solutions

FEATURES AND BENEFITS

Dust arresting treatment – Binds the surface of old or new concrete to reduce dusting

Prolongs the serviceable life of "problem" concrete floors before re-topping is required
- Deep penetrating liquid hardener.

Increased durability and resistance to abrasion - protects concrete surfaces by sealing and hardening concrete surfaces

• **dense surface** - Resists penetration of oil and grease. Protects concrete from the corrosive effects of smoke fumes, mild acids, salts and many other aggressive chemical solutions

Economical – large areas can be dustproofed with an application

Caution:

Will etch glass

Not suitable for clay, bricks or pavers

APPLICATION

Preparation

Correct surface preparation is essential to ensure a successful application. Surfaces must be dry and absorbent, free from oil, grease, paint, curing compounds and other contaminants.

New concrete floors:

New concrete floors that require hardening, sealing or dust arresting treatment should be left until they are at least 28 days old then dilute

MasterTop 333 1:1 with clean potable water, and carefully apply by broom, mop, spray or squeegee until absorption ceases and all pores are filled. Do not allow **MasterTop 333** to puddle. Liquid

membrane curing compounds should NOT be used when using **MasterTop 333**, use alternative methods such as polythene film or water curing.

Old concrete floors, soft stone, concrete blocks:

After surface preparation, apply 3 coats, at 24 hour intervals.

1st coat diluted 1:3 with potable water

2nd coat diluted 1:2 with potable water

3rd coat diluted 1:1 with potable water

The application of the first coat should continue until no more solution will penetrate the surface. Allow to dry for 24 hours. Repeat procedure for 2nd and 3rd coats.

During application do not allow puddles to form or a significant surface build will occur. A glaze or sheen should not form on the surface. **MasterTop 333** is formulated to penetrate, not form a surface coating. 24 hours after the completion of the 3rd coat, wash and broom any excess surface material away.

NOTE: Surfaces treated with **MasterTop 333** can exhibit a whitish, blotchy appearance. Where the treated surface has been allowed to become wet up to seven days after the final coat, it can become slippery. To overcome these surface conditions, neutralise by brooming a solution of 1 part hydrochloric acid diluted in 15 parts of water onto the floor. Hose down after 10 minutes and allow to dry.

The above procedure is also necessary before considering overcoating with paints, renders etc. A small test area is recommended prior to application of any subsequent surface finish.

Treated surfaces may be opened to traffic when the surface has dried completely and no tackiness remains, usually after 24 hours.

ESTIMATING DATA

Coverage will vary greatly depending on the porosity and texture of the surface of the concrete and its age.

MasterTop 333

Old concrete can take double the quantity of **MasterTop 333** compared to new concrete, as will a very rough profile at the surface. As a guide:

Concrete Finish Old/New Coverage

Wood float Old 0.17 litre/m² (6m²/litre)

Wood float New 0.10 litre/m² (10m²/litre)

Steel float Old 0.12 litre/m² (8m²/litre)

Steel float New 0.08 litre/m² (12m²/litre)

PACKAGING

MasterTop 333 is packed in 5 and 20 litres containers.

SHELF LIFE

MasterTop 333 has a shelf life of 12 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the Master Builders Solutions Material Safety Data Sheet (MSDS) from our office or our website.

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication is based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by commonwealth or State legislation. The owner, his representative or the contractor is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided, does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions Hong Kong Limited
 Unit 2, 20/F, EW International Tower, 120-124 Texaco Road, Tsuen Wan, New Territories, Hong Kong.

Tel: (852) 2408 4400
 Fax: (852) 2408 4401