










MasterTop 1327-20dB

High sound deadening (-20 dB), elastic, satin matt, bacteriostatic, low emission (compliant with AgBB) polyurethane system

Fields of application: crack bridging, high noise deadening and sound absorbing indoor floor where high impact absorption is required: for example homes for elderly people, hospitals, offices, schools etc.

Consumption:		
	Primer	MasterTop P 617 EP, 2-component, non-solvented (total solid) 0,3-0,5 kg/m ²
	Optional / Scratch primer	MasterTop P 617 Filled 1 : 0,5 with oven dried silica sand, size 0,1-0,3 mm 0,6-1,0 kg/m ² *
	Elastic underlayment	MasterTop BC 329 massive, high elastic, pigmented, PU, 2 component, non-solvented 2,5-3,0 kg/m ²
	1. Body coat	MasterTop BC 375N pigmented, PU, 2 component, non-solvented 1,8-2,0 kg/m ²
	2. Body coat	MasterTop BC 325N or MasterTop BC 361N pigmented, PU, 2-component, non solvented 2,5-2,7 kg/m ²
	Top coat* <i>By light colours at least two applications are necessary</i>	MasterTop TC 417W (pigmented) pigmented, PU, 2-component, water borne, non-solvented, UV-stable bacteriostatic 0,10-0,12 kg/m ² per layer
		or MasterTop TC 417W (clear) (only with MasterTop BC 361N) 2-component, water borne, clear, PU, non-solvented, bacteriostatic 0,10-0,12 kg/m ² per layer
Total thickness of the system		ca. 6,0-7,0 mm



MasterTop 1327-20dB

High sound deadening (-20 dB), elastic, satin matt, bacteriostatic, low emission (compliant with AgBB) polyurethane system

Remark: Consumptions are indicative and may be higher, depending on substrate roughness, temperature and porosity, as well as waste produced during application.
* Total consumption includes sand

The flooring system fulfills, as minimum requirements, the following properties and technical data determined by internal and external testing:

EN 13813	SR-B1,5-AR1-IR4
Emissions behavior	AgBB conform AFFSET conform A+ classification
Bacteriostatic properties	According to ISO 22196:2011
Slip resistance	R9 with MasterTop TC 417W pigmented or clear R 10 with MasterTop TC 417W pigmented or clear + glassbeads
Impact sound reduction (ISO 717-2)	Delta L = 20 dB
Fire behavior according to (DIN EN 13501-1)	Cfl-s1



MasterTop 1327-20dB

High sound deadening (-20 dB), elastic, satin matt, bacteriostatic, low emission (compliant with AgBB) polyurethane system

CONTACT

Should you require any further information, please do not hesitate to contact your local sales consultant or take directly contact with us:

Master Builders Solutions Hong Kong Limited

Unit 2, 20/F, EW International Tower
120-124 Texaco Road, Tsuen Wan, N.T., Hong Kong

Tel: +852 2408 4400

Fax: +852 2408 4401

Mitglied der



Disclaimer:

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with Master Builders Solutions and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.