

MasterProtect® 200

Flexible, decorative waterproof & protective coating for external Concrete & Masonry surfaces

DESCRIPTION

MasterProtect 200 is a single component, flexible, elastomeric coating based on acrylic co-polymers. The coating enables long term protection of concrete & masonry from aggressive atmospheric gases such as, carbon dioxide, sulphur dioxide and chloride ions & prevents water ingress.

It is available in standard pastel colours. It can be made available in custom colours subject to prior agreement.

RECOMMENDED USES

MasterProtect 200 is recommended for external protection of concrete to prevent ingress of atmospheric corrosive gases, wind driven rain, and water borne chlorides.

Applications include protection of:

- RCC Frame structures with masonry infill
- Residential & Commercial Buildings
- Multi storey car parks & podiums
- Overhead water tanks.
- Industrial buildings and power plants.

MasterProtect 200 is not recommended for application in areas likely to be submerged in water and on floors subjected to traffic.

FEATURES AND BENEFITS

- Resists water ingress and permeable to water vapour – suitable for splashes and wind driven rain
- Resists dirt pick up, and growth of fungus suitable for the tropics
- Flexible capable to bridge cracks
- Good resistance to CO2 & SO2 diffusion suitable for urban environments.
- UV resistance suitable for external applications.
- Robust Washable coating with excellent durability

PERFORMANCE DATA

	1
Aspect	: Viscous Dispersion
Density	: 1.3 ± 0.1 kg/litre
Volume Solids	: 41%
Application temperature:	: 5°C to 50°C
DFT at 0.5 Kg/m²	: 150µ
Touch dry	:1 Hour at 25°C
Recoatable	: 4 Hours at 25°C
Full cure	:7 Days
Elongation, ASTM D 638	: >200%
Adhesive bond strength to concrete (ASTM D4541)	: > 1.0 MPa

APPLICATION

New masonry and concrete should be at least 14 days old before treatment and with moisture level in substrate below 7% by volume.

Surface preparation

Correct substrate preparation is critical for optimum performance. The surface to be treated must be thoroughly cleaned. Remove all traces of formwork, release agent, grease, efflorescence, laitance, algae, or other contaminant that may prevent proper adhesion. Remove organic materials by scraping, brushing or high pressure water cleaning. Spores must be treated with a suitable fungicide sterilizing agent and carefully rinsed.

On non-decorated concrete surface containing blow holes and/or minor irregularities, and on some rough rendered or dashed surface, it is advantageous to use **MasterEmaco N 5100** to close the surface, thus preventing the possibility of pinholes occurring. Cracks wider then, hairline should be patched using **MasterSeal 928** or sealed using acrylic caulk before treatment.

Priming

Prime the surface using **Masterseal 399** or **MasterKure 181** as primer.

Allow the primer to dry for 2-3hr (at temp. >25°C) before applying **MasterProtect 200**. At lower temperatures, allow a longer time to dry.

Note: If **MasterKure 181** is used as the curing membrane, priming may not be required. Contact Master Builders Solutions for advice.



MasterProtect[®] 200

Mixing

MasterProtect 200 is ready for use. Stir (do not dilute) to obtain a uniform mixture before use.

Application

Apply **MasterProtect 200** in one coat using airless spray to achieve a wet film thickness of 370μ or in two coats each of 185μ WFT using roller or brush, with the second coat applied 2-4 hours after the first and at right angle to it. The prepared substrate must be air-dry when the first coat is applied.

Where a textured finish is required use a medium nap roller to apply the product and over roll with a textured roller to give the desired finish in One direction only.

Only apply **MasterProtect 200** when the ambient temperature and substrate temperature are at least 5°C and will not fall below 5°C within 24 hours. To avoid condensation which influences the adhesion negatively, surface temperature during application should be at least 3°C higher than the dew point.

Curing

MasterProtect 200 is self-curing.

Equipment

Airless sprayer, medium nap roller or brush

ESTIMATING DATA

The coverage rate is strongly influenced by the roughness and porosity of the substrate.

Minimum recommended rate of application for **MasterProtect 200** is 0.25 Kg/m²/coat.

Each pack of 25kg is sufficient for an area of 50 m² to achieve the recommended final dry film thickness of 150μ .

PACKAGING

MasterProtect 200 is supplied in 25kg containers

SHELF LIFE

Store under cover, out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air-conditioned environment.

Shelf life is 12 months when stored as above.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the Master Builders Solutions Material Safety Data Sheet (MSDS) from our office or our website.

® = registered trademark of MBCC Group member in many countries of the world

MAP#MasterProtect 200 v2 12.2020

STATEMENT OF RESPONSIBILITY The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability, or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified, or rejected by the owner, engineer, or contractor since they, and not Master Builders Solutions are responsible for carrying out procedures appropriate to a specific application.

PT Master Builders Solutions Indonesia JI. Jababeka V Blok I/1 Cikarang Industrial Estate, Bekasi 17530,Indonesia Tel : +62 21 893 4339