

MasterSeal[®] 536

General purpose polymer cement waterproofing slurry

DESCRIPTION

MasterSeal 536 is a prepacked system, consisting of acrylic polymer as Part A and a premixed cementitious powder as Part B. The two parts on mixing yield a brushable, smooth slurry with excellent bond to most substrates.

RECOMMENDED USES

MasterSeal 536 is designed to be used as an effective waterproofing membrane on a variety of substrates. Applications include:

- waterproof coatings to the internal faces of sumps, planter boxes etc., before tiling or other surface finishing.
- treating terraces, balconies, kitchen and toilet floors as a sandwich treatment, to prevent water ingress.
- treating bridge and flyover decks before wearing course to protect concrete from rainwater ingress.

FEATURES AND BENEFITS

- **Cost effective/general purpose** - Need only minimum surface preparation; economical to apply
- **Permeable to water vapours** - Allows surface to breath, preventing buildup of vapour pressure
- **Flexible** - Can stand moderate movements of hair-line cracks
- **Brushable consistency** - Easy to apply by brush or spray

PERFORMANCE DATA

Pull off bond strength	>1.0 N/mm ²
Water Penetration Test (0.5kg/cm ²)	<1.0 mm

ESTIMATING DATA

The minimum recommended coverage of **MasterSeal 536** is 1.0 to 1.5 kg/m² to get 0.5 mm to 0.8 mm thick wet film build per coat. Actual coverage depends upon the method of application, the texture and porosity of the surface.

Therefore material requirement is approximately 2 kg/m² for 1 mm thick coating.

Note: mix only complete packs.

PROPERTIES

	Part A	Part B
Supply form:	Liquid	Powder
Colour :	White	Grey

Mixed material:	Grey Slurry
Working time @ 20°C: @ 30°C::	1 hour (approx.) 0.5 hour (approx.)
Application temperature:	>5°C

APPLICATION

Surface Preparation

Correct substrate preparation is critical for optimum performance. Surfaces should be structurally sound direct tensile strength of more than 1.5MPa via a pull off tester with a load rate of 100N/s), clean, and free from laitance, loose particles, oil and grease, old coatings, curing compounds or any other contaminants.

Cement laitance, loose particles, mould release agents, curing membranes, and other contaminants must be removed by wet grit blasting, high pressure water jetting (approx. 150 bars) or such other effective methods.

Prior to application use **MasterEmaco** repair mortars to achieve a smooth and level surface by filling holes and irregularities.

The prepared substrate should be saturated (saturated surface dry) with clean water before applying **MasterSeal 536**.

Mixing

Mechanical mixing is necessary. A slow speed (300 rpm), heavy duty electric drill with a wing type paddle is recommended. Place approx. 75% of Part A of the pack in a clean pail. Keeping the mixer running, add the Part B slowly. Mix for at least 3 minutes to get a lump-free homogenous mix. While continuing to mix, add all of the remainder of Part A if applying on a horizontal surface, or a part of it if applying on vertical surfaces till the required consistency is obtained.

Placing

It is extremely important that the area being treated is shaded from direct sun and wind to prevent rapid drying of the coating.

Apply **MasterSeal 536** evenly with a stiff brush or by spray, onto the prepared surface, to give a continuous film. The total film build up should be 1 to 2 mm on vertical & overhead surfaces and 1 to 3 mm in case of horizontal surfaces, which should be built up in at least two coats, subsequent coat applied after previous coat has dried.

To avoid pin holes, apply the second brush coat at right angles to the direction of first coat.

In hot climates, it may be necessary to retard the setting time of MasterSeal 536 to minimise the risk of frequent choking of the spray nozzle. Consult Master Builders

MasterSeal[®] 536

General purpose polymer cement waterproofing slurry

Solutions Construction Chemicals Representatives for advice.

CURING

Slow drying of **MasterSeal 536** membrane ensures homogenous curing and high waterproofing characteristics.

MasterSeal 536 must be protected against rapid drying due to high temperatures or wind. Curing by wet burlap, polyethylene sheet or a curing compound such as **MasterKure 181** is recommended.

CLEANING

Clean tools using water and rags before the resin system hardens. Hardened material can only be removed mechanically.

PACKAGING

MasterSeal 536 is available in 25 kg packs.

Part A: 5.60 kg plastic pail

Part B: 19.40 kg paper bag

SHELF LIFE

MasterSeal 536 can be kept for 12 months in original unopened packing when stored indoors. Do not store in direct sunlight and avoid allowing the material to freeze which will render the material unusable.

PRECAUTIONS

For detailed Environmental, Health and Safety information, please consult and follow all instructions on the product Material Safety Data Sheet. Contact your local Master Builders Solutions office for the latest version.

® = registered trademark of a MBCC Group member in many countries of the world

MID#MasterSeal[®] 536 - 04.2021

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

PT Master Builders Solutions Indonesia

Jl. Jababeka V Blok I No 1, Kawasan Industrial Estate

Jababeka 1, Pasirgombong, West Cikarang,

Bekasi, West Java 17530

www.master-builders-solutions.com/en-id