

MasterFlow[®] 920 ANS

Epoxy acrylate (styrene-free) resin based high performance anchoring grout

DESCRIPTION

MasterFlow 920 ANS is a two-component epoxy acrylate resin based high performance anchoring grout for use in cracked and uncracked concrete under normal as well as seismic conditions (seismic category C1). It is a styrene-free system with very low voc content. **MasterFlow 920 ANS** has extended gel and cure time for tropical temperatures.

USES / APPLICATION

- Structural applications in cracked and uncracked concrete applications in seismic zones (C1)
- Reinforcing & starter bars
- Suspended ventilation systems
- Safety barriers
- Machinery & heavy machinery
- Racking
- Rolling cranes

APPROVALS & TESTS

- ETA according ETAG 001 Part 1 and Part 5 Option 1 for anchoring of threaded bars into cracked and uncracked concrete application in seismic zones (C1)
- ETA according to TR023 for post-installed rebar connections
- Tested according to LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)
- A+ as per French VOC Regulation
- WRAS – Suitable for use with potable water

FEATURES AND BENEFITS

- Anchors may be placed close to free edges
- Suitable for dry, wet & flooded holes
- Reduced drilling diameters i.e. M20 only requires a 22mm hole and M24 requires only a 26mm hole making it an economical injection system
- Variable embedment depths
- Ratio of 10:1

PACKAGING


MasterFlow 920 ANS is available in boxes of 12 co-axial cartridges of 380ml.

ACCESSORIES

- Application guns
- Mixing nozzles
- Cleaning blow pump
- Cleaning brushes
- Extension tubes
- Plastic sleeves

INSTALLATION PROCEDURE

Please refer to the method statement or contact Master Builders Solutions Technical Services department.



MasterFlow® 920 ANS

WORKING & LOADING TIMES

TECHNICAL DATA

Resin cartridge Temperature	T Work	Base Material Temperature	T Load
+15 to +20°C	15 mins	+15 to +20°C	5 hours
+20 to +25°C	10 mins	+20 to +25°C	145 minutes
+25 to +30°C	7.5 mins	+25 to +30°C	85 minutes
+30 to +35°C	5 mins	+30 to +35°C	50 minutes
+35 to +40°C	3.5 mins	+35 to +40°C	40 minutes

Note: T Work is the typical time to gel at the highest temperature in the range. T load is set at the lowest temperature in the range

PHYSICAL PROPERTIES

Property		Value	Test Standard
Compressive Strength	24 hours	72.3N/mm ²	ASTM D695 @ +20°C
	7 days	77.8N/mm ²	
Compressive Modulus Strength	24 hours	5GN/m ²	ASTM D695 @ +20°C
	7 days	7GN/m ²	
Tensile Strength	24 hours	13.5N/mm ²	ASTM D638 @ +20°C
	7 days	15.2N/mm ²	
Tensile Strength Elongation at Break	24 hours	6%	ASTM D638 @ +20°C
	7 days	6.7%	
Tensile Modulus	24 hours	3.75GN/m ²	ASTM D638 @ +20°C
	7 days	3.8GN/m ²	
Flexural Strength	24 hours	29.3N/mm ²	ASTM D790 @ +20°C
	7 days	38.7N/mm ²	

THEORETICAL NUMBER OF FIXINGS PER CARTRIDGE


Applies to installations in solid substrates only

Cartridge Volume	h _{ef}	Ø8	Ø10	Ø12	Ø16	Ø20	Ø25	Ø32
		Drilling Ø 12mm	Drilling Ø 14mm	Drilling Ø 16mm	Drilling Ø 20mm	Drilling Ø 25mm	Drilling Ø 32mm	Drilling Ø 40mm
380ml	10d	69	45	32	19	9	4	2
	12d	57	38	27	16	8	3	2
	20d	34	22	16	9	5	2	1

Note: Jobsite/contractor installations usually result in more resin being injected than the theoretical requirement resulting in lower number of fixings per cartridge. The reduction to the number of fixings per cartridge in practice is greater for smaller diameter holes and shallower embedment depths.

MasterFlow[®] 920 ANS

INSTALLATION PARAMETERS



MasterFlow 920 ANS with REINFORCING BARS (ANCHOR THEORY)

Diameter of rebar (mm)	10	12	16	20	25	32
Drilled hole diameter (mm)	14	16	20	25	32	40

DESIGN RESISTANCE

Rebar size	Ø10	Ø12	Ø16	Ø20	Ø25	Ø32
Effective embedment depth h_{ef} [mm]	90	110	125	170	250	300
non-cracked concrete temperature range (-40°C / +40°C)						
tension C20/25 $N_{Rd,p}$ [kN]	18.85	23.04	34.91	53.41	98.17	92.15
shear C20/25 $N_{Rd,s}$ [kN]	9.33	14.67	20.67	57.33	90.00	147.33

RECOMMENDED RESISTANCE

Rebar size	Ø10	Ø12	Ø16	Ø20	Ø25	Ø32
Effective embedment depth h_{ef} [mm]	90	110	125	170	250	300
non-cracked concrete temperature range (-40°C / +40°C)						
tension C20/25 $N_{Rd,p}$ [kN]	13.46	16.46	24.93	38.15	70.12	65.82
shear C20/25 $N_{Rd,s}$ [kN]	6.67	10.48	14.76	40.95	64.29	105.24

$f_{yk} = 500 \text{ N/mm}^2$


Partial safety factor $\gamma_{1.4}$

For resistance values in higher temperatures, please contact Master Builders Solutions Technical Services.

All the above resistance values are considering combined pull out and concrete cone failure in tension and steel failure in shear.

MasterFlow[®] 920 ANS

MasterFlow 920 ANS with REINFORCING BARS (REBAR THEORY)



INSTALLATION PARAMETERS

Diameter of rebar	8	10	12	16	20	25	32
Drilled hole diameter	12	14	16	20	25	32	40

DESIGN RESISTANCE

Rebar size	Ø8	Ø10	Ø12	Ø16	Ø20	Ø25	Ø32
Effective embedment depth h_{ef} [mm]	110	140	170	230	280	350	680
cracked concrete (static cracks) temperature range (-40°C / +40°C)							
tension C20/25 $N_{Rec,p}$ [kN]	9.4	14.7	21.2	37.5	58.6	91.6	224.9

RECOMMENDED RESISTANCE

Rebar size	Ø8	Ø10	Ø12	Ø16	Ø20	Ø25	Ø32
Effective embedment depth h_{ef} [mm]	110	140	170	230	280	350	680
cracked concrete (static cracks) temperature range (-40°C / +40°C)							
tension C20/25 $N_{Rd,p}$ [kN]	6.6	10.3	14.8	26.2	41.0	64.1	160.64

$f_{yk} = 500 \text{ N/mm}^2$

For resistance values in higher temperatures, please contact Master Builders Solutions Technical Services.

All the above tension loads are valid for good bond conditions according to EN 1991-1-1. For all other conditions multiply the value by 0.7

All the above resistance values are considering combined pull out and concrete cone failure in tension and steel failure in s

MasterFlow[®] 920 ANS

CLEANING OF TOOLS

Residual material must be mechanically removed after hardening, or by brush and with plenty of soapy water or solvent when still uncured.

STORAGE & SHELF LIFE

Cartridges should be stored in their original packaging, the correct way up, in cool conditions (+5°C to +25°C) out of direct sunlight.

When stored correctly, the product shelf life will be 12 months from the date of manufacture.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local Master Builders Solutions representative.

Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

* Properties listed are based on laboratory controlled tests.

MFlow920ANS/01/03/2020

® = registered trademark of a MBCC Group member in many countries of the world

STATEMENT OF RESPONSIBILITY (Disclaimer)

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions India Private Limited
Registered office: Plot No D-126,
TTC Industrial Area, MIDC,
Shiravane, Navi Mumbai - 400706,
Maharashtra, India
Tel: +91 8657906776
E-mail: Construction-india@mbcc-group.com
www.master-builders-solutions.com/en-in

