

MasterSeal TC 640

Aliphatic single component polyurethane topcoat for MasterSeal 2163 system

DESCRIPTION

MasterSeal TC 640 is a single component, polyurethane based, solvent containing topcoat for UV protection of polyurethane membranes.

FIELDS OF APPLICATION

UV protection of MasterSeal M 635 membrane in exposed applications.

FEATURES AND BENEFITS

- Single component product that allows simple application without the need of mixture.
- Excellent adhesion.
- UV resistant. Colour stability.
- Fast Curing.
- Resistant to standing water.
- Frost resistant.
- Withstands pedestrian traffic

APPLICATION METHOD

(a) Surface Preparation

MasterSeal M 635 to which MasterSeal TC 640 is to be applied should be clean and dry and free of any substances which may impair adhesion. Application should take place within the re-coat intervals of the coating to which is to be applied.

(b) Mixing

MasterSeal TC 640 is a single component material. Prior to application, the temperature of the material should be in the range of 15–25 °C. Some settling of the pigments may occur on standing. MasterSeal TC 640 should, therefore, be well stirred before use with a mechanical drill and paddle at a very low speed (approx. 300 rpm).

(c) Application

MasterSeal TC 640 is applied normally in two coats. Apply homogeneously covering the substrate using a brush, a short hair roller or an air-less spray gun.

Temperature of the support should be minimum +5 °C and maximum +35 °C. The residual moisture content of the substrate must not exceed 4% (check with e.g. CM device). The temperature of the substrate must be at least

3 K above the current dew point temperature. Try to keep the temperature uniform during application and hardening. After maximum 6 hours apply the second coat. MasterSeal TC 640 can be broadcasted with dry silica sand to provide a hard wearing, slip resistant finish.

The product must not be applied when the temperature is below +5 °C or above 35 °C. Do not mix solvents, sand or other products that could affect the products properties must not be added. High humidity during hardening can affect final appearance, specially gloss.

COVERAGE

Approx. 150 to 200 g/ m² are required per coat.

These consumptions are theoretical and can vary according to application consumptions. It is essential to carry out representative trials on site to evaluate the exact consumption.

FINISHING AND CLEANING

While still wet with solvent (e.g. Cleaner 40 or solvent naphtha). Once cured it can only be removed mechanically.

PACKAGING

MasterSeal TC 640 is available in 20 kg and 5 kg pails.

COLOUR

Colours: white, grey, red

STORAGE / SHELF LIFE

Store in original containers under dry conditions at a temperature between 15 – 25 °C. Do not expose to direct sunlight. For maximum shelf life under these conditions see "Best before....." label.

WATCH POINTS

This product conforms to the EU directive 2004/42/EG (Deco-Paint directive) and contains less than the maximum allowable VOC limit (Stage 2, 2010).

MasterSeal TC 640

According to the EU directive 2004/42, the maximum allowable VOC content for the Product Category IIA / j is 500 g/l (Limit: Stage 2, 2010). The VOC content for MasterSeal TC 640 is < 500 g/l (for the ready to use product).

HANDLING / PRECAUTIONS

In its cured state, MasterSeal TC 640 is physiologically non-hazardous. The following protective measures should be taken when working with this material:

Wear safety gloves, goggles and protective clothing. Avoid contact with the skin and eyes. In case of eye contact, seek medical attention. Avoid inhalation of fumes. When working with the product, do not eat, smoke or work near a naked flame. For additional references to safety hazard warnings, regulations regarding transport and waste management, please refer to the relevant Material Safety Data Sheet. The regulations of the local trade association and/or other authorities regarding safety and hygiene of workers handling polyurethanes and isocyanates must be observed.

MasterSeal TC 640

Technical data*			
Properties	Standard	Data	Unit
Chemical base	-	Polyurethane	-
Mixing ratio	A : B	single component	-
Density at 20 °C	-	1.13	g/cm ³
Solids content at 20 °C	-	55	%
Tack free / Rain safe at 20 °C	-	2	h
Re-coating interval at 20 °C	-	4 - 6	h
Open to pedestrian traffic at 20 °C	-	12	h
Fully cured at 20 °C	-	7	d
Substrate and ambient temperatures	-	min. 8	°C
		max. 35	°C
Permissible relative humidity	-	max. 85	%

Technical data after curing*

Properties	Standard	Data	Unit
Service temperatures	-	min. - 20	°C
		max. 80	°C
Tensile strength	DIN EN ISO 527	3.5	N/mm ²
Elongation	DIN EN ISO 527	> 300	%
Solar reflection SR (white colour)	ASTME903-96	93.5	%

* The above figures are intended as a guide only and should not be used as a basis for specifications.

MSealTC640/01/0417

MasterSeal TC 640

® = registered trademark of a MBCC Group member in many countries of the world

**STATEMENT OF
RESPONSIBILITY
(Disclaimer)**

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions India Private Limited
Registered office: Plot No D-126,
TTC Industrial Area, MIDC,
Shiravane, Navi Mumbai - 400706,
Maharashtra, India
Tel: +91 8657906776
E-mail: Construction-india@mbcc-group.com
www.master-builders-solutions.com/en-in

