

MasterEmaco[®] S 650

Fast setting high strength thixotropic roadway patching mortar

DESCRIPTION

MasterEmaco S 650 trowelable mortar is a thixotropic high strength formulation for repairs to trafficked concrete.

MasterEmaco S 650 is suitable for placing in thicknesses of 10 mm to 50 mm horizontally.

MasterEmaco S 650 provides a durable, strong repair fully compatible with host concrete.

RECOMMENDED USES

MasterEmaco S 650 is the ideal material for horizontal repairs where the thickness of repair is more than 10 mm and the patch will be subject to traffic loads. Typical applications are:

- Repairs to bridge decks, concrete road, airport runways or aprons.
- Repair of warehouse floors where rapid return to service is required.

FEATURES AND BENEFITS

- **Shrinkage compensated** - Reduced cracking tendency
- **One component, factory made only addition of water** - Uniform predictable performance even in remote situations
- **No bonding agent required** - Simple installation
- **Impermeable to aggressive elements** - Long life repairs
- **Rapid setting** - Able to return to service in 2-3 hours
- **Fast and easy placing** - No formwork required thus reducing time for repairs

PROPERTIES

Appearance	Grey powder
Water powder ratio	0.11
Compressive strength (ASTM C109)	15 MPa 3 hours
	25 MPa 1 Day
	50MPa 28 Days
Working life	20 minutes @ 25°C

	10 minutes @ 40°C
Final setting time	120 minutes @ 25°C
Density	Approx. 1900 kg/m ³
Mixing water per 25kg bag	Approx. 2.75litres
Temperature for application (substrate and material)	Between +10 and +40°C (+5 and +30°C)

APPLICATION

Surface preparation

Concrete must be fully cured with a minimum direct tensile strength of 1.5 MPa. All loose traces of concrete or mortar, dust, grease oil, etc. must be removed. Damaged or contaminated concrete shall be removed to obtain a keyed aggregate exposed surface. Non-impact/ vibrating cleaning methods, e.g. grit or high pressure water blasting are recommended to achieve CSP 5-8. Cut the edges of the repair vertically to a minimum depth of 10 mm. Clean all exposed reinforcement to a minimum grade of SA 2 according to ISO 8501-1 / ISO 2944-4. Ensure back of rebar is also clean.

Where reinforcing bars are corroded, cut back the concrete to at least 20mm behind the reinforcing bars. Grit blast around the reinforcing bars to remove corrosion products. Replace and coat the affected part of reinforcing bar with **MasterEmaco P 130** for protection against corrosion. If the diameter after grit blasting is found reduced by more than 20% of the original diameter on the advice of the structural engineer responsible for the works.

Mixing

Only full bags are mixed. Damaged or opened bags should not be used. Mix one full bag at one time. Place approximately 80% of the water in the mixer/clean container. Keeping the mixer/drill running add **MasterEmaco S 650** slowly. Add remaining water while continuing to mix. Mix for

MasterEmaco[®] S 650

3–4 minutes or until a lump free homogeneous consistency is achieved.

Mix **MasterEmaco S 650** in a forced action pan mixer, or with a helical paddle attached to a low speed (300-600rpm) mixer for 3 minutes until a lump free, thixotropic consistency is achieved. Only use clean water. Mixing water needed: 2.75litres per 25kg bag. Allow the mortar to rest for 2-3 minutes and then remix briefly before applying. If the temperature is above 25⁰C use chilled water as the mixing water.

Priming Concrete

No special primer is required. For extra adhesion you may use epoxy bond coat of MasterBrace 1414.

Mortar application

The prepared substrate should be pre-soaked, preferably for 2 hours before applying **MasterEmaco S 650**. The surface must be saturated surface dry, but without standing water. Apply the mixed **MasterEmaco S 650** directly to the prepared damp substrate, or wet on wet onto the primed surface. A thin scrape coat or contact layer before building up to the required thickness, wet on wet, will improve adhesion especially in case of hand application. MasterEmaco S 650 loses initial flowable consistency due to fast setting nature, hence its recommended to place & tool material quickly in repair patch/pocket. Apply to the desired layer thickness of 10 mm to max 50 mm and level using a screeding bar, trowel or wooden board.

Patch repair size should be limited to max. 0.04-0.05cum in a single stage of application due to its fast-setting property and thixotropic consistency, depending on the ambient temperature.

Smoothing with a trowel or finishing by float or sponge can be done as soon as the mortar has begun to stiffen.

CURING

MasterEmaco S 650 should be cured with a water mist or wet hessian for minimum 7 days and continue as long as possible.

Begin the curing process immediately after the initial set (say 1 hour of placing depending on drying conditions)

Do not use any curing compounds/ agents.

ESTIMATING DATA

Each bag of **MasterEmaco S 650** when mixed with 2.75L of water yields 14.6L.

PACKAGING

MasterEmaco S 650 is available in 25kg bags.

SHELF LIFE

MasterEmaco S 650 has a shelf life of 6 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall.

PRECAUTIONS

Do not exceed the recommended water/powder ratio. It may result in excessive shrinkage crack formations.

Do not pour more than the recommended volume of material in single stage application to avoid early setting of the material.

Do not mix more than 1 bag of material for mixing.

Please adhere to the working time of the material depending on the ambient temperature while finishing the material.

It is highly recommended to use necessary PPE (Gloves, mask etc.,) during installation of the product. In case of Incidents of direct inhalation, causing dizziness/giddiness, loss of consciousness, contact with eyes etc, seek immediate medical advice. The requirements may vary depending on the application areas. Please ensure to have proper ventilation while working in confined areas. Contact Master Builders Solutions representative in case you need further details or refer to the material safety datasheet of the product to know more.

TDS Ref No: MasterEmaco S 650/02/09/2022

MasterEmaco[®] S 650

® = registered trademark of a MBCC Group member in many countries of the world

**STATEMENT OF
RESPONSIBILITY
(Disclaimer)**

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions India Private Limited
Registered office: Plot No D-126,
TTC Industrial Area, MIDC,
Shiravane, Navi Mumbai - 400706,
Maharashtra, India
Tel: +91 8657906776
E-mail: Construction-india@mbcc-group.com
www.master-builders-solutions.com/en-in

