

MasterEmaco[®] S 488PM

Polymer modified, shrinkage compensated, fiber reinforced, thixotropic repair mortar

DESCRIPTION

MasterEmaco S 488PM, is a polymer modified cementitious pre-bagged ready-to-use structural repair mortar in powder form. When mixed with the correct amount of water, it produces a thixotropic, high strength repair mortar, reinforced with acrylic fibres. It possesses excellent bond characteristics to steel reinforcement and to concrete.

MasterEmaco S 488PM mortar is shrinkage compensated. It has low permeability and is extremely durable. **MasterEmaco S 488PM** contains no metallic aggregate and is chloride free.

MasterEmaco S 488PM is formulated for sprayed or trowelled applications, in thicknesses up to 50mm in one layer by hand application.

TYPICAL APPLICATIONS

- All types of structural repair which can be applied by trowel or wet spray.
- Repair of structural members subjected to repetitive loading.
- Repairs to reinforced or pre-stressed beams or columns.
- Protection of concrete subject to attack from water containing chlorides and sulphates etc.
- Repairs in industrial areas, especially those containing mineral oils, lubricants.
- Repairs in marine environments.

ADVANTAGES

- Shrinkage compensation - reduces the risk of cracking due to shrinkage and ensures full contact with host concrete and load transfer in structural repair situations
- No primer required - allows rapid application at reduced cost
- Can be spray applied - rapid application of large quantities
- Low rebound - when spray applied rebound is minimal, with subsequent saving in material cost
- Extremely low permeability - gives excellent resistance to attack by aggressive elements

PACKAGING

MasterEmaco S 488PM is available in 25kg bags.

TYPICAL PROPERTIES @ 4 L OF WATER / BAG

Appearance	grey powder containing micro fine fibres
Wet density	Approx. 2195 kg/m ³
Compressive strength BS 1881: Part 116	>25 N/mm ² @ 1 day >70 N/mm ² @ 28 days
Tensile strength @ 25°C ASTM C307	>4.5 N/mm ² @ 28 days
Water penetration BS EN 12390 Part 8 : 2000	5 mm
Flexural strength @ 25°C BS EN 12390 Part 3	>10 N/mm ² @ 28 days
Chloride migration co-efficient NT Build 492	<1 x 10 ⁻¹² m ² / s
Rapid chloride permeability ASTM C1202 : 2012	<1000 coulombs
Pull off strength BS EN 1542	>2 N/mm ²

APPLICATION GUIDELINES

PREPARATION OF SUBSTRATE

It is essential that the substrate to be repaired is sound, clean and free of all contamination.

The damaged areas of concrete to be removed should be clearly identified. The perimeter of the area should be saw cut to a depth of 10mm and the edges cut as neatly as possible keeping the sides square. Feather-edging is not permitted and a minimum thickness of 10mm must be maintained over the whole repair area.

The substrate should be prepared to provide a rough surface having at least a 5mm amplitude at 20mm frequency.

MasterEmaco® S 488PM

If unsound or contaminated concrete is found to extend beyond the premarked area, consult the engineer in charge. Subject to his approval cut out as necessary back to clean sound concrete.

If reinforcement is corroded ensure that the back of the steel has been exposed. Reinforcement should have all rust removed by the use of power tools, abrasive blasting (wet or dry) or wire brushing. Reinforcing steel should be exposed and cleaned around its whole circumference. Steel should be prepared to Swedish Standard SIS 05-900:1967-SA 2½ or BS 4232 Ref. 24 second quality.

Extra protection to the reinforcement can be provided by use of **MasterEmaco 8100 AP** dependent upon the circumstances of use and requirement of the client.

Severely corroded reinforcement may require replacement and the engineer must be consulted.

WATER SATURATION

Thoroughly saturate the surface of the concrete to provide a saturated surface dry condition. Poor quality concrete may require soaking for a significant length of time. Any surface water should be removed using an oil free compressed airjet.

MIXING

MasterEmaco S 488PM must be mixed mechanically. The following mixing equipment is suitable, heavy duty slow speed drill with spiral mixing paddle, forced action mixer.

Add 3.5 L of water into the mixer. Start the mixer and add the **MasterEmaco S 488PM** powder rapidly and continuously. Mix for 3-5 minutes after all the powder has been added until mortar is homogeneous and lump free.

Add water, if necessary, within the limits given (max 4 L / bag), until the required consistency is achieved. Mix for a further 1-2 minutes. The amount of water required will be affected by ambient temperature and relative humidity.

MasterEmaco S 488PM can be used when the ambient temperature is between 5-50°C. If ambient temperature is >30°C, use chilled water to ensure that the maximum mixed temperature should be no more than 35°C.

PLACING / APPLICATION

After mixing, **MasterEmaco S 488PM** can be sprayed or trowel applied.

When applying by hand **MasterEmaco S 488PM** must be forced tightly into the substrate to ensure intimate contact with the pre-wetted substrate.

Levelling and initial finishing should be carried using a wooden or plastic float.

Final finishing should be carried out using a steel float.

When the material has stiffened to the point where finger pressure lightly marks the surface, a final firm trowelling should be given using the steel float.

CURING

Good curing is essential. Particular care is required in hot and/or windy conditions. Curing can either be with a single coat of **MasterKure 181** curing membrane, which is compatible with most subsequent protective coatings, or by covering the work with plastic sheet fixed over wet hessian or wet foam rubber.

MasterEmaco® S 488PM

COVERAGE / YIELD

One 25kg bag of **MasterEmaco S 488PM** with 4 L of added water will yield approximately 12.6 L of mortar which will cover 1 m² at 12.6mm average thickness.

Note: In addition to shrinkage compensation, this product has been designed to develop tensile strength sufficient to withstand the internal stress generated by volume change to reduce the incidence of drying shrinkage cracking.

STORAGE AND SHELF LIFE

Store out of direct sunlight, clear of the ground on pallets, protect from rainfall. Avoid excessive compaction. Shelf life is 12 months when stored as above

HEALTH AND SAFETY

As with other products containing Portland cement, the cementitious material in **MasterEmaco S 488PM** grout may cause irritation. In case of contact with eyes, immediately flush with plenty of water for at least 15 minutes. Call a physician. In case of contact with skin, wash skin thoroughly.

QUALITY AND CARE

All products originating from Master Builders Solutions Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001 and ISO 14001.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

MBS_CC-UAE/Em_S488PM_04_16/v3/07_17/v4/09_19

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
Construction Chemicals LLC
P.O. Box 37127, Dubai, UAE
Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae



A brand of
MBCC GROUP

Disclaimer: the TUV mark relates to certified management system and not to the product mentioned on this datasheet