

MasterFlow[®] 544

High strength, non-shrink cementitious mortar

DESCRIPTION

MasterFlow 544 is a ready to use product in powder form, which requires only the on-site addition of water to produce a non-shrink mortar of predictable performance.

TYPICAL APPLICATIONS

MasterFlow 544 is formulated for use at plastic consistency, and may be used with confidence for bedding, repairing, grouting and void filling operations such as:

- Concrete repairs
- Void filling between old and new concrete
- Floor patching
- Packing under columns and stanchions
- Caulking of concrete pipes
- Filling tie-bar holes
- Re profiling of stanchion or mast bases when formwork is undesirable
- Pile cap reprofiling and encapsulation

ADVANTAGES

- Non shrink
- Adjustable consistency
- Proven and predictable performance
- Trowellable
- High bond strength to steel and concrete
- Early strength development even at pourable consistency
- Good fatigue and impact resistance
- Impermeable

PACKAGING

MasterFlow 544 is supplied in 25 kg bags.

TYPICAL PROPERTIES*

When mixed with 3.9 L of water a 25 kg bag will have the following properties:		
Compressive Strength BS EN 12390-3	24 h 28 days	>25 N/mm ² >65 N/mm ²
Tensile Strength BS 6319 - Part 7	28 days	>4.0 N/mm ²
Flexural Strength BS EN 1015-11	24 h 28 days	>4.0 N/mm ² >8.0 N/mm ²

APPLICATION GUIDELINES

SURFACE PREPARATION

All surfaces in contact with the material must be sound, dense and clean. All laitance and any unsound material should be removed - an evenly scabbled, slightly textured surface is required, with all dust and dirt removed. (Note: heavy scabbling, creating deep troughs or high peaks is unsuitable). Surfaces must be pre-wetted to thoroughly dampen the concrete, but any free surface water must be removed before **MasterFlow 544** is placed.

For large areas of application, such as floor toppings or concrete repair, **MasterBrace ADH 1414** epoxy bonding agent should be used on the interface to ensure total bond.

Feather edging is not recommended. Minimum acceptable depth is 10 mm. Maximum recommended depth for toppings is 50 mm.

MIXING

First dry mix contents of bag, then thoroughly mix with the specified amount of water.

Plastic consistency:

Add 3.9 L of water to one 25 kg bag and mix thoroughly.

Pourable consistency:

Add 4.4 L of water to one 25 kg bag and mix thoroughly.

MasterFlow[®] 544

Notes:

1. To achieve the properties described, water additions should be accurate to ± 0.1 L.
2. Water should be slowly added over a 1½ minute period and then mixing continued for a further 2 minutes.
3. It is important that a forced action mixer is used to ensure complete dispersion of the water and thorough mixing thereafter.

PLACING / APPLICATION

All of the mix should be placed within 45 minutes of water addition. No water should be added for retempering.

Placing must not take place below 5°C. Below 8°C it is advisable to tent before placing, to warm the substrate to 8°C minimum, and subsequently to maintain the placed mortar at 8°C minimum.

For plastic consistencies tamping is essential to achieve good compaction. Do not vibrate.

CURING

Curing of the exposed surfaces of **MasterFlow 544** must commence immediately. Following placement, the exposed surfaces must be continuously cured at moderate temperatures for seven days after finishing operations. This will prevent early drying shrinkage and help to develop strength, durability and other desired properties. Any deficiencies in the method of curing may also reduce the amount of initial expansion which is needed to offset later drying shrinkage. The use of **Master Kure** curing compounds is strongly recommended.

GROUTING A SPACE USING PLASTIC MORTAR

Formwork is erected on 3 sides (and is prepared for the fourth). Plastic mortar is rammed into place, filling all voids. Without delay, a vertical or sloping form is fixed on the fourth side, the grout is surcharged and is consolidated by thorough hand punning (i.e., caulking by ramming). Just before final set, the surplus grout is removed.

COVERAGE / YIELD

12.9-13.4 L / 25 kg bag dependent on water addition rate.

78 x 25 kg bags/m³

STORAGE AND SHELF LIFE

Store out of direct sunlight, clear of the ground on pallets protected from rainfall. Avoid excessive compaction.

The shelf life is 12 months when stored as above in original sealed bags.

HEALTH AND SAFETY

The temperature of both the grout and elements coming into contact with the grout should be in the range of +5°C to +35°C. Do not use water in an amount or at a temperature that will produce a consistency more than fluid or cause mixed grout to bleed or segregate. **DO NOT OVERWORK AND AVOID USING MECHANICAL VIBRATION. UNDER NO CIRCUMSTANCES SHOULD MasterFlow 544 BE RETEMPERED BY THE LATER ADDITION OF WATER.** It is essential that a mechanically powered grout mixer is used to obtain the optimum properties.

WARNING

As with other products containing Portland cement, the cementitious material in **MasterFlow 544** mortar may cause irritation. Avoid contact with eyes and prolonged exposure. In case of contact with the eyes, immediately flush with plenty of water for at least 15 minutes. Call a physician. In case of contact with skin, wash skin thoroughly.

MasterFlow[®] 544

NOTE

For free-flowing grouting operations consider the use of **MasterFlow 524**. Precision grouting of heavy machinery use **MasterFlow 928** or **MasterFlow 980**.

When a very rapid set is required in areas subject to chemical spillage or contamination, use epoxy grouts **MasterFlow 400 / MasterFlow 648**.

For additional information on **MasterFlow 544** mortar or other non-shrink grouting and repair materials, contact your Master Builders Solutions representative.

QUALITY AND CARE

All products originating from Master Builders Solutions Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001 and ISO 14001.

Request and refer to recommended installation procedures for **MasterFlow** grouts prior to use

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

MBS_CC-UAE/FI_544_03_94/v2/03_15/v3/12_19

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
Construction Chemicals LLC
P.O. Box 37127, Dubai, UAE
Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae

Disclaimer: the TUV mark relates to certified management system and not to the product mentioned on this datasheet



A brand of
MBCC GROUP