

# MasterGlenium<sup>®</sup> 195

**Polycarboxylic ether based superplasticizer for the production of high quality ready-mix concrete with exceptional workability retention.**

## DESCRIPTION

**MasterGlenium 195** is an innovative latest generation superplasticizer based on polycarboxylic ether (PCE) polymers, and is specially engineered for ready-mix concrete.

**MasterGlenium 195** is differentiated from conventional superplasticisers, such as those based on sulphonated naphthalene formaldehyde condensate in that it is based on a unique carboxylic ether polymer with long lateral chains. This greatly improves cement dispersion. At the start of the mixing process the same electrostatic dispersion occurs but the presence of the lateral chains, linked to the polymer backbone, generate a steric hindrance which stabilises the cement particles capacity to separate and disperse. This mechanism provides flowable concrete with greatly reduced water demand.

## TYPICAL APPLICATIONS

**MasterGlenium 195** is used for the production of high quality ready-mix concrete.

## ADVANTAGES

The ready-mix producer:

- Capability of delivering high performance concrete at any time to the job site in place
- Production of a concrete with low water cement ratios with excellent workability retention properties.
- Single product for many application needs

The contractor / applicator:

- Easier placing and faster strength development
- Improved concrete surfaces

The engineer:

- Insurance that concrete meets original specification
- High quality durable concrete

## PACKAGING

**MasterGlenium 195** is supplied in 210 L drums, 1,000 L containers or in bulk.

## STANDARDS

ASTM C-494 Type F&G  
 BS EN 934-2

## TYPICAL PROPERTIES\*

Appearance	Medium to dark brown coloured liquid
Specific gravity @ 25°C	1.108
pH value	4 – 7
Chloride content	"chloride-free" to EN 934

## APPLICATION GUIDELINES

The normally recommended dosage rate of **MasterGlenium 195** is 0.5 to 2.0 kg per 100kg of total cementitious material.

Other dosages may be recommended in special cases according to the specific site conditions. In this case please consult our Technical Services Department for advice.

## MIXING

**MasterGlenium 195** is a ready-to-use admixture to be added to the concrete as a separate component. Optimal result is obtained if **MasterGlenium 195** is poured into the concrete mix right after the addition of the first 80% of the mixing water, i.e. when all solids are wetted. Avoid adding the admixture to the dry aggregates.

**MasterGlenium 195** is suitable for mixes containing:

- Microsilica (Silica Fume)
- Fly Ash (PFA)
- GGBS (ground granulated blast furnace slag)

Note: **MasterGlenium 195** is not compatible with **MasterRheobuild** superplasticizers.

# MasterGlenium<sup>®</sup> 195

## STORAGE AND SHELF LIFE

**MasterGlenium 195** should be stored in unopened containers or bulk tanks so as to protect from extremes of temperature. The shelf life is 12 months when stored as above

The occurrence of a surface layer with **MasterGlenium 195** is normal and will have no effect on the performance of the product.

## HANDLING AND TRANSPORTATION

No special requirements must be observed during use. Protection gloves and glasses are however recommended. **MasterGlenium 195** is non-flammable, non-toxic or irritant and is not subject to special transport requirements.

## HEALTH AND SAFETY

**MasterGlenium 195** contains no hazardous substances requiring labelling. For further information refer to the Material Safety Data Sheet.

## QUALITY AND CARE

All products originating from Master Builders Solutions Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001 and ISO 14001.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

MBS\_CC-UAE/GI\_195\_06\_13/v2/11\_15/v3/08\_18/v4/05/19

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions  
Construction Chemicals LLC  
P.O. Box 37127, Dubai, UAE  
Tel: +971 4 8090800  
[www.master-builders-solutions.com/en-ae](http://www.master-builders-solutions.com/en-ae)

**Disclaimer:** the TÜV mark relates to certified management system and not to the product mentioned on this datasheet



A brand of  
**MBCC GROUP**