

# MasterPolyheed® 3536

Next generation superplasticizer for the production of high-quality ready-mix concrete with low water cement ratio and enhanced rheology

#### **DESCRIPTION**

**MasterPolyheed 3536** is part of a range of latest generation superplasticizers formulated from unique polymers manufactured in-house by Master Builders Solutions. It is specially engineered for ready-mix concrete.

MasterPolyheed 3536 is differentiated from conventional superplasticisers, such as those based on sulphonated naphthalene formaldehyde condensate in that it is based on unique polymers with long lateral chains. This greatly improves cement dispersion. At the start of the mixing process the same electrostatic dispersion occurs but the presence of the lateral chains, linked to the polymer backbone, generate a steric hindrance which stabilises the cement particles capacity to separate and disperse.

This mechanism provides flowable concrete with greatly reduced water demand.

#### **TYPICAL APPLICATIONS**

**MasterPolyheed 3536** is used for the production of high-quality ready-mix concrete.

#### **ADVANTAGES**

## The ready-mix producer:

- Capability of delivering high performance concrete at any time to the job site in place
- Production of a concrete with low water cement ratios with excellent workability retention properties.
- · Single product for many application needs

#### The contractor / applicator:

- Easier placing and faster strength development
- Improved concrete surfaces
- Guarantee to place the same concrete as specified and ordered from ready-mix plant

#### The engineer:

- Insurance that concrete meets original specification
- · High quality durable concrete

#### **PACKAGING**

**MasterPolyheed 3536** is supplied in 210 L drums, 1,000 L containers or in bulk.

### **STANDARDS**

ASTM C-494 Type F&G BS EN 934-2

#### **TYPICAL PROPERTIES\***

Appearance	Light to dark brown liquid
7 10000101100	Light to dant brown highla
Specific gravity @ 25°C	1.048 - 1.062
pH value	4.0 - 7.0
Chloride content	"chloride-free" to EN 934

### **APPLICATION GUIDELINES**

The normally recommended dosage rate of **MasterPolyheed 3536** is 0.80 - 2.50 L/100kg of total cementitious material.

Other dosages may be recommended in special cases according to the specific site conditions. In this case please consult our Technical Services Department for advice.

#### MIXING

MasterPolyheed 3536 is a ready-to-use admixture to be added to the concrete as a separate component. Optimal result is obtained if MasterPolyheed 3536 is poured into the concrete mix right after the addition of the first 80% of the mixing water, i.e. when all solids are wetted. Avoid adding the admixture to the dry aggregates.

**MasterPolyheed 3536** is suitable for mixes containing all types of cement and supplementary cementitious materials such as:

- Microsilica (Silica Fume)
- Fly Ash (PFA)
- GGBS (ground granulated blast furnace slag)

Note: **MasterPolyheed 3536** is not compatible with **MasterRheobuild** superplasticizers.



# MasterPolyheed® 3536

#### STORAGE AND SHELF LIFE

**MasterPolyheed 3536** should be stored in closed containers or storage tanks to protect from evaporation.

The shelf life is 12 months when stored as above.

The occurrence of a surface layer with **MasterPolyheed 3536** is normal and will have no effect on the performance of the product.

#### HEALTH AND SAFETY

No special requirements must be observed during use. Protection gloves and glasses are however recommended. **MasterPolyheed 3536** is non-flammable, non-toxic or irritant and is not subject to special transport requirements.

**MasterPolyheed 3536** contains no hazardous substances requiring labelling. For further information refer to the Material Safety Data Sheet.

#### **QUALITY AND CARE**

All products originating from Master Builders Solutions Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001 and ISO 14001.

- \* Properties listed are based on laboratory controlled tests.
- ® = Registered trademark of the MBCC Group in many countries.

 ${\tt MBS\_CC-UAE/PI\_3536\_04\_13/v4/01\_17/v5/08\_19/v6/11\_19}$ 

# STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application

Master Builders Solutions Construction Chemicals LLC P.O. Box 37127, Dubai, UAE Tel: +971 4 8090800 www.master-builders-solutions.com/en-ae







