

MasterPozzolith[®] RMC 50

Low dosage, high performance plasticising and strength increasing admixture for concrete with set retardation properties

DESCRIPTION

MasterPozzolith RMC 50 is a high performance concrete plasticiser and water reducing agent. Unlike conventional lignosulphonate plasticisers it possesses the ability to increase early and ultimate strengths even at constant water cement ratios.

MasterPozzolith RMC 50 is designed to optimise hydration of the cement paste, subject to the mix design. When compared to a control concrete 28 days strengths are achievable in 7 days and similarly 7 days strengths are achievable within 3 days.

MasterPozzolith RMC 50 is a versatile product which can be utilised throughout a varying range of temperatures. It can be used as a standard plasticiser in the low dosage range through to a powerful retarder at the high dosage range.

PRIMARY USES

- To increase workability.
- To increase compressive strength.
- Hot weather concreting.
- To effect cement economies.

TYPICAL APPLICATIONS

MasterPozzolith RMC 50 is used wherever optimum workability and maximum strengths are required such as:

- In areas of congested reinforcement where high workability is of benefit.
- Hot weather concreting where controlled delays to initial set are beneficial.
- Readymix concrete where workability retention coupled with retardation of initial set are beneficial.
- Concrete mixes containing mineral admixtures such as PFA, where maximum workability and maximum strength gain is beneficial.

ADVANTAGES

- Highly effective over wide range of cement contents
- Higher early and ultimate strengths
- Low dosage
- Improves workability whilst at the same time increasing compressive strength
- Permits water reduction, in the region of 10% to 15%
- Increases impermeability and durability
- Reduces placing problems in hot weather concreting by improving workability and workability retention
- Improves surface finish, pumpability and trowellability
- Enables significant economies in mix design to be achieved thereby saving cement

PACKAGING

MasterPozzolith RMC 50 is available in bulk or in 210 litre drums.

STANDARDS

EN 934-2 Tables 2 and 10
 ASTM C494 : Types A, B and D
 BS 5075 : Part 1 (superseded EN 934-2)

TYPICAL PROPERTIES*

Colour	Dark brown liquid
Specific gravity	1.215 at 25°C
Chloride content	"chloride free" to EN 934
Freezing point	0°C

MasterPozzolith[®] RMC 50

APPLICATION GUIDELINES

MasterPozzolith RMC 50 should be added to the concrete mix during the mixing cycle at the same time as the water or the aggregates. Never add **MasterPozzolith RMC 50** to the dry cement. No extension to normal mixing times is necessary.

COMPATIBILITY

MasterPozzolith RMC 50 can be used with all types of Portland cement including sulphate resisting and modified cement (Type II). For use with special cements contact Master Builders Solutions ME's Technical Services Department. **MasterPozzolith RMC 50** should not be premixed with other admixtures.

If other admixtures are to be used in concrete containing **MasterPozzolith RMC 50**, they must be dispensed separately. Consult Master Builders Solutions Technical Services Department for advice.

DOSAGE

The normal dosage range is 120 to 400ml per 100kg of cement. Higher dosages may be required when certain combinations of materials and conditions are present.

In all cases we recommend trial mixes are carried out to determine the correct levels of admixture required to achieve the desired concrete properties.

EFFECTS OF OVER DOSAGE

A severe over dosage of **MasterPozzolith RMC 50** will result in the following:

- Retardation of initial and final set.
- Slight increase in air entrainment.
- Increase in workability.

Providing it is properly cured, the ultimate strength of the concrete will not normally be adversely affected and will generally be higher than for normal concrete. The retarding effect of over dosage will be exaggerated with SRC cement.

SETTING TIME

MasterPozzolith RMC 50 provides controlled retardation to initial set. Setting times of concrete mixes are related to cement type and ambient temperature.

DISPENSING

MasterPozzolith RMC 50 should be dispensed through a proprietary dispenser, such as is available from Master Builders Solutions. Details upon on request.

ACTION

MasterPozzolith RMC 50 acts on the cement particles by combining the effects of powerful plasticising and deflocculating agents. It considerably improves the workability of concrete mixes without the addition of extra water. The improved dispersion of the cement particles ensures the process of hydration proceeds under the optimum conditions.

STORAGE

Store under cover, out of direct sunlight and protect from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult Master Builders Solutions Technical Services Department.

MasterPozzolith[®] RMC 50

HEALTH AND SAFETY

MasterPozzolith RMC 50 is not a fire or health hazard. Spillages should be washed down immediately with cold water. For further information refer to the material safety data sheet.

QUALITY AND CARE

All products originating from Master Builders Solutions Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001 and ISO 14001.

* Properties listed are based on laboratory controlled tests.

© = Registered trademark of the MBCC Group in many countries.

MBS_CC-UAE/PI_RMC50_04_94/v2/07_15

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
Construction Chemicals LLC
P.O. Box 37127, Dubai, UAE
Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae

Disclaimer: the TUV mark relates to certified management system and not to the product mentioned on this datasheet



A brand of
MBCC GROUP