

# MasterRheobuild<sup>®</sup> 1100

A high range water reducing superplasticising admixture for the production of rheoplastic concrete

## DESCRIPTION

The basic components of **MasterRheobuild 1100** are synthetic polymers which allow mixing water to be reduced considerably and concrete strength to be enhanced significantly, particularly at early ages. **MasterRheobuild 1100** is a chloride free product.

## TYPICAL APPLICATIONS

- Precast concrete.
- Low water/cement ratio concrete.
- In complicated formwork or with congested reinforcement.

## ADVANTAGES

**MasterRheobuild 1100** allows the production of very flowable concrete, with a low water / cement ratio. Concrete with **MasterRheobuild 1100** shows strengths higher than concrete without admixture having the same workability. The increase in strength, specially evident at early ages remains at later ages, both in air cured and steam cured processes. Initial and final sets do not change significantly with respect to concrete without admixture.

Due to the reduction in the water / cement ratio, all other properties of hardened concrete improve significantly, namely; lowered permeability, shrinkage and creep, increased workability and modulus of elasticity.

For more detailed information on the influence of superplasticisers on hardened concrete properties, consult your local Master Builders Solutions representative.

## PACKAGING

**MasterRheobuild 1100** is available in bulk or 210 L drums.

## STANDARDS

EN 934-2 Tables 3.1 and 3.2  
 ASTM C-494 Types A and F  
 BS 5075 Part 1 & 3 (superseded by EN 934-2)

## TYPICAL PROPERTIES\*

Colour	Dark brown liquid
Specific gravity @ 25°C	1.210
Chloride content	"chloride-free" to EN 934
Freezing point	0°C

## APPLICATION GUIDELINES

**MasterRheobuild 1100** should be added to the mix with the gauging water.

No extension to the mixing time is necessary. Never add **MasterRheobuild 1100** to dry cement.

Alternatively, when using **MasterRheobuild 1100** to produce flowing concrete at site using ready mix trucks, it can be added to the concrete via the feed hopper at the rear of the truck. Mix before discharge for 3 minutes at 10rpm to produce a fully homogenous mix.

When using **MasterRheobuild 1100** to obtain very high early strengths, advantage must be taken of its water reducing properties.

## DOSAGE

**MasterRheobuild 1100** is normally dispensed at a rate of 0.8-1.5 L/100kg of cement. Subject to successful trials, other dosages may be used up to a rate of 3 L/100kg of cementitious material.

## EFFECTS OF OVER DOSAGE

A severe over-dosage of **MasterRheobuild 1100** will result in the following:

- Retardation of initial and final set.
- Slight increase in air entrainment.
- Increase in workability.

# MasterRheobuild<sup>®</sup> 1100

## DISPENSING

**MasterRheobuild 1100** is introduced into the mixer together with mixing water. The plasticising effect or water reduction is higher if the admixture is added to the concrete after 50-70% of the mixing water has been added. The addition of **MasterRheobuild 1100** to dry aggregate or cement is not recommended.

## MIXING

**MasterRheobuild 1100** is compatible with all cements and admixtures meeting ASTM standards.

The use of **MasterRheobuild 1100** and **MasterAir** air entraining agent is recommended whenever concrete is required to withstand freeze / thaw cycling.

## STORAGE AND SHELF LIFE

Store under cover, out of direct sunlight and protect from extremes of temperature. Shelf life is 12 months when stored as above.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult Master Builders Solutions Technical Services Department.

## HEALTH AND SAFETY

**MasterRheobuild 1100** contains no hazardous substances requiring labelling. For further information refer to the material safety data sheet.

## QUALITY AND CARE

All products originating from Master Builders Solutions Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001 and ISO 14001.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

MBS\_CC-UAE/Rh\_1100\_10\_94/v1/11\_13/v2/12\_19

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

**Master Builders Solutions**  
**Construction Chemicals LLC**  
P.O. Box 37127, Dubai, UAE  
Tel: +971 4 8090800  
[www.master-builders-solutions.com/en-ae](http://www.master-builders-solutions.com/en-ae)

**Disclaimer:** the TUV mark relates to certified management system and not to the product mentioned on this datasheet



A brand of  
**MBCC GROUP**