

MasterRheobuild[®] 857

High range water reducing superplasticiser

DESCRIPTION

MasterRheobuild 857 is formulated from synthetic polymers specially designed to impart rheoplastic qualities to concrete.

A rheoplastic concrete is a fluid concrete with a slump of at least 200 mm, easily flowing, but at the same time free from segregation and having the same water/cement ratio as that of a low slump concrete (25 mm) without admixture.

MasterRheobuild 857 is chloride free.

TYPICAL APPLICATIONS

- Mixes containing GGBS or microsilica
- Mass concrete pours
- Ready mixed concrete
- Pumped concrete
- Casting in hot climates

To obtain:

- High workability for longer periods
- Lower pumping pressure
- Delayed setting with longer workability
- Higher ultimate strengths
- Reduced permeability
- Improved durability

ADVANTAGES

MasterRheobuild 857 considerably improves the properties of fresh and hardened concrete.

PACKAGING

MasterRheobuild 857 is available in bulk or in 210 L drums.

STANDARDS

EN 934-2 Tables 3.1, 3.2, 11.1 and 11.2
ASTM C-494 Type A, B, D, F and G

TYPICAL PROPERTIES*

| | |
|---------------------------|---------------------------|
| Colour | Dark brown liquid |
| Specific gravity @25°C | 1.235 |
| Chloride content | "chloride-free" to EN 934 |
| Freezing point | 0°C |

APPLICATION GUIDELINES

Optimum dosage **MasterRheobuild 857** should be determined in trial mixes. As a guide, the following dosages are recommended as a starting point for any trial. In normal concrete a dosage of between 0.8 - 2.0 L/100kg total cementitious material. In a high performance, low water cement ratio concrete, a dosage of between 1.5 - 2.5 L/100kg total cementitious material. Dependent upon mix requirement, it is possible to use a higher dosage of **MasterRheobuild 857** without causing any adverse effects upon the concrete. Please consult Master Builders Solutions Construction Chemicals Technical staff for further information.

MIXING

MasterRheobuild 857 is a ready-to-use liquid which is dispensed into the concrete together with the mixing water. The plasticising effect and water reduction are higher if the admixture is added to the concrete after 50-70% of the mixing water has been added. The addition of

MasterRheobuild 857 to dry aggregate or cement is not recommended. Automatic dispensers are available.

MasterRheobuild 857 ensures that rheoplastic concrete remains workable in excess 3 hours at +20°C.

Workability loss is dependent on temperature, and on the type of cement, the nature of aggregates, the method of transport and initial workability. It is strongly recommended that concrete should be properly cured particularly in hot and dry climates.

MasterRheobuild 857 is suitable for concrete mixes containing all types of portland cement and cementitious materials such as:

- Microsilica (Silica Fume)
- Fly Ash (PFA)
- GGBS (ground granulated blast furnace slag)

MasterRheobuild[®] 857

STORAGE AND SHELF LIFE

MasterRheobuild 857 must be stored where temperatures do not drop below +5°C. If the product has frozen thaw and agitate until completely reconstituted. Store under cover, out of direct sunlight and protect from extremes of temperature, the shelf life is 12 months.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult Master Builders Solutions Technical Services Department.

HEALTH AND SAFETY

MasterRheobuild 857 is not a fire or health hazard. Spillages should be washed down immediately with cold water. For further information refer to the material safety data sheet.

QUALITY AND CARE

All products originating from Master Builders Solutions Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001 and ISO 14001.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

MBS_CC-UAE/Rh_857_09_01/v2/01_18/v3/08_19

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
Construction Chemicals LLC
P.O. Box 37127, Dubai, UAE
Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae



A brand of
MBCC GROUP

Disclaimer: the TUV mark relates to certified management system and not to the product mentioned on this datasheet