

MasterRheobuild[®] 858

High range, water reducing superplasticiser for rheoplastic concretes

DESCRIPTION

MasterRheobuild 858 is a ready-to-use, high range water-reducing admixture designed to produce high slump concrete with workability retaining properties. The product is chloride free.

TYPICAL APPLICATIONS

- Microsilica concrete
- Mass concrete pours
- Ready mixed concrete
- Long-distance transport
- Pumped concrete
- Casting in hot climates

To obtain:

- Reduced thermal peaks
- High workability for longer periods
- Lower pumping pressure
- Delayed setting with longer workability
- Higher ultimate strengths.
- Reduced permeability
- Improved durability

ADVANTAGES

MasterRheobuild 858 considerably improves the properties of fresh and hardened concrete.

PACKAGING

MasterRheobuild 858 is available in bulk or in 210 litre drums.

STANDARDS

ASTM C-494 Type A, B, D, F and G

TYPICAL PROPERTIES*

Colour	Dark brown
Specific gravity @ 25°C	1.240
Chloride content	"chloride-free" to EN 934
Freezing point	0°C
Flashpoint	N/A

APPLICATION GUIDELINES

DOSAGE

Optimum dosage of **MasterRheobuild 858** should be determined in trial mixes. As a guide the following dosages are recommended as a starting point for any trial. In normal concrete a dosage of between 0.8 to 2.0 litres per 100kg cementitious material. In high performance micro silica concrete a dosage of between 1.5 to 2.5 litres per 100kg cementitious material. Dependent upon mix requirement, it is possible to use a higher dosage of **MasterRheobuild 858** without causing any adverse effects upon the concrete. Please consult Master Builders Solutions Construction Chemicals Technical staff for further information.

COMPATIBILITY

MasterRheobuild 858 is compatible with all cements and most air entraining agents meeting the ASTM standards. The addition of **MasterRheobuild 858** and **MasterAir 100** (air entraining agent) to concrete is recommended where it is required to withstand freezing and thawing cycles.

DISPENSING

MasterRheobuild 858 is a ready-to-use liquid which is dispensed into the concrete together with the mixing water. The plasticising effect and water reduction are higher if the admixture is added to the concrete after 50 to 70% of the mixing water has been added. The addition of **MasterRheobuild 858** to dry aggregate or cement is not recommended. Automatic dispensers are available

MasterRheobuild[®] 858

WORKABILITY

Workability loss is dependent on temperature, and on the type of cement, the nature of aggregates, the method of transport and initial workability. It is strongly recommended that concrete should be properly cured particularly in hot and dry climates.

STORAGE

MasterRheobuild 858 must be stored where temperatures do not drop below +5°C. If product has frozen thaw and agitate until completely reconstituted. Store under cover, out of direct sunlight and protect from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult Master Builders Solutions Technical Services Department.

HEALTH AND SAFETY

MasterRheobuild 858 is not a fire or health hazard. Spillages should be washed down immediately with cold water. For further information refer to the material safety data sheet.

QUALITY AND CARE

All products originating from Master Builders Solutions Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001 and ISO 14001.

* Properties listed are based on laboratory controlled tests.

© = Registered trademark of the MBCC Group in many countries.

MBS_CC-UAE/Rh_858_02_96/v4/10_15

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
Construction Chemicals LLC
P.O. Box 37127, Dubai, UAE
Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae

Disclaimer: the TUV mark relates to certified management system and not to the product mentioned on this datasheet



A brand of
MBCC GROUP