

MasterRoc[®] MP 650

Fast setting micro fine Portland cement for injection into rock and soil

DESCRIPTION

MasterRoc MP 650 is a well graded cement milled from pure Portland cement clinker with a Blaine value of 650 m²/kg.

Due to its small particle size it penetrates very well into tight joints, fissures and pore spaces to provide a water-tight grouted rock or soil mass.

It achieves initial and final setting faster than standard micro fine cements. This increases productivity in a tunnel injection operation. The short open time of 1 to 1½ hours and a very short setting time of 2½ hours (at about 20°C) reduce the waiting time for the next excavation round to start to a minimum.

TYPICAL APPLICATIONS

- Pre-injection in all underground structures
- Also possible for post injection
- Water ingress reduction
- Ground stabilization
- Contact injection

ADVANTAGES

- Excellent penetration into tight joints, fissures and pore spaces
- Fast setting
- Durable
- Better working environment - no hazardous components
- Economical solution
- Standard cement injection equipment can be used

PACKAGING

MasterRoc MP 650 is supplied in 20 kg plastic bags and 1000 kg bags.

TYPICAL PROPERTIES*

Fineness (Blaine) >625 m²/kg

Particle size distribution:

| | |
|------------|------|
| <40 micron | 100% |
| <30 micron | 98% |
| <20 micron | 97% |
| <15 micron | 94% |
| <10 micron | 77% |
| < 5 micron | 44% |
| < 2 micron | 16% |

SETTING TIMES

The setting times, at a 1:1 w/c ratio (by weight) and at 20° C are as follows:

Initial set: 60-120 min (Measured by Vicat needle)

Final set: 120-150 min (1 mm penetration by Vicat needle) Injection grout properties indicated below, relates to a mix containing 1.5% MasterRheobuild 2000PF:

| | |
|--------------------|------------------|
| Water/Cement ratio | 1.0 |
| Mud balance | 1.48 - 1.50 kg/l |
| Flow cone | 32 – 34 s |
| Bleeding maximum | 2 % |

APPLICATION GUIDELINES

MasterRoc MP 650 should always be used with **MasterRheobuild 2000PF** water reducing admixture (1.0 - 2.0 % of cement weight). The w/c ratio (by weight) should normally be between 0.5 and 1.0.

MIXING

- Fill the mixer with water
- Add **MasterRheobuild 2000PF**
- Add cement and mix for 2 minutes
- Transfer to agitator

MasterRoc[®] MP 650

It is very important to use an efficient mixer. Colloidal mixers give the best result. Minimum rpm for colloidal mixers is 1500.

NB: Do not over mix. Mixing longer than recommended may cause the grout temperature to increase and set in the pump and hoses.

POT LIFE

The mix should be kept under constant agitation prior to injection. Do not keep grout in agitator longer than 30 – 40 minutes.

INJECTION

High-pressure piston pumps are normally used to pump the suspension into the rock. The grout should be injected within 30 - 40 minutes after mixing to ensure that it keeps penetrating into the fissures. Longer open times can be achieved by using MasterRoc HCA 10 stabilizer hydration control admixture.

For much longer open times, an alternative is to use **MasterRoc MP 650 SR**. This product is available on special request.

HARDENING

MasterRoc MP 650 will have set sufficiently after 2 - 2½ hours to allow drilling to commence for control or blast holes.

STORAGE AND SHELF LIFE

MasterRoc MP 650 has a shelf life of 9 months when stored in original closed bags in ventilated dry areas.

HEALTH AND SAFETY

Any physical contact (e.g. skin or eyes) made with the product should be avoided, as it may cause irritation or burns.

If such contact occurs, the affected area should be washed with plenty of clean water. In case of eye contact, seek immediate medical advice.

For further information please refer to the Material Safety Data Sheet or contact your local Master Builders Solutions representative.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

MBS_CC-UAE/Roc_MP650/v2/07_14

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
Construction Chemicals LLC
P.O. Box 37127, Dubai, UAE
Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae

Disclaimer: the TUV mark relates to certified management system and not to the product mentioned on this datasheet



A brand of
MBCC GROUP