

MasterRoc[®] SA 430

Liquid sprayed concrete accelerator for wet-mix spraying

DESCRIPTION

MasterRoc SA 430 is an accelerator for the wet-mix spraying process but can also be used in the dry-mix spraying process. It is a liquid additive whose dosage can be varied to the desired setting and hardening times.

TYPICAL APPLICATIONS

MasterRoc SA 430 is suitable for all applications where high early strength and very thick sprayed concrete layers are required.

- For temporary ground support in tunneling and mining
- Slope stabilization

ADVANTAGES

- Fast setting and higher early strength
- Rapid work progress
- Low viscosity
- Easy to mix into the concrete, also at low temperatures
- Low consumption

PACKAGING

MasterRoc SA 430 is supplied in IBCs or in bulk.

TYPICAL PROPERTIES*

Form	Liquid
Color	Transparent
Density (at +20°C)	1.34 ± 0.02
Viscosity (at +20°C)	30-70 mPa.s (cps)
Solubility in water	Total
Thermal stability	+5°C
Chloride content	<0.1%
Physiological effect	Irritant to skin and eyes

APPLICATION GUIDELINES

The substrate must be clean and free from loose particles and preferably damp. Fresh standard Portland cement should be used because the reaction time is increased by prolonged storage. Preliminary tests are recommended for cements providing high sulphate resistance.

CONSUMPTION

The consumption of **MasterRoc SA 430** also depends on the w/c+b ratio, temperature conditions (concrete and ambient), cement reactivity and on required layer thickness, setting time and early strength development. The consumption is normally in the range of 3 to 8% of binder weight.

Overdosing (>8%) may result in decreased final strength.

STORAGE AND SHELF LIFE

Storage temperature for **MasterRoc SA 430** is between + 5°C and + 60°C. If it has frozen, thaw at +20 °C or above and completely reconstitute with a mild mechanical agitation. Please contact your local Master Builders Solutions representative prior to the use of any product that has been frozen. Performance tests should always be carried out before use. If stored tightly closed in original containers and under the above conditions, **MasterRoc SA 430** has a shelf life of at least 12 months.

MasterRoc[®] SA 430

HEALTH AND SAFETY

MasterRoc SA 430 is an irritant fluid - any contact with skin and eyes must be avoided. It is essential that safety glasses and rubber gloves always be worn during handling. The use of a protective cream e.g. Ketodex 1, is recommended. In case of contact with eyes or skin, flush immediately with plenty of water and seek medical advice.

Further details can be found in the Material Safety Data Sheet.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

MBS_CC-UAE/Roc_SA430/v2/08_15

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
Construction Chemicals LLC
P.O. Box 37127, Dubai, UAE
Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae

Disclaimer: the TUV mark relates to certified management system and not to the product mentioned on this datasheet



A brand of
MBCC GROUP