

MasterSeal[®] 122

Multi-purpose, premium quality, silicone sealant

DESCRIPTION

MasterSeal 122 is a versatile, neutral cure silicone sealant, having exceptional bond to most surfaces without primer. It is virtually odorless during cure. It is non-slump, low viscosity, with excellent resistance against UV, weather and water, which can be used in vertical and horizontal joints, in internal and external environments, to provide a long-term, durable, elastic seal.

TYPICAL APPLICATIONS

MasterSeal 122 has been developed to form a durable elastic seal for vertical and horizontal, sanitary, building, glazing and façade joints in internal and external areas.

Because it is neutral curing, **MasterSeal 122** can also be used to provide long lasting elastic sealing of movement & construction joint in concrete, blockwork and brick masonry without priming.

Also recommended for curtain wall construction, glazing systems, bathrooms, showers, kitchens and wet rooms having with anti-fungal property for use in residential, commercial and industrial buildings.

ADVANTAGES

- Neutral cure, almost odourless
- Perfect bond without primer on most common substrates: saves time and money
- High quality silicone: excellent UV, weather and water resistance, elasticity and resilience and long service life
- Resistant to mold and mildew even in high moisture and temperature environments
- Range of colours: standard commonly used colours available

PACKAGING AND COLORS

MasterSeal 122 is supplied in boxes of 24 x 280ml cartridges and available as Clear, White (RAL 9010), Standard colors. Following non-standard colors can be obtained with MOQ: Light Grey (RAL 7035), Concrete Grey (RAL 7040), Light Ivory (RAL 1015), Black, Mahogany Brown (RAL 8016) and Bronze (RAL 1036)

Note: The colours mentioned are closest match to the RAL Nos.

STANDARDS

Conforms to ASTM C920 Type S, Grade NS, Class 25, Use T2, NT, A, G and M

TYPICAL PROPERTIES*

Cure mechanism	Neutral cure with atmospheric moisture
Specific gravity	0.97
Skin formation time (23°C 55% RH)	10 mins
Tack free time	30 mins
Rate of cure (25°C 50% RH)	3 mm/day
Application temperature	+5°C to 40°C
Movement capability	25%
E-Modulus at 100%	0.25 N/mm ²
Shore A Hardness (ASTM D2240)	20
Ultimate elongation at break	400%
Tensile Strength	0.9 N/mm ²
Temperature in service	-50°C to +120°C

MasterSeal[®] 122

APPLICATION GUIDELINES

SURFACE PREPARATION


To ensure optimum adhesion the joint faces must be sound, clean, dry and free from any loosely adherent material which could prevent adequate

bond to the substrate. **MasterSeal 122** adheres perfectly without the use of a primer to most non porous substrates. Strongly porous substrates may need priming using **MasterSeal P 101**. It is good practice to test adhesion before commencing full installation. Protect surrounding surfaces with masking tape if they are to be painted.

Joint dimensions:

Correct joint design is essential to ensure correct performance of the installed joint sealant. Minimum joint widths should be 6mm. Up to 12mm width depth should equal the width. For all joints 12mm to 15mm wide it is recommended

that the depth of the installed joint sealant should be at least 8mm. For joints >15mm the maximum depth should be half the width.



Joint depth is controlled by the use of closed cell backer rod. This also prevents 3 sided adhesion which would be highly detrimental to long term performance of the joint sealant.

Corner beads should be a minimum of 6mm x 6mm.

PLACING / APPLICATION

Fix cartridge into cartridge gun. Cut screw threaded nipple at end of cartridge. Attach application nozzle. Cut nozzle at 45° so that aperture is equal to width of joint. Gun sealant into joint in one smooth continuous operation ensuring sufficient material is delivered to fill joint. Using a spatula or tooling tool press sealant into joint and onto joint faces while leaving a smooth concave surface. Remove any masking tape used.

APPLICATION TEMPERATURE RANGE

Minimum +5°C
 Maximum +40°C

CLEANING

Clean uncured material using a solvent such as xylene or toluene. Cured material can only be cleaned mechanically (Tip: WD 40 can assist to remove cured silicones).

COVERAGE / YIELD

Linear meter / 280ml unit

Joint depth (mm)	Joint width (mm) approx.		
	6	12	20
6	7.8	3.9	-
8	-	2.9	-
10	-	-	1.4

Note: The above coverage rates do not include wastage

WATCHPOINTS

- Not suitable for PE, PP, PC, PMMA, PTFE, Neoprene, and bituminous substrates
- **MasterSeal 122** is NOT paintable.
- Compatibility with glazing edge seals need to be checked individually.

STORAGE AND SHELF LIFE

MasterSeal 122 has a shelf life of 12 months from production date when stored in its original packaging at temperatures between 5°C and 25°C.

MasterSeal[®] 122

HEALTH AND SAFETY

May produce an allergic reaction.
 Please refer to Material Safety Datasheet for detailed health and safety information.

Avoid contact with the skin, eyes and clothing.

On skin contact:

Wash thoroughly with soap and water. Under no circumstances should organic solvent be used. If irritation develops, seek medical attention.

On contact with eyes:

Wash affected eyes for at least 15 minutes under running water with eyelids held open, consult an eye specialist.

On ingestion:

Rinse mouth and then drink plenty of water. Do not induce vomiting unless told to by a poison control center or doctor.

No special measures necessary if stored and handled correctly. Handle in accordance with good building materials hygiene and safety practice. Wearing of closed work clothing is recommended. When using, do not eat, drink or smoke. Hands and/or face should be washed before breaks and at the end of the shift. At the end of the shift the skin should be cleaned and skin-care agents applied. Gloves must be inspected regularly and prior to each use. Replace if necessary (e.g. pinhole leaks).

QUALITY AND CARE

All products originating from Master Builders Solutions Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001 and ISO 14001.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
Construction Chemicals LLC
 P.O. Box 37127, Dubai, UAE
 Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae

Disclaimer: the TÜV mark relates to certified management system and not to the product mentioned on this datasheet



A brand of
MBCC GROUP

MBS_CC-UAE/SI_122_05_16/v4/12_17/v5_10_18