

MasterSeal® 550

Acrylic reinforced cementitious, flexible waterproof coating

DESCRIPTION

MasterSeal 550 is a two-component acrylic modified cementitious coating that requires only on site mixing to form the ideal product to waterproof and resurface concrete, masonry, and most other construction materials.

Simply applied by stiff brush, roller, or trowel, it forms a waterproof, flexible coating.

MasterSeal 550 provides an effective barrier to waterborne salts and atmospheric gases.

Fluid applied, **MasterSeal 550** provides a hard wearing, seamless, waterproof membrane for roofs and foundation protection.

MasterSeal 550 is composed of specially selected cements, silica sand and reactive fillers supplied in powder form together with a liquid component of blended acrylic copolymers and wetting agents.

TYPICAL APPLICATIONS

- To reface and even out variations in concrete surfaces.
- As a waterproof lining for water retaining structures.
- For coating seawater channels.
- Sealing and coating tie bar holes to ensure watertightness.
- For waterproofing and protection against brackish water.
- To provide foundation protection.
- As a waterproof coating for roofs.
- As a backing to marble and granite to prevent water ingress and thus alleviate surface staining.
- To provide protection to concrete surfaces from carbonation and chloride attack.
- For use on pedestrian walkways in marine areas.
- For waterproofing of wet areas under tiling.
- As a waterproof and protection coating on top of spray polyurethane foam roof insulation.

ADVANTAGES

- Waterproof
- Excellent adhesion. Bonds to porous and non-porous surfaces
- Flexible
- Suitable for light pedestrian traffic
- Breathable - whilst repelling water, allows substrate to breathe
- High resistance to chloride ion diffusion
- Unlike conventional coatings which require a 7-28 day cure of concrete, **MasterSeal 550** can be applied to 24 hour-old concrete thereby giving immediate protection
- White color has high solar reflectivity index (SRI >78) to prevent heat island effect on roofs

PACKAGING AND COLORS

MasterSeal 550 is available in 20 kg double pack.

MasterSeal 550 is available in three standard colours: J-Light Grey, K-White and H-Dark Grey.

STANDARDS

BS 6920: Part 1 2000 - Suitable for use in contact with potable water.

TYPICAL PROPERTIES*

Density	1826 kg/m ³
Chloride ion diffusivity	Not measurable after 24 months of testing
Depth of water penetration under pressure BS EN 12390 Part 8: 2009	Nil
Liquid water permeability BS EN 1062-3: 2008	<0.1 kg (m ² xh ^{0.5})
Carbon dioxide permeability BS EN 1062-6: 2002 Method A	>50 m
Equivalent air layer thickness (SD)	

APPLICATION GUIDELINES

SURFACE PREPARATION

As with all coating systems, surface preparation is of prime importance. Remove all grease, oil, dust, residual curing compound, mould release agent, laitance or other contaminant that could impair adhesion. Suitable cleaning methods include ultra-high-pressure water jetting grit blasting and grinding. Spalled concrete should be cut back to

MasterSeal® 550

sound concrete and made good with a suitable cementitious repair mortar such as **MasterEmaco S 488**. Conventional concrete curing compounds should be removed before application. The exception to this is when **MasterKure 181** has been used.

Chloride Ion diffusivity

MasterSeal 550 provides an effective barrier to waterborne salts such as chlorides and sulphates. *Independent assessment has shown that even after 12 months constant immersion the chloride ion diffusion co-efficient could not be measured for **MasterSeal 550**.

Chemical resistance

MasterSeal 550 has outstanding wear and weather resistance and good resistance to sodium hydroxide, calcium chloride, de-icing salts. **MasterSeal 550** coated surfaces exhibit good resistance to mild acids.

Anti carbonation coating

MasterSeal 550 is an extremely effective barrier to atmospheric acidic gases which cause carbonation in concrete structures. **MasterSeal 550** at an applied rate of 1.8 kg/m² gives an equivalent air layer thickness for carbon dioxide diffusion (R) of 92 m. The accepted minimum value for R is 50 m. Testing to confirm this was carried out independently by Taywood Engineering 2005. A report is available on request.

MIXING

MasterSeal 550 is supplied in premeasured units and should be mixed on site utilising clean containers. Slowly add the powder to the liquid and mix, using a slow speed drill fitted with a suitable paddle. MIX AND USE. Do not mix more material than can be used in one hour.

NOTE: Although **MasterSeal 550** is supplied in premeasured packs, part packs can be used by mixing 2 volumes of powder to 1 volume of liquid. Mix thoroughly and keep mixed during application. DO NOT RE-TEMPER WITH WATER.

PLACING / APPLICATION

Do not apply to dry concrete

Saturate concrete surfaces with clean water whilst still visibly damp, but free of standing water, apply, using a short, stiff bristle brush or roller. Trowel application can be undertaken as necessary. For heavy 6-10 mm depressions, honeycombs etc. use less gauging liquid and mix to the desired consistency. Where more than one coat is found necessary to achieve the desired thickness, apply the second or subsequent coats after the previous coat has dried.

It is recommended, for general resurfacing, that each coat should be a minimum of 1 mm thick. Spray application is recommended for large areas, details of suitable equipment can be provided by Master Builders Solutions Technical Service Department.

Notes

Where subsequent tiling works are to be carried out on vertical surfaces, contact the local Master Builders Solutions representative for advice.

COVERAGE / YIELD

1.8 kg / m² at 1 mm thickness.

STORAGE AND SHELF LIFE

Part A (powder): Shelf life is 12 months from date of manufacturing in unopened original bags. Product must be kept out of direct sunlight, in a dry, cool place, stored clear of the ground on pallets. Avoid excessive compaction.

Part B (liquid): Shelf life is 12 months from date of manufacturing in unopened original containers. Product must be kept out of direct sunlight and in a dry, cool, preferably air-conditioned warehouse below 35°C temperature. Store clear of the ground on pallets. Do not stack pallets.

MasterSeal[®] 550

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention.

QUALITY AND CARE

All products originating from Master Builders Solutions Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001 and ISO 14001.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

MBS_CC-UAE/SI_550_12_94/v10/07_20/v11/11_20/v12/02_21

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
Construction Chemicals LLC
P.O. Box 37127, Dubai, UAE
Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae



A brand of
MBCC GROUP

Disclaimer: the TUV mark relates to certified management system and not to the product mentioned on this datasheet