

MasterSeal[®] P 640

Single component polyurethane primer for MasterSeal M 640

DESCRIPTION

MasterSeal P 640 is a single component, polyurethane based, solvent containing primer for absorbent surfaces in applications where **MasterSeal M 640** is utilized.

TYPICAL APPLICATIONS

- Primer for polyurethane waterproofing membranes like certified **MasterSeal M 640**.
- Can be applied on concrete, cement mortar, wood, etc.

ADVANTAGES

- Single component product that allows simple application without the need of mixture
- Excellent adhesion
- Excellent penetration and sealing of pores of concrete
- Fast Curing
- Elasticity to absorb substrate movements
- Resistant to standing water
- Frost resistant

PACKAGING AND COLORS

MasterSeal P 640 is supplied in 5kg and 17kg and available in Semi-transparent.

APPLICATION GUIDELINES

SURFACE PREPARATION

All substrates (new and old) must be structurally sound, dry and free of laitance and loose particles. Clean of oil, grease, paint stains and other adhesion impairing contaminants. Temperature of the support should be minimum +5°C and maximum +35°C. Profile mechanically the surface by shot blasting, high-pressure water jetting or other suitable mechanical preparation method. After surface preparation the tensile strength of the substrate should exceed 1N/mm² (check with an approved pull-off tester). The residual moisture content of the substrate must not exceed 4% (check with e.g. CM device). The temperature of

the substrate must be at least 3°C above the current dew point temperature.

MIXING

MasterSeal P 640 is a single component material. Prior to application, the temperature of the material should be in the range of 15-25°C.

PLACING / APPLICATION

MasterSeal P 640 is applied normally in one coat, homogeneously covering the substrate. In certain cases, for complete sealing of substrate a second coat may be necessary. Try to keep the temperature uniform during application and hardening. The product must not be applied when the temperature is below +5°C or above 35°C. Do not mix solvents, sand or other products that could affect the products properties must not be added. After maximum 4 hours apply the waterproofing membrane. Refer to TDS for application guidelines.

CLEANING

While still wet with a suitable thinner (Xylene / MEK / Acetone). Once cured it can only be removed mechanically.

COVERAGE / YIELD

Approx. 200-250g/m² are required per layer. These consumptions are theoretical and can vary according to the absorption and roughness of the support. It is essential to carry out representative trials on site to evaluate the exact consumption.

STORAGE AND SHELF LIFE

Store in cool and dry warehouse conditions between 15-25°C. Do not expose to direct sunlight. Shelf life in these conditions is 9 months in unopened original containers.

MasterSeal[®] P 640

TYPICAL PROPERTIES*

Properties	Result
Chemical base	Polyurethane
Mixing ratio	single component
Solids content @20°C	51%
Density @20°C	1.0g/cm ³
Viscosity @20°C	220mPas
Re-coating interval / 23°C, 50 % rel. h.	min. 2 hours max. 5 hours
Fully cured / 23°C, 50 % rel. h.	7 days
Substrate and ambient temperatures	min. 5°C max. 35°C
Permissible relative humidity	max. 85%

Technical data after curing*

Properties	Standard	Result
Service temperatures		min. -20°C max. 80°C
Shore A hardness	ASTM D2240	>95
Adhesion to concrete	ASTM D903	>2.2N/mm ²

**The above figures are intended as a guide only and should not be used as a basis for specifications.*

MasterSeal[®] P 640

WATCHPOINTS

This product conforms to the EU directive 2004/42/EG (Deco-Paint directive) and contains less than the maximum allowable VOC limit (Stage 2, 2010).

According to the EU directive 2004/42, the maximum allowable VOC content for the Product Category IIA / j is 500g/l (Limit: Stage 2, 2010). The VOC content for **MasterSeal P 640** is <500g/l (for the ready to use product)

HANDLING / PRECAUTIONS

In its cured state, **MasterSeal P 640** is physiologically non- hazardous. The following protective measures should be taken when working with this material:

Wear safety gloves, goggles and protective clothing. Avoid contact with the skin and eyes. In case of eye contact, seek medical attention. Avoid inhalation of fumes. When working with the product, do not eat, smoke or work near a naked flame. For additional references to safety hazard warnings, regulations regarding transport and waste management, please refer to the relevant Material Safety Data Sheet. The regulations of the local trade association and/or other authorities regarding safety and hygiene of workers handling polyurethanes and isocyanates must be observed.

® = Registered trademark of the MBCC Group in many countries.

* Properties listed are based on laboratory controlled tests.

MBS_CC-UAE/SI_P640_04_15/v1/

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
Construction Chemicals LLC
P.O. Box 37127, Dubai, UAE
Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae

Disclaimer: the TUV mark relates to certified management system and not to the product mentioned on this datasheet



A brand of
MBCC GROUP