

THIS METHOD STATEMENT FLEXIBLE MULTI PURPOSE TILE ADHESIVE FOR ALL WALL AND FLOOR CERAMIC TILES, PORCELAIN MOSAIC AND FULLY VITRIFIED TILES.

## **METHOD STATEMENT: MasterTile FLX 23 Grey and White**

### **1. SUBSTRATE:**

- 1.1. The substrate must be sound, clean and able to bear weight, bond-inhibiting materials and other residues must be thoroughly removed.
- 1.2. The substrate must be plumb and flush in accordance with BS 5385.
- 1.3. Very absorbent cement-based substrates and aerated blocks should be primed with **MasterTile P 302**.
- 1.4. Refer to Master Builders Solutions Technical department if there is any uncertainty as to the type of preparation needed or any other related problems such as cracks in the substrate.

### **2. APPLICATION PROCEDURE:**

#### **2.1. Mixing of bedding mortar**

- 2.1.1. Place **approx. 4.8-5.0 L (per 20 kg bag)** gauging water in a clean mixing vessel. Add powder and mix the mortar with a suitable paddle attached to an electric drill until a plastic, lump-free consistency is achieved.
- 2.1.2. Allow a slake time of approx. 3 minutes for **MasterTile FLX 23**, and then remix briefly.

#### **2.2. Laying Tiles**

- 2.2.1. Apply a thin scratch coat to the substrate with the smooth edge of the trowel.
- 2.2.2. Comb mortar the **MasterTile FLX 23** onto the fresh scratch coat with a notched trowel. Apply the adhesive bed in one direction, if possible.
- 2.2.3. Apply only as much adhesive as can be covered with tiles during the open time. Check the open time by touching the adhesive with your finger tip.
- 2.2.4. Place tiles in the adhesive bed with a twist and slide motion and adjust to correct position.
- 2.3. When laying larger format single tiles in areas subject to frequent or constant contact with water use **MasterTile FLX 23** in the combined method buttering-floating, applying the adhesive to the tile and to the substrate to provide void free bedding.
- 2.4. A minimum of gap of 2mm, or as specified shall be left between tiles. Adjustments to tiles should only be made during the adhesives open wet time.
- 2.5. Remove excess adhesive from the face of the tile with a damp sponge or cloth before it sets.
- 2.6. Joints shall be raked out in readiness for grouting whilst the adhesive is still of a plastic consistency.

- 2.7. A minimum of 24 hours shall elapse before grouting.
- 2.8. Movement joints shall be provided in accordance with the specification or, if not included, to published local standards or BS 5385.

---

**STATEMENT OF RESPONSIBILITY**

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

---

---

**NOTE**

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

---