

Ucrete® IF

Iron Armoured Heavy-Duty Polyurethane Floor Finish

DESCRIPTION

Ucrete IF is a unique HD polyurethane resin floor which provides an extremely tough surface for environments subject to extreme impact and abrasion.

Its dense and impervious iron armoured surface provides protection against severe abrasion making it the ideal floor finish for applications in the waste management, heavy engineering and manufacturing industries and wherever a robust long-lived floor is required.

Ucrete Industrial Flooring has been widely used throughout industry for more than 40 years, many of the older floors are still in service. A detailed project reference list is available upon request

TYPICAL APPLICATIONS

Ucrete IF is used to protect horizontal surfaces including:

- Waste transfer station
- Transition strips
- Heavy engineering workshops
- Heavy process areas
- Under mixing heads
- Storage bunkers
- Loading docks
- Heavy equipment maintenance facilities

ADVANTAGES

- Can be applied onto 7 day old concrete or 3 day old polymer screeds
- Fully serviceable within only 24 hours (subject to temperature)
- Solvent free and non-tainting
- Specially treated iron aggregates for maximum abrasion resistance
- Long lived and low maintenance
- Steam cleanable
- No primer required, enabling rapid installation in a single application

COLOURS

Ucrete IF is available in seven standard colours:

Red	Yellow	Green	Orange
Grey	Blue	Green/Brown	

Because of the iron aggregate the colour shades are significantly different from other Ucrete flooring systems.

Ucrete floor systems have been formulated to provide the very highest chemical and heat resistance. As a direct result some yellowing of the installed floor will occur in areas of direct UV exposure. This is most apparent in lighter colours.

PERFORMANCE DATA

RAPID INSTALLATION

Specifications are available that enable **Ucrete IF** to be installed and cured within a 12 hour application window even at low temperatures.

AIR QUALITY

Ucrete has been awarded the Indoor Air Comfort Gold Label following extensive VOC emission chamber testing and auditing of quality management and production control procedures.

This demonstrates that Ucrete is an extremely clean product without any volatile compounds that might taint foodstuff or affect the well-being of personnel.

All Ucrete grades give very low emissions and conform to all the emissions requirements for indoor flooring systems in Europe including AgBB in Germany, Afsset in France, where they are rated A+ for VOC emissions (the cleanest rating), and M1 in Finland.

For further information please contact your local Master Builders Solutions representative.

Ucrete® IF

TYPICAL PROPERTIES*

Density	2800 kg/m³
Compressive strength (EN13892-2)	55 - 60 MPa
Tensile strength (BS6319 Part 7)	8 MPa
Flexural strength (EN13892-2)	17 MPa
Compressive modulus (BS 6319:Part 6)	3350 MPa
Adhesive strength to concrete (EN13892-8)	concrete failure
Fire Testing: (EN13501: Part 1)	B _{FL} – S ₁

Note: Samples cured for 28 days at 20°C

TEMPERATURE RESISTANCE

Ucrete IF floors are fully resistant to high temperature spillage and discharge up to 120°C and are fully steam cleanable

Ucrete IF is suitable for use where trafficked by racking with hot steel wheeled racks and bins, for example upon their removal from ovens or autoclaves.

NON-TAINTING

Ucrete IF is solvent free and non-tainting from the end of mixing.

IMPACT RESISTANCE

With high mechanical strengths and a low elastic modulus, **Ucrete IF** is very resilient and able to withstand severe impact loads. While no material is indestructible and surface chipping may occur, brittle modes of failure resulting in cracking and disbondment are unknown with Ucrete floors.

ABRASION RESISTANCE

The carefully selected mineral and iron aggregates impart very high abrasion resistance characteristics. In heavy wear areas the iron becomes annealed on the surface providing long term protection.

CHEMICAL RESISTANCE

Ucrete IF offers exceptional resistance to a wide range of chemical aggressors. For example, Ucrete is resistant to spillages of the following commonly encountered classes of chemicals:

Most dilute and concentrated organic acids such as, Acetic Acid, Lactic Acid, Oleic Acid and Citric Acid as commonly found in the food industry.

Dilute mineral acids: hydrochloric, nitric, phosphoric and sulphuric.

Dilute and concentrated alkalis, including sodium hydroxide to 50% concentration

Animal fats and vegetable oils, sugars flavourings and essences.

Mineral oils, kerosene, gasoline and brake fluids

A wide range of organic solvents including Methanol, Xylene Ethers and Chlorinated solvents.

Note: some staining or discolouration may occur with some chemicals depending upon the nature of the spillage and the standards of housekeeping employed.

Some strong mineral acids and oxidizing agents may cause some corrosion of the iron aggregates.

Extensive chemical resistance tables are upon request. For detailed information, please contact your local Master Builders Solutions Construction Chemicals office for guidance.

SUBSTRATE MOISTURE TOLERANCE

Ucrete Industrial Flooring is extremely tolerant to residual substrate moisture and can be installed directly onto 7 day old concrete, or onto old good quality concretes with high moisture contents without the use of special primers, provided there is a functioning DPM within the structure.

Ucrete® IF

This enables rapid construction programmes to be maintained and facilitates refurbishment work in wet process areas.

Epoxy surface DPMs should not be used as they soften under high temperature conditions and will lead to floor failure.

PERMEABILITY

Ucrete IF exhibits zero absorption when tested to CP.BM2/67/2.

SLIP RESISTANCE

The **Ucrete IF** surface profiles have coefficient of friction as determined to EN 13036 Part 4 using the 4S rubber on the wet floor as follows:

Ucrete IF 45 - 60

Optimum slip resistance can only be maintained with regular cleaning.

SPECIFICATION

The floor finish shall be **Ucrete IF** from Master Builders Solutions UK Ltd of 19 Broad Ground Road, Redditch, Worcestershire, B98 8YP, installed at a minimum 9mm in accordance with the manufacturer's instructions.

SUBSTRATE QUALITY

Concrete substrates should be visibly dry and have a minimum tensile strength of 1.5 MPa.

Refer to the guide 'The Design & Preparation of Substrates for Ucrete Industrial Flooring'

All joints in the substrate concrete subject to movement should be reflected through the Ucrete floor and sealed with a suitable sealant

CURING

Normally **Ucrete IF** floors can be put into service within 24 hours even at 8°C. Specifications are available that can be put back into service after 5 hours at 10°C.

CLEANING

Regular cleaning and maintenance will enhance the life and appearance of any floor. **Ucrete IF** is readily cleaned with industry standard cleaning chemicals and equipment. The use of alkaline based cleaners

is recommended. Please consult your local cleaning chemical or equipment supplier.

Detailed cleaning guidelines are available from your local Master Builders Solutions Construction Chemicals office.

COVERAGE

9mm: 25.5 kg/m²

Note: Above coverage rates do not include wastage.

STORAGE

In covered warehouse conditions, above 5°C and below 30°C and out of direct sunlight. Materials must be raised off the floor and kept dry. Liquid components must be protected from frost.

DISPOSAL

Part 2 containers should be decontaminated with 5% sodium carbonate (washing soda) solution after use and disposed of as building waste in accordance with local regulations.

HEALTH AND SAFETY

In its cured state Ucrete is physiologically non-hazardous.


For normal flooring applications Ucrete does not require the use of respiratory protective equipment during installation.

Operatives should consult the CoSHH risk assessment and their work instructions.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

Ucrete[®] IF

	
Master Builders Solutions UK Ltd 19 Broad Ground Road Lakeside, Redditch Great Britain B98 8YP	
04	
01110069	
EN 13813:2002	
Synthetic resin screed material	
Reaction to fire:	B _{FL} – S ₁
Release of corrosive substances:	NPD
Water permeability:	NPD
Mechanical resistance:	NPD
Wear resistance:	AR0,5
Bond strength:	B>2,0
Impact resistance:	IR>4
Sound insulation:	NPD
Sound absorption:	NPD
Thermal resistance:	NPD
Chemical resistance:	NPD
Electrical resistance:	NPD



MBS_CC-UAE/Ucr_IF_08_13/v3/10_15/v4/05_20

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions
Construction Chemicals LLC
P.O. Box 37127, Dubai, UAE
Tel: +971 4 8090800
www.master-builders-solutions.com/en-ae



A brand of
MBCC GROUP

Disclaimer: the TUV mark relates to certified management system and not to the product mentioned on this datasheet