

MasterBrace[®] ADH 2200

High strength epoxy bedding and repair mortar

DESCRIPTION

MasterBrace ADH 2200 is a solvent free, high performance, non-slumping epoxy mortar and adhesive. **MasterBrace ADH 2200** can be used as a bedding mortar, thixotropic adhesive and non-sag concrete repair mortar.

RECOMMENDED USES

- Bedding of bridge beams or steel bridge bearings
- Repairing surface defects in concrete in horizontal, vertical and overhead applications
- Fining of injection ports for MasterInject resins
- Bonding of dowels, bolts and anchors into concrete
- Rapid structural repair of concrete
- Repair of concrete posts in situ

FEATURES AND BENEFITS

- **Adheres to concrete surfaces** – Allows rapid repair of concrete
- **Solvent free** – Low VOC and non-shrink
- **Pre-proportioned packaging** – No job site errors
- **Easy application** – No primer necessary
- **High abrasion, impact and chemical resistance** – Can be used as contact surface in aggressive environments
- **Cures hard at low temperatures** – Wide application range

PERFORMANCE DATA

Mixed resin and hardener only	
Compressive Strength @ 25°C (BS 6319 part 2)	
@ 1 day	40 MPa
@ 7 day	65 MPa
Flexural strength @ 25°C (ASTM C 580 part 7)	
@ 7 day	20 MPa
Tensile Strength @ 25°C (BS 6319 Part 7)	
@ 7 day	10 MPa
Pot life in Minutes	
@ 25°C	50
@ 40°C	30

Recoat time in Hours	
@ 25°C	8
@ 40°C	6
Bond Strength	>2. MPa (concrete failure)
Setting time @ 25°C	12 Hours
Meets the requirements of ASTM C881 Type 1 Grade 3 Class B & C	

Chemical Resistance

MasterBrace ADH 2200 resists most common organic and inorganic acids in diluted form, also resistant to alkalis, water, oils, grease, etc. Chemical resistance depends on the chemicals involved, their concentration, temperature and degree of exposure. Good housekeeping practices such as immediate clean-up of all spillages will greatly extend the service life.

PROPERTIES

	Part A	Part B	Mixed
Supply Form	Paste	Liquid	Paste
Colour	Grey	Amber	Grey
Mix Ratio pbw	100	75	
Density Kg/L			1.85
Application Temperature	15°C - 35°C		

APPLICATION

Surface preparation

Remove all grease, oil, dust, residual curing compound, mould release agent or other contaminant that could impair adhesion. Laitance should preferably be removed by light sweep blasting or hydro-jetting. Mechanical wire brushing may be appropriate for small areas.

Spalled concrete should be cut back to sound concrete and made good with **MasterBrace ADH 2200** mortar. Conventional concrete curing compounds should be removed before application.

MasterBrace[®] ADH 2200

Mixing

Proportion part kits accurately mixing only what can be used in less than 30 minutes. Thoroughly stir Part A, add Part B and blend thoroughly using a slow speed mixer fitted with a suitable paddle.

Application

The **MasterBrace ADH 2200** may be placed using a trowel or spatula and applied evenly across the whole surface. Subsequent coats should be placed within 30-45 minutes and the **MasterBrace ADH 2200** should still be tacky. The use of a trowel dipped in solvent is recommended of a very smooth final surface is required.

CURING

Cure time will vary depending on the ambient temperature, quantity mixed and placed. **MasterBrace ADH 2200** will have fully cured after 7 days at 23°C.

ESTIMATING DATA

A 6 kg kit of **MasterBrace ADH 2200** will yield 3.24 litres.

PACKAGING

MasterBrace ADH 2200 comes in a 6 kg kit

SHELF LIFE

MasterBrace ADH 2200 can be stored in tightly closed original containers for 12 months at moderate temperature.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the Master Builders Solutions Material Safety Data Sheet (MSDS) from our office or our website.

® = registered trademark of MBCC Group member in many countries of the world

MAP#MasterBrace ADH 2200 v2-12.2020

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability, or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified, or rejected by the owner, engineer, or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions Malaysia Sdn Bhd

No. 8, Jalan Keluli 2, Kawasan Perindustrian Bukit Raja,
 41050 Klang, Selangor, Malaysia.
 Tel : +603 3082 1000