

MasterEase® 3003

Low Viscosity Concrete Concept

New superplasticizer technology imparts advanced rheological properties delivering a significant decrease in the viscosity of concretes and extended rheology maintenance

DESCRIPTION

The MasterEase 3003 is a superplasticizer, high range water reducer from recent research work of R & D laboratories of BASF's Master Builders Solutions. The MasterEase 3003 is designed to impart exceptional rheological properties to fresh concrete. : It improves considerably the placing and finishing of concretes and enhances the pumping of concrete plants for all construction activities.

INNOVATION

The **MasterEase 3003** is based on an innovative polymer chemistry and it is patented by BASF.

Its action differs from traditional superplasticizers, to the extent that the adsorption of polymers of **MasterEase 3003** on binder particles is provided by a flexible chemical bond which does not impede the flow of concretes. This innovation significantly improves rheological behaviour of concretes treated by **MasterEase 3003**, they have a low yield stress, low viscosity with additional feature of long workability retention.

LOW VISCOSITY CONCRETE

Low Viscosity Concrete is an innovative concept dedicated to the viscosity (rheology) of concretes. It is based on the use of **MasterEase** polymer with dedicated technical services of **Master Builders Solutions**. This concept not only allows the achievement of a significant reduction in concrete viscosity but also optimizing the performance of concrete.

MasterEase 3003: Plastic viscosities of concrete S4 has a W/C 0.45, at T_0 and T_{120}



Page 1 of 2

FEATURES AND BENEFITS

The MasterEase 3003 is recommended for the production of self-compacting concrete requiring low viscosity, long workability retention and high compressive strength. It imparts additional benefit of robustness to the addition of water or the variation of moisture content of aggregates thus reducing the likelihood of segregation to the SCC mixes.

The MasterEase 3003 is specially formulated for the concrete industry. It is also suitable for applications in the general Civil and building sites.

It can be used for the realization and achievement of the following:

- Concrete complying to EN 206-1 / CN
- Precast and Site Mix concretes
- Superior Concrete pumping
- Reduction of Concrete waste
- Ease of compacting and finishing concrete
- High performance and ultra-high strength concrete
- Concrete for low environmental impact and high in mineral additions
- Architectural concrete

PROPERTIES

The **MasterEase 3003** delivers many advantages both in the fresh concrete on hardened concrete.

At fresh state, optimizing the rheology:

Decrease in the viscosity of concretes at constant W/C

- I. Improvement of the implementation of concretes
 - Improved pumping (lower pressure and longer distance)
 - Better response to vibration
 - Greater Ease of Pumping
 - Superior finishing, floating and smoothing operations
 - Excellent flexibility, mobility and flow of self-compacting concrete.



MasterEase® 3003

Reduction possible to the W/C ratio without affecting the viscosity of concretes.

- New windows for technical and economic optimization of concrete mix designs (addition and types of binder, choice of aggregates)
- High strength and resistance to segregation
- Workability retention over 120 minutes without retardation.
- Good compatibility with all types of cement and mineral additions.

In the cured state, improvement of sustainability

- I. Excellent early and late compressive strength
- II. Improvement of quality of surface finishes
- III. As part of a reduction of W/C
 - Increased mechanical resistances
 - Decreased porosity and permeability
 - · Decreased shrinkage and cracking
 - Enhanced durability

APPLICATION

The optimal effect is generally achieved by dosing **MasterEase 3003** in the concrete mix after addition 70% of water in the mixer. However, it is possible to dose **MasterEase 3003** on aggregates directly.

DOSAGE

Recommended range: 400ml to 1500ml per 100kg cement. Other dosages can also be used depending on the specific working conditions.

For other uses, please contact your local Master Builders Solutions representative.

To use in synergy and combination with another Master Builders Solutions' product range, please consult your local representative.

PACKAGING

The **MasterEase 3003** is available in 205L drum and bulk.

SHELF LIFE

MasterEase 3003 has a 12 month shelf life from date of manufacture. It is recommended to stock it in temperature above +5°C.

PRECAUTIONS

Health: MasterEase 3003 does not contain any hazardous substances requiring labelling.

It is safe for use with standard precautions followed in the construction industry, such as use of hand gloves, safety goggles, etc.

For detailed Health, Safety and Environmental Recommendations, please consult and follow all instructions on the product Material Safety Data Sheet.

 $@= {\it registered trademark of MBCC Group member in many countries of the world } \\$

MY#MasterEase _3003 v1-1215

STATEMENT OF RESPONSIBILITY	The technical information and application advice given in this MBCC Group publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.
NOTE	Field service where provided does not constitute supervisory responsibility. Suggestions made by MBCC Group either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MBCC Group, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions Malaysia Sdn Bhd No. 8, Jalan Keluli 2, Kawasan Perindustrian Bukit Raja, 41050 Klang, Selangor, Malaysia.

Tel: +603 3082 1000