

MasterBrace[®] SAT 4500

Resin for MasterBrace FIB Fiber Reinforced Polymer Strengthening Systems

DESCRIPTION

MasterBrace SAT 4500 is an epoxy resin for use in conjunction with **MasterBrace FIB** sheets. With the chosen **MasterBrace FIB** fiber, the **MasterBrace SAT 4500** resin produces a high performance composite system for use in structural strengthening and upgrade, repair, or blast mitigation applications.

FEATURES AND BENEFITS

- Increased flexural strength
- Increased shear strength
- Increased impact resistance
- Confinement
- Blast resistance
- Fatigue enhancement
- Lightweight
- Durable
- Control of crack propagation
- Excellent strength to thickness ratio

PACKAGING

MasterBrace SAT 4500 Base	4.24kg
MasterBrace SAT 4500 Reactor	2.12kg
Total	6.36kg

YIELD

6 liters

TYPICAL PROPERTIES

Composition	Two parts (A & B)
Mixed density	1.06 kg / Lt
Color	Blue
Bond strength	>2.5 N/mm ² (Failure in concrete)
Full cure	7 days at 20°C

APPLICATION PROCEDURE PREPARATION OF SUBSTRATE

Preparation shall be by grinding or abrasive blasting to remove loose material, laitance and surface

contamination. Concrete must be, free of oils, curing compounds or mold release agents and must be thoroughly dried and free of dust at time of application. It is not always necessary to remove existing coatings. Substrates must be repaired using epoxy resin or polymer modified cementitious mortars from the **MasterEmaco** or **MasterBrace** range of repair materials. Small surface defects in concrete should be made good using **MasterBrace ADH 2200**. Concrete surface protrusions such as small projections, grouting lines etc. must be ground flat. Depressions in concrete surfaces such as a concrete joint must be filled with **MasterBrace ADH 2200**. Sharp corners must be rounded with a radius of at least 30mm.

MIXING:

Mechanically premix the **MasterBrace SAT 4500** Part A resin individually prior to adding Part B. Mechanically mix Resin Part A and Hardener Part B for 3 minutes or until homogeneous.

APPLICATION: MASTERBRACE 4500

The chosen **MasterBrace FIB** sheet must be cut to the correct length and prescribed sizes using scissors or cutters before application of **MasterBrace SAT 4500**. The number of sheets cut shall be limited to those that can be used within a day.

The mixed **MasterBrace SAT 4500** shall be applied to the **MasterBrace FIB** sheet a roller ensuring that the fibers are completely impregnated with the resin.

At the same time apply a coat of the **MasterBrace SAT 4500** resin by roller or brush to the substrate to 'wet' out the surface.

The resin saturated **MasterBrace FIB** sheet should be placed immediately fiber side down onto the concrete surface onto which the **MasterBrace SAT 4500** has been applied.

The applied FRP sheet should be squeezed only in the longitudinal direction of the fibers using a defoaming roller, rubber spatula or by hand in order to ensure that the fibers are fully impregnated with the resin and to ensure all air bubbles are removed.

MasterBrace[®] SAT 4500

Resin for MasterBrace FIB Fiber Reinforced Polymer Strengthening Systems

For joining strips of fiber sheet, a 10cm overlap length is required in the horizontal direction and 2cm overlap length in the vertical direction. Additional resin must be applied at the overlap location on top of the outer layer of fiber sheet to be overlapped.

The plastic backing sheet shall be removed from applied FRP sheet before continuing and the adhered Fiber Reinforcement System should be allowed to stand for at least 30 minutes before continuing. Any lifting or dislocation that occurs during this period must be corrected using the roller and spatula.

Where a second layer of **MasterBrace FIB** sheet is required the mixed **MasterBrace SAT 4500** should then be applied onto the cut fiber sheet then the resin impregnated second layer laid onto the initial application of fiber sheet.

Applied FRP sheet should be squeezed in the fiber longitudinal direction with a roller, spatula or by hand in order to impregnate the fiber sheet in the same manner as above.

In cases where multiple layers of fiber sheet is to be applied, the above application method for should be repeated.

MasterBrace System - overcoating

The **MasterBrace** system should be overcoated where the installed system is directly exposed to sunlight or chemicals. The chosen coating system finish should be determined by the type of exposure anticipated and should be from the Master Builders Solutions range of available coatings.

Where an Architectural plaster or render is required MasterTop SR 3 aggregate can be cast into the wet resin to act as a key for the subsequent finish.

MasterBrace SAT 4500

Estimated coverage is 0.7-1.6 Lt /m² per layer of FRP sheet depending upon the type, grade and weight of sheet chosen for the particular application.

CLEANING

Use MasterTop THN 2, Methyl Ethyl Ketone or Acetone. Observe fire and health precautions with solvents.

STORAGE

Store in cool, dry area (10 to 32°C) away from direct sunlight, flame or other hazards. **MasterBrace** fiber reinforcement materials contain carbon fibers. During application of **MasterBrace** fiber materials, wear appropriate work clothing to minimize contact. Use caution when handling flammable liquids and eliminate all sources of ignition from work area. Product Material Safety Data Sheets (MSDS) are available and should be consulted and on hand during application and/or whenever handling these products. These products are for professional and industrial use only; application directions must be followed.

SHELF LIFE

Twelve months when properly stored in unopened containers.

WATCHPOINTS

MasterBrace SAT 4500 contains reactive resins and diluents. Observe the following health and physical precautionary measures before using this product:

Wear gloves, eye protection, and appropriate work clothing to avoid contact with components. Ventilation is required with special consideration for enclosed or confined areas. Air movement must be designed to ensure turnover at all locations in work adjacent areas to avoid build-up of heavy vapors.

Do not apply the **MasterBrace** Fiber Reinforcement Systems when ambient temperature is less than 5°C.

Surfaces should be overcoated within two days when exposed to direct sunlight, or in other cases within one week to assure proper adhesion of coating to saturant.

MAINTENANCE

Periodically inspect the applied material and repair localized areas needed. Consult Master Builders Solutions Construction Chemicals Technical Services for additional information

MasterBrace® SAT 4500

Resin for MasterBrace FIB Fiber Reinforced Polymer Strengthening Systems

HEALTH AND SAFETY

*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products. As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapor until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

SOLVENT BASED PRODUCTS

Use in well ventilated areas; avoid inhaling. Suitable respiratory equipment may be needed, e.g. when spraying. Can cause skin, eye irritation. Wear protective eye shields and gloves during use. Do not smoke or allow sparks or naked lights when stored or in use.

POWDER PRODUCTS

Should be handled to minimize dust formation; use light mask if excessive dust unavoidable. Cement powders when wet or moistened can cause burns to skin and eyes which should be protected during use.

RESIN PRODUCTS

Can cause irritation, dermatitis or allergic reaction. Use protective equipment particularly for skin and eyes. Use only in well ventilated areas.

SPILLAGE

Chemical products can cause damage; clean spillage immediately.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local Master Builders Solutions representative.

Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All Master Builders Solutions Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and Master Builders Solutions ESHQ recommendations.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC-Group in many countries

CONTACT

Should you require any further information, please do not hesitate to contact us:

www.master-builders-solutions.com/en-sa
enquirycc.saudi@mbcc-group.com
M: +966 13 853 8600

Master Builders Solutions Saudi Arabia for Manufacturing LLC.
P.O. Box 1884, Al Khobar, KSA

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

Disclaimer:

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with Master Builders Solutions and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.