

MasterFlow® 400

High strength, free flowing epoxy grout

DESCRIPTION

MasterFlow 400 is a solvent free epoxy resin grout formulated to withstand static and dynamic loads in a wide variety of applications.

MasterFlow 400 is suitable for an application thickness range of 20-100mm. The product is three component and easily mixed on site, to a pourable consistency.

TYPICAL APPLICATIONS

- Crane and transporter rails.
- New and old machine base plates.
- Structural filling of holes and cavities in concrete.
- Industrial equipment and machinery subject to static or dynamic forces.
- Equipment where chemical and acid spillage occurs.
- Bridge bearings

ADVANTAGES

- No priming required
- Excellent flow characteristics
- Long pot-life
- High tensile, flexural and compressive strength
- Excellent adhesion to steel and concrete
- Rapid installation and strength gain
- High resistance to dynamic loads and chemical attack
- Non-shrink and tolerant of damp surfaces

PACKAGING / YIELD

MasterFlow 400 is supplied in Grey color and in a total pack size of 27kg.

Yield: 14 liters

TYPICAL PROPERTIES*

Pot life / Working time:	at 25°C at 40°C	60 min 30 min
**Compressive strength @25°C (ASTM C579 2007 / BS 6319)	7 days	>80N/mm ²
**Flexural strength @25°C (BS 6319 Part 3 1990)	7 days	>25N/mm ²
**Tensile strength @25°C (BS 6319 Part 7)	7 days	>10N/mm ²

Density @ 25°C Approx.	1925kg/m ³
Co-efficient of thermal expansion (ASTM C531-95):	5.65 x 10-5/°C
Effective Bearing Area (EBA) ASTM C1339	>85%

** The above properties are highly temperature dependent. Longer pot life and lower strengths to be anticipated at low ambient temperatures.

CHEMICAL RESISTANCE:

The resistance of **MasterFlow 400** to most common corrosive chemicals is excellent:

- Dilute and concentrated alkalis
- Most dilute acids
- Oil and petrol
- Ammonia
- Formaldehyde
- Saline solutions
- Mineral oil, vegetable and animal fats

CURE TIME VS. TEMPERATURE

Cure time of the grout will depend upon the temperature of the base and foundation rather than the ambient air temperature. Unless the ambient air temperature has been constant for several days the base / foundation temperature will generally be lower than air temperature. A surface thermometer and field judgement should be used to determine actual cure rates. Cured grout should have solid, almost metallic ring when struck lightly with a hammer, checking as close to the base as possible.

APPLICATION PROCEDURE SURFACE PREPARATION

As with all epoxy resin applications the quality of surface preparation has a direct effect on the performance and durability of the system.

Concrete surfaces should be sound, dimensionally stable, clean, free from laitance, paint, oil, grease, mould release agent and residual curing compound. A rough surface is preferable. Metal surfaces or components to be bedded, should be free from any rust, scaling or paint. Formwork if used should be wrapped in polythene to ensure a clean release.

MasterFlow® 400

High strength, free flowing epoxy grout

MIXING

Do not split packs or alter the ratio of resin components in any way. Mix with a slow speed drill and paddle. Add the contents of the reactor container to the base component in a suitable mixing vessel, ensuring complete transfer of both resin components. Mix for one minute before slowly adding the aggregate and continue mixing until a flowing, pourable lump free consistency is achieved. Mixing for too long can entrain air.

PLACING

Allow to stand free 5min before pouring, into the prepared area in such a manner that it has the shortest distance to flow. For long pours a suitable head of pressure may be required. Ensure the area to be grouted is not completely sealed, and any displaced air can be expelled. Pour continuously from one side only. Allow the grout to set prior to removal of formwork (normally after 6 hours). Where placement exceeds depths of 80mm, application should be carried out in layers. The second layer to be applied after 6 hours.

EQUIPMENT CARE

Clean all equipment promptly with MasterTop THN 2. Any excess cured material will have to be mechanically removed.

STORAGE

Store under cover out of direct sunlight and protect from extremes of temperature. (In tropical climates the product must be stored in an air-conditioned environment). Shelf life is up to one year when stored in unopened containers as above.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult Master Builders Solutions's Technical Services Department.

SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs (which can also be tainted with vapor until product is fully cured or dried). Treat splashes to skin and eyes immediately. If accidentally ingested, seek medical attention. Reseal containers after use. For specific storage and disposal instructions refer to the Material Safety Data Sheet.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local Master Builders Solutions representative.

Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All Master Builders Solutions Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and Master Builders Solutions ESHQ recommendations.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC-Group in many countries

MasterFlow® 400

High strength, free flowing epoxy grout

CONTACT

Should you require any further information, please do not hesitate to contact us:

www.master-builders-solutions.com/en-sa
enquirycc.saudi@mbcc-group.com
M: +966 13 853 8600

Master Builders Solutions Saudi Arabia for
Manufacturing LLC.
P.O. Box 1884, Al Khobar, KSA

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

Disclaimer:

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with Master Builders Solutions and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.