

MasterFlow[®] 544

High strength, non-shrink cementitious mortar

DESCRIPTION

MasterFlow 544 is a ready to use product in powder form, which requires only the on-site addition of water to produce a non-shrink mortar of predictable performance.

APPLICATIONS

MasterFlow 544 is formulated for use at plastic consistency, and may be used with confidence for bedding, repairing, grouting and void filling operations such as:

- Concrete repairs.
- Void filling between old and new concrete.
- Floor patching.
- Packing under columns and stanchions.
- Caulking of concrete pipes.
- Filling tie-bar holes.
- Re profiling of stanchion or mast bases when formwork is undesirable.
- Pile cap reprofiling and encapsulation.

ADVANTAGES

- Non shrink
- Adjustable consistency
- Proven and predictable performance
- Trowel able
- High bond strength to steel and concrete
- Early strength development even at pourable consistency
- Good fatigue and impact resistance
- Impermeable

PACKAGING

MasterFlow 544 is supplied in 25kg bags.

APPLICATIONPROCEDURE

SURFACEPREPARATION:

All surfaces in contact with the material must be sound, dense and clean. All laitance and any unsound material should be removed - an evenly scraped, slightly textured surface is required, with all dust and dirt removed. (Note: heavy scabbling, creating deep troughs or high peaks is unsuitable). Surfaces must be pre-wetted to thoroughly dampen the concrete, but any free surface water must be removed before **MasterFlow 544** is placed.

For large areas of application, such as floor toppings or concrete repair, **MasterBrace ADH 1414** epoxy bonding agent should be used on the interface to ensure total bond.

Feather edging is not recommended. Minimum acceptable depth is 10mm. Maximum recommended depth for toppings is 50mm.

MIXING:

First dry mix contents of bag, then thoroughly mix with the specified amount of water.

PLASTICCONSISTENCY:

Add 3.9 liters of water to one 25kg bag and mix thoroughly.

POURABLECONSISTENCY:

Add 4.4 liters of water to one 25kg bag and mix thoroughly.

NOTES:

- To achieve the properties described, water additions should be accurate to + 0.1 liter.
- Water should be slowly added over a 1½ minute period and then mixing continued for a further 2 minutes.
- It is important that a forced action mixer is used to ensure complete dispersion of the water and thorough mixing thereafter.

PLACING:

All of the mix should be placed within 45 minutes of water addition. No water should be added for re-tempering.

Placing must not take place below 5°C. Below 8°C it is advisable to tent before placing, to warm the substrate to 8°C minimum, and subsequently to maintain the placed mortar at 8°C minimum.

For plastic consistencies tamping is essential to achieve good compaction. Do not vibrate.

MasterFlow® 544

High strength, non-shrink cementitious mortar

CURING:

Curing of the exposed surfaces of **MasterFlow 544** must commence immediately. Following placement the exposed surfaces must be continuously cured at moderate temperatures for seven days after finishing operations. This will prevent early drying shrinkage and help to develop strength, durability and other desired properties. Any deficiencies in the method of curing may also reduce the amount of initial expansion which is needed to offset later drying shrinkage. The use of **MasterKure** curing compounds is strongly recommended.

GROUTING SPACE USING PLASTIC MORTAR:

Formwork is erected on 3 sides (and is prepared for the fourth). Plastic mortar is rammed into place, filling all voids. Without delay, a vertical or sloping form is fixed on the fourth side, the grout is surcharged and is consolidated by thorough hand punning (i.e., caulking by ramming). Just before final set, the surplus grout is removed.

TYPICAL PROPERTIES*:

When mixed with 3.9 liters of water a 25kg bag will have the following properties:		
Compressive Strength N/mm ² (ASTM C109)	24 hrs.	29.0
	3 days	34.0
	7 days	50.0
	28 days	55.0
Tensile Strength N/mm ² (BS 6319 : Part 7)	24 hrs.	1.5
	3 days	3.2
	7 days	3.8
	28 days	4.0
Flexural Strength N/mm ² (BS 4551)	24 hrs.	4.5
	3 days	8.0
	7 days	9.0
	28 days	10.0
Initial Surface Absorption (ISAT BS 1881 : Part 111)	10 mins	0.02
	30 mins	0.01
	60 mins	<0.01
	120 mins	-

STORAGE

Store out of direct sunlight, clear of the ground on pallets protected from rainfall. Avoid excessive compaction. Storage life is approximately 12 months when stored as above in original sealed bags

PRECAUTIONS

The temperature of both the grout and elements coming into contact with the grout should be in the range of +5°C to +35°C. Do not use water in an amount or at a temperature that will produce a consistency more than fluid or cause mixed grout to bleed or segregate.

DO NOT OVERWORK AND AVOID USING MECHANICAL VIBRATION.

UNDER NO CIRCUMSTANCES SHOULD **MasterFlow 544** BE RETEMPERED BY THE LATER ADDITION OF WATER.

It is essential that a mechanically powered grout mixer is used to obtain the optimum properties.

Do not use water in an amount or at a temperature that will produce a consistency more than flowable or cause mixed grout to bleed or segregate.

MasterFlow 544 should be laid at a minimum thickness of 25mm and up to a depth of 125mm.

YIELD / CONSUMPTION

12.9 - 13.4 ltr / 25kg bag dependent on water addition rate.

78 x 25kg bags / m³.

NOTE:

For free flowing grouting operations consider the use of **MasterFlow 526**. Precision grouting of heavy machinery use **MasterFlow 928 T** or in critical operating conditions; **MasterFlow 885**.

When a very rapid set is required in areas subject to chemical spillage or contamination, use epoxy grouts **MasterFlow 400/ MasterSeal 915**.

For additional information on MasterFlow 544 mortar or other non-shrink grouting and repair materials, contact your Master Builders Solutions representative

MasterFlow® 544

High strength, non-shrink cementitious mortar

SAFETY PRECAUTIONS

As with other products containing Portland cement, the cementitious material in **MasterFlow 544** mortar may cause irritation. In case of contact with eyes, immediately flush with plenty of water for at least 15 minutes. Call a physician. In case of contact with skin, wash skin thoroughly.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local Master Builders Solutions representative.

Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All Master Builders Solutions Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and Master Builders Solutions ESHQ recommendations.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC-Group in many countries

CONTACT

Should you require any further information, please do not hesitate to contact us:

www.master-builders-solutions.com/en-sa
enquirycc.saudi@mbcc-group.com
M: +966 13 853 8600

Master Builders Solutions Saudi Arabia for
Manufacturing LLC.
P.O. Box 1884, Al Khobar, KSA

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

Disclaimer:

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with Master Builders Solutions and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.