

# MasterFlow<sup>®</sup> 928T

High strength, non-shrink cementitious grout

## DESCRIPTION

**MasterFlow 928T** is a ready to use product in powder form, which requires only the on-site addition of water to produce a non-shrink grout of predictable performance.

## APPLICATIONS

**MasterFlow 928T** is formulated for use at any consistency from fluid to damp-pack, and may be used with confidence for bedding, grouting and precision bearing operations such as:

- Gas or steam turbines
- Generators
- Presses
- Crane rails
- Milling machines
- Precast elements
- Anchor bolts
- Suitable for use in bridge bearing applications

## ADVANTAGES

- Non shrink.
- Adjustable consistency.
- Proven and predictable performance.
- Excellent workability retention even at high ambient temperatures.
- High bond strength to steel and concrete.
- Early strength development even at fluid consistency.
- Good fatigue and impact resistance.
- Micro silica content enhances strength and durability.
- Impermeable.

## PACKAGING

**MasterFlow 928T** is supplied in 25kg moisture resistant bags.

## STANDARDS

Complies with CRD-C 621  
ASTM C1107 - Grade B

## APPLICATION PROCEDURE

### PREPARATION:

The surface onto which the grout is to be applied should be scraped to remove laitance and expose aggregate. Do not use bush hammers or similar preparation equipment that can crush the aggregate but leave it in place. The surface must be free of oil, dust, dirt, paint, curing compounds, etc. Soak area to be grouted with water for 24 hours prior to grouting to minimize localized absorption and to assist in the free flow of the grout. Surfaces should be damp but free of standing water.

Particular attention should be paid to bolt holes to ensure that these are water-free. Use oil free compressed air to blow out bolt holes and pockets as necessary.

Base plate, bolts, etc. must be clean and free of oil, grease and paint etc. Set and align equipment. If shims are to be removed after the grout has set; lightly grease them for easy removal. Ensure formwork is secure and watertight to prevent movement and leaking during the placing and curing of the grout. The area should be free of excessive vibration. Shut down adjacent machinery until the grout has hardened. In hot weather, base plates and foundations must be shaded from direct sunlight. Bags of grout should be stored in the shade prior to use.

In cold weather, the temperature of base plates and foundations should be raised to >10°C.

### MIXING:

In hot weather use cool water to bring the mixed grout temperature to <30°C.

In cold weather use warm water to raise the mixed grout temperature to >10°C.

Damp down the inside of the grout mixer with water prior to mixing the initial batch of **MasterFlow 928T**. Ensure the mixer is damp but free of standing water. Add the pre-measured quantity of water. Slowly add the **MasterFlow 928T**, mixing continuously. Mix for at least five minutes until a smooth, uniform, lump free consistency is achieved.

# MasterFlow® 928T

High strength, non-shrink cementitious grout

## PLACING

Lengths of metal strapping laid in the formwork prior to placing may be necessary to assist grout flow over large areas and in compacting and eliminating air pockets. Pour the grout continuously. Maintain a constant hydrostatic head, preferably of at least 15 cm.

On the side where the grout has been poured, allow 10 cm clearance between the side of the form and the base plate of the machine.

On the opposite side allow 5-10 cm clearance between the formwork and the base plate. **MasterFlow** grouts are suitable for use with most types of pumping equipment.

Immediately after **MasterFlow 928T** grout is placed, cover all exposed grout with clean damp hessian, and keep moist until grout is firm enough to accept a curing membrane.

Should the grout shoulders require finishing work, this should be carried out prior to application of the curing membrane. We recommend the use of a curing membrane from our **MasterKure** range.

## SHOULDERS

Due to differences in temperature between the grout under the base plate, and exposed shoulders that are subject to more rapid temperature changes, debonding and / or cracking can occur. Avoid shoulders wherever possible.

If shoulders are required they should be firmly anchored with reinforcing to the substrate to prevent debonding.

## TYPICAL WATER REQUIREMENTS TABLE 1

Application	Consistency	Flow Table\$	Flow Cone*	Mix Water liters/ 25kg	
				Min	Max
Grouting machinery	Fluid	-	20-30	4.5	5
Grouting machinery	Flowable	130	-	3.5	4
Bedding Precast	Plastic	60	-	3.0	3.5
Filling Tie bar voids	Dry pack	-	-	2.0	2.5

\*Properties listed are based on laboratory controlled tests. ASTM C939 (formerly CRD-C 79)  
 \$:ASTMC230/ASTMC827

## FLOWABLE GROUTING TECHNIQUES




Diagram A illustrates the use of grout surcharge to ensure complete filling under a base.

Diagram B shows that straps can be used to aid grout flow under a wider base. A gentle “sawing” action with the strap allows the grout to flow without segregation for greater distances.

## TYPICAL PROPERTIES STRENGTH DEVELOPMENT

The strength of grout is dependent on many factors which include mixing, water addition, curing, temperature and humidity. The table below gives typical average strengths of **MasterFlow 928T** at 25°C, when mixed with 4.5 liters (fluid) per 25kg bag.

For compressive strength 100mm cubes and flexural strength 40 x 40 x 160mm prisms were used.

	Compressive Strength	Flexural Strength
Time	Fluid N/mm <sup>2</sup>	Fluid N/mm <sup>2</sup>
1 day	20	4.0
3 days	35	6.0
7 days	45	8.0
28 days	60	9.0

# MasterFlow<sup>®</sup> 928T

High strength, non-shrink cementitious grout

## BLEED WATER

No bleed water is apparent (ASTM C-232) at recommended water addition rates.

## EXPANSION:

Tests were made following both ASTM Standard C-878, on the use of expansive cements and Corps of Engineers Standard for grout. Tests made as prescribed by ASTM standard C-878 show an expansion value of about 0.05%. Tests in conformity with Corps of Engineers show an expansion value of 0.3% that is lower than the maximum value (0.4%) fixed by the same standards. Moreover, **MasterFlow 928T** expansion occurs both in the plastic and in the early hardened state. However, the expansion action of **MasterFlow 928T** exhausts mainly during the first 12 hours of curing.

## MODULUS OF ELASTICITY

The static modulus of elasticity, measured by applying a load corresponding to 1/3 of the strength, is approximately 28,000 N/mm<sup>2</sup> at 28 days.

## FATIGUE RESISTANCE:

Cube samples, produced with **MasterFlow 928T** and cured for a month, underwent fatigue tests of 2,000,000 pulsing stresses ranging between 20 and 50 N/mm<sup>2</sup> at a frequency of 500 cycles/min. Tested specimens were undamaged and their compressive strength was higher than that of similar specimens that were not subjected to fatigue tests.

## BOND TO CONCRETE:

Typical direct tensile “pull off” testing indicates a bond to concrete in the region of 2-4Mpa.

## BOND TO STEEL:

The bond of **MasterFlow 928T** to steel calculated by applying loads to the bars undergoing pull-out tests and by the grout steel contact surface is 3 N/mm<sup>2</sup> at 7 days and 4 N/mm<sup>2</sup> for plain bars ;20 N/mm<sup>2</sup> at 7 days and 30 N/mm<sup>2</sup> at 28days for deformed bars

## WORKABILITY

Tests at the fluid consistency performed according to ASTM C939, show compliance with the requirements of CRD-C 621-82.

## CAPILLARY PORES AND PERMEABILITY

Even under a pressure of 20 atm, water does not penetrate **MasterFlow 928T** specimens. The permeability factor is calculated to be therefore lower than 1.10-12 cm/sec.

## RESISTANCE TO CHEMICAL ATTACK:

Thanks to its water tightness, **MasterFlow 928T** grout is protected against environmental aggressive agents in solution.

## RESISTANCE TO HIGH TEMPERATURE:

**MasterFlow 928T** grouts can withstand high temperature (+400°C) for very long periods without deteriorating substantially.

## RESISTANCE TO LOW TEMPERATURE:

After 300 freezing and thawing cycles, the modulus of elasticity decreases only 5%. This indicates that **MasterFlow 928T** is highly resistant to the disrupting action of frost.

## STORAGE

Store out of direct sunlight, clear of the ground on pallets protected from rainfall. Avoid excessive compaction. Storage life is approximately 12 months when stored as above in original sealed bags.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult Master Builders Solutions's Technical Services Department.

## PRECAUTIONS

The temperature of both the grout and elements coming into contact with the grout should be in the range of >10°C to >35°C. Do not use water in an amount or at a temperature that will produce a consistency more than fluid or cause mixed grout to bleed or segregate.

**MasterFlow 928T** should be laid at a minimum thickness of 10mm and to a maximum depth of 80mm.

# MasterFlow® 928T

High strength, non-shrink cementitious grout

For applications above 80mm consider the use of **MasterFlow 980**. For applications below 10mm consult Master Builders Solutions's Technical Services Department for advice.

To simulate on-site conditions it is necessary to restrain cubes for the first 24 hours immediately after casting.

DO NOT OVERWORK AND AVOID USING MECHANICAL VIBRATION.

UNDER NO CIRCUMSTANCES SHOULD MASTERFLOW® 928T BE RETEMPERED BY THE LATER ADDITION OF WATER.

It is essential that a mechanically powered grout mixer is used to obtain the optimum properties.

## YIELD/CONSUMPTION

13.8 liters/25kg bag at 5 liters water addition rate.  
73 x 25kg bags / m<sup>3</sup>

## WARNING

As with other products containing Portland cement, the cementitious material in **MasterFlow 928T** grout may cause irritation. Avoid contact with eyes and prolonged irritation. In case of contact with eyes, immediately flush with plenty of water for at least 15 minutes. Call a physician. In case of contact with skin, wash skin thoroughly.

## NOTE

The fatigue and impact resistance of **MasterFlow 928T** grout is exceeded only by the metallic reinforced, non-catalyzed **MasterFlow 4800** grout. The specially prepared metallic aggregate in this product contributes to impact resistance, a desirable property of grout to be subjected to severe dynamic operating forces and

repetitive loading such as found in steel and aluminum rolling mills, crane rails, heavy presses, etc.

When a very rapid set is required in areas subject to chemical spillage or contamination, use epoxy grouts **MasterFlow 400** or **MasterFlow 648**.

For additional information on **MasterFlow 928T** grout or other non-shrink grouting materials, contact your local Master Builders Solutions representative.

## QUALITY AND CARE

All Master Builders Solutions Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and Master Builders Solutions ESHQ recommendations.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC-Group in many countries

## CONTACT

Should you require any further information, please do not hesitate to contact us:

[www.master-builders-solutions.com/en-sa](http://www.master-builders-solutions.com/en-sa)  
[enquirycc.saudi@mbcc-group.com](mailto:enquirycc.saudi@mbcc-group.com)  
M: +966 13 853 8600

Master Builders Solutions Saudi Arabia for Manufacturing LLC.  
P.O. Box 1884, Al Khobar, KSA

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## Disclaimer:

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with Master Builders Solutions and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.