

MasterKure® 106

Water based concrete curing compound / bond breaker

DESCRIPTION

MasterKure 106 is a solvent free, membrane forming wax emulsion, suitable for spray application to freshly poured concrete.

The resultant film retains sufficient moisture in the concrete to ensure full hydration of the cement; essential for optimum strength development. Membrane cured concrete is typically harder and exhibits a dust free surface with a reduced incidence of drying shrinkage cracks.

The film can also act as a bond breaker between initial and subsequent concrete pours.

PRIMARY USES

As a more effective and economical alternative to hessian and water and polythene curing regimes. Suitable for use on all concrete surfaces.

As a bond breaking film for the vertical face of precast bridge segments during match casting.

ADVANTAGES

- Eliminates the need for water.
- Single application.
- Promotes a harder dust free surface.
- Cured film is clear and water repellent.
- Reduces drying shrinkage.
- High curing efficiency.
- Reduced labor costs.
- Water based.

PACKAGING

MasterKure 106 is available in 210 liter drums.

TYPICAL PROPERTIES

Appearance:	White liquid
Specific gravity:	1.00
Flashpoint:	Not applicable
Finished film appearance:	Clear, tack free, water repellent film
Water retention ASTM C156:	Pass
Drying time ASTM C309:	Less than 4 hours

STANDARDS

ASTM C309 Type 1 Class A

AASHTO M-148 Type 1 Class A

DIRECTIONS FOR USE AS A CURING COMPOUND

The compound should be spray applied as evenly as possible on to the freshly placed concrete.

For horizontal surfaces **MasterKure 106** should be applied as soon as the initial surface sheen has disappeared from the concrete surface. In the case of formed concrete, the **MasterKure 106** should be applied immediately on removal of the formwork. To assist breakdown of the **MasterKure 106** film on vertical and formed surfaces, it is essential to dampen down the concrete with clean water prior to application.

DIRECTIONS FOR USE AS A BOND BREAKER

The compound should be spray applied to form an even film covering the entire surface against which the subsequent segment will be cast.

If necessary more than one coat should be applied. The actual coverage and number of coats will be dependent on texture and porosity of the surface. The recommended application rate when used as a bond breaker is 4 square meters per liter.

COVERAGE

The recommended rate of application is 5-6 square meters per liter. This corresponds to that at which **MasterKure 106** has been tested, and at which it attains the claimed degree of curing efficiency. In favorable conditions such as shaded interior surfaces, adequate curing can be achieved with extended coverage rates.

FILM BREAKDOWN

The time for deterioration of the membrane is dependent on a number of variables, which include film thickness, degree of exposure to weathering, traffic, UV light, and the porosity of the substrate concrete.

MasterKure® 106

Water based concrete curing compound / bond breaker

SUBSEQUENT SURFACE FINISHES

It is important that the complete removal of the **MasterKure 106** should be ensured prior to the application of any surface finish or additional treatment. It is recommended that where the concrete is to receive a coating or the application of tiles, the use of **MasterKure 181** is considered.

MasterKure 181 is a resin based non-degrading curing membrane meeting the requirements of ASTM C-309 Type 1 Class B. It is additionally formulated to act as a primer for many finishes or to seal concrete surfaces and provide a degree of abrasion to flatwork.

SPECIFICATION CLAUSE

Where indicated, concrete shall be cured by application of **MasterKure 106**, membrane forming wax emulsion manufactured by Master Builders Solutions or similar approved; to the following specification:

Specification type:

ASTM C309: Type 1 Class A

AASHTO M-148

MasterKure 106 is to be applied at a coverage rate of 5 to 6 square meters per liter and strictly in accordance with the manufacturer's instructions.

STORAGE

Shelf life is up to 12 Months when stored under cover, out of direct sunlight and protected from extremes of temperature.

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical

attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local Master Builders Solutions representative.

Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All Master Builders Solutions Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and Master Builders Solutions ESHQ recommendations.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC-Group in many countries

CONTACT

Should you require any further information, please do not hesitate to contact us:

www.master-builders-solutions.com/en-sa

enquirycc.saudi@mbcc-group.com

M: +966 13 853 8600

Master Builders Solutions Saudi Arabia for Manufacturing LLC.

P.O. Box 1884, Al Khobar, KSA

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

Disclaimer:

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with Master Builders Solutions and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.