

# MasterLife<sup>®</sup> CI 222

Organic corrosion inhibiting admixture

## DESCRIPTION

Inhibiting admixture formulated to inhibit the corrosion of steel reinforcement in concrete. **MasterLife CI 222** provides two levels of corrosion protection, inhibiting and waterproofing making it the most effective corrosion inhibiting admixture available.

## ADVANTAGES

**MasterLife CI 222** extends the service life of reinforced concrete by slowing the ingress of chlorides and moisture into the concrete and by forming a strong, durable protective film on the reinforcing steel for a second level of corrosion protection. This dual mechanism system makes **MasterLife CI 222** effective with all cement factors, as well as in cracked concrete where the elements that cause corrosion have direct access to the reinforcing steel.

## PACKAGING

**MasterLife CI 222** is available in 208 litre drums and bulk if required.

## STANDARDS

ASTM G-109

## HOW IT WORKS

**MasterLife CI 222** functions by inhibiting corrosion at its most critical points. **MasterLife CI 222** lines the pores of the concrete matrix thus waterproofing and slowing the rate at which chlorides and moisture enter the concrete and denying the corrosion process of its two most important components.

**MasterLife CI 222** provides additional protection by adsorbing onto the reinforcing steel to form a corrosion resistant protective film. This protective film dramatically slows the corrosion process by preventing chlorides from reacting with the reinforcing steel, and by depriving the corrosion process of moisture and oxygen, thus slowing the rate of corrosion once it begins.

## PLASTIC PROPERTIES

The plastic properties of concrete are not significantly affected by the use of **MasterLife CI 222**

## SLUMP AND TEMPERATURE DEVELOPMENT

**MasterLife CI 222** has no effect on slump or the temperature development profile of concrete.

## CONCRETE-STEEL BOND STRENGTH

Concrete to steel bond strength is not affected by **MasterLife CI 222**.

## CORROSION INHIBITING SYSTEMS

In order to control corrosion in steel reinforced concrete, the ACI Building Code (ACI 318) requires certain design considerations, such as limiting the water-cementitious materials ratio; providing adequate concrete cover over reinforcing steel; and limiting the initial chloride ion content of the concrete. Additionally, construction practices should be such that a dense, void-free concrete is obtained.

In addition to the elements of good concrete practice required by the ACI Building Code, Master Builders Solutions recommends a corrosion inhibiting system that inhibits corrosion at multiple levels for maximum protection.

The basis for this system can be established through the use of **MasterLife CI 222** which restricts the ingress of chlorides and moisture and slows the rate of corrosion by forming a protective film on the reinforcing steel. Additional protection can be attained through the use of high-range water-reducing admixtures to provide adequate placeability and consolidation at low water-cement ratios and/or the use of silica fume admixtures to reduce concrete permeability.

## DOSAGE

**MasterLife CI 222** is recommended for use at a dosage rate of 5 litre / m<sup>3</sup> of concrete for all applications and corrosion environments. **MasterLife CI 222** dosed at 5 litre / m<sup>3</sup> is formulated to provide optimum corrosion protection of reinforced concrete structures in severe corrosive environments, and therefore provides excellent corrosive protection in less severe corrosion environments as well.

# MasterLife® CI 222

## Organic corrosion inhibiting admixture

**MasterLife CI 222** is formulated for use at a single dosage in order to eliminate the confusion and uncertainties related to determining the severity of the corrosive environment and predicting the chloride exposure of the structure.

### DIRECTIONS FOR USE

**MasterLife CI 222** may be added with concrete batch water. It should not be mixed with any other admixtures prior to being introduced into the concrete mixer. The use of this admixture does not require changes in normal batching procedures.

### WATCHPOINTS

Trials must be carried out to ensure mix design meets specified performance criteria.

### TEMPERATURE PRECAUTION

Store at ambient temperatures above 2°C but not exceeding 52°C. Precautions should be taken to protect **MasterLife CI 222** from freezing. If product freezes, thaw and reconstitute by mild mechanical agitation. Do not use pressurised air for agitation.

### NON-CHLORIDE

**MasterLife CI 222** will not initiate or promote corrosion of reinforcing steel embedded in concrete, prestressed concrete or concrete placed on galvanised steel floor and roof systems. Neither calcium chloride nor any chloride-based ingredients are used in the manufacture of **MasterLife CI 222** corrosion inhibiting admixture.

### SAFETY PRECAUTIONS

**MasterLife CI 222** is not a fire or health hazard. Spillages should be washed down immediately with cold

water. For further information refer to the material safety data sheet.

### NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local Master Builders Solutions representative.

Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

### QUALITY AND CARE

All Master Builders Solutions Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and Master Builders Solutions ESHQ recommendations.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC-Group in many countries

### CONTACT

Should you require any further information, please do not hesitate to contact us:

[www.master-builders-solutions.com/en-sa](http://www.master-builders-solutions.com/en-sa)  
[enquirycc.saudi@mbcc-group.com](mailto:enquirycc.saudi@mbcc-group.com)

M: +966 13 853 8600

Master Builders Solutions Saudi Arabia for Manufacturing LLC.

P.O. Box 1884, Al Khobar, KSA

#### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

#### Disclaimer:

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with Master Builders Solutions and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.