

MasterLife[®] SRA 50

Expanding plasticizing admixture for cement, grout and concrete

DESCRIPTION

MasterLife SRA 50 is an expansion system which compensates for plastic shrinkage and settlement in cementitious grouts. Supplied in powder form, **MasterLife SRA 50** produces controlled expansion in cement grouts and maintains high water retention. It contains a water-reducing agent which increases the workability of the mix with a reduced water content, making a stronger grout.

Full expansion is achieved before initial setting occurs resulting in a high degree of interfacial contact.

APPLICATIONS

For bedding, jointing, duct grouting and void filling applications where the following characteristics are beneficial:

- A cement plasticizing and water reducing agent to improve the free flowing properties of the grout at low water/cement ratios.
- For post tensioning of cables
- An expanding agent, that increases the volume of the grout which in turn eliminates shrinkage and settlement.
- A catalyst to control the rate of expansion and to ensure full expansion of the grout.

(For precision grouting and load bearing operations use **MasterFlow** grouts.)

PACKAGING

MasterLife SRA 50 is available in 20kg bags.

TYPICAL PROPERTIES*

Color	:	Brown/grey powder
Chloride content	:	Nil to BS 5075 : 1982
Nitrate content	:	Nil
Freezing point	:	N/A
Flash point	:	None
Dosage	:	500gm/100kg cement

EXPANDING PROPERTIES

The expansion of grouts containing **MasterLife SRA 50** is sufficient to overcome normal settlement without producing undue pressure against the sides of the duct. The grout therefore forms a firm and uniform bond to the concrete and to the steel along the length of the tendon , and at the same time provides good protection for the cable. The expansion obtained by the use of **MasterLife SRA 50** reaches a maximum within 1 - 2½ hours of

mixing under average temperature conditions. After this period no settlement occurs, and the grout retains its maximum expansion.

MasterLife SRA 50 produces a maximum expansion of 3.25% in a neat cement grout, and 2% expansion in a 1:1 sand/cement grout.

PLASTICISING PROPERTIES

MasterLife SRA 50 imparts fluidity to grout, even at reduced water/cement ratios, and because of the water reducing action, higher compressive strengths are obtained.

Compressive strength (N/mm²) after 7 days

	Neat cement grout	Sand/cement grout 1:1
Control	27.0	21.8
Masterlife SRA 50	29.2	24.3

DIRECTIONS FOR USE

First add the water to the mixer and then the Portland cement, mix thoroughly until the cement has been completely dispersed. Then add the **MasterLife SRA 50** and sand (if any is being used), and continue mixing a further 2 minutes or until complete dispersion of the **MasterLife SRA 50** is achieved.

The type of mixing equipment generally used in preparing cement grouts is that which will produce a high local turbulence thus ensuring an efficient breakdown and dispersion of the cement.

Grouts for ducts of post-tensioned concrete members should be passed through a 1.18mm BS sieve before reaching the pump, and the pump should be capable of giving a continuous flow of grout to the injection equipment.

DOSAGE

MasterLife SRA 50 is used at the rate of 500gm per 100kg cement in the grout, and can be used either with ordinary Portland cement or Rapid Hardening Portland cement.

During the winter months when temperatures may fall to between 7°C and 1°C, it is recommended that Rapid Hardening Portland cement should be used in grouts for filling the ducts of post-tensioned concrete members.

Recommended grout specifications for grouting ducts of post-tensioned concrete members:

MasterLife[®] SRA 50

Expanding plasticizing admixture for cement, grout and concrete

1. Neat cement grout:

Ordinary Portland cement :	100kg
MasterLife SRA 50 :	500gms
Water :	Not >50 liters

2. Cement sand grout

Ordinary Portland cement :	100kg
Sharp graded sand :	100kg
(passing 1.18mm mesh sieve)	
MasterLife SRA 50 :	500gms
Water :	Not >54 liters

SPECIFICATION CLAUSE:

MasterLife SRA 50, manufactured by Master Builders Solutions, or similar approved, is to be incorporated in grouts where indicated.

The **MasterLife SRA 50** shall be added at the rate of 500gm per 100kg Portland cement and used strictly in accordance with the manufacturer's recommendations.

SAFETY PRECAUTIONS:

As with all chemical products, care should be taken during use and storage to avoid contact with the eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention. Keep away from children and animals. Reseal containers after use.

STORAGE:

Store out of direct sunlight, clear of the ground on pallets protected from rainfall. Avoid excessive compaction. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult Master Builders Solutions's Technical Services Department. Shelf life is 6 month when stored as above.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local Master Builders Solutions representative.

Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All Master Builders Solutions Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and Master Builders Solutions ESHQ recommendations.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC-Group in many countries

CONTACT

Should you require any further information, please do not hesitate to contact us:

www.master-builders-solutions.com/en-sa
enquirycc.saudi@mbcc-group.com
M: +966 13 853 8600

Master Builders Solutions Saudi Arabia for
Manufacturing LLC.
P.O. Box 1884, Al Khobar, KSA

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

Disclaimer:

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with Master Builders Solutions and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.